Det här verket har digitaliserats vid Göteborgs universitetsbibliotek. Alla tryckta texter är OCR-tolkade till maskinläsbar text. Det betyder att du kan söka och kopiera texten från dokumentet. Vissa äldre dokument med dåligt tryck kan vara svåra att OCR-tolka korrekt vilket medför att den OCR-tolkade texten kan innehålla fel och därför bör man visuellt jämföra med verkets bilder för att avgöra vad som är riktigt.

This work has been digitized at Gothenburg University Library. All printed texts have been OCR-processed and converted to machine readable text. This means that you can search and copy text from the document. Some early printed books are hard to OCR-process correctly and the text may contain errors, so one should always visually compare it with the images to determine what is correct.

SOLVENT-ASSISTED DYEING OF WOOL

BY

MARIANNE KÄRRHOLM

GÖTEBORG 1960

SOLVENT-ASSISTED DYEING OF WOOL

BY

MARIANNE KÄRRHOLM

AKADEMISK AVHANDLING

som med tillstånd av Chalmers Tekniska Högskola för
teknologie doktorsgrads vinnande till offentlig gransk-
ning framlägges å föreläsningssalen för fysik, Gibraltar-
gatan 5 B, Göteborg, lördagen den 2 april 1960 kl. 10.

GÖTEBORG 1960

**SOLVENT-ASSISTED DYEING
OF WOOL**

BY

MARIANNE KÄRRHOLM

TO MY MOTHER

TO MY HUSBAND

ERRATA

to the paper SOLVENT-ASSISTED DYEING OF WOOL by Marianne Kärrholm

p.11, line 3: "out" change to "cut"

line 6: "thermostate" change to "thermostat"

p.17, line 15: "gives" change to "give"

p.28, line 9 from the bottom: "coloumn" change to "column"

p.31, table 3, heading: "millimol/l" change to "millimol/100 ml"

column 3: "13.2, 25.8, 50.8, 75.2" change to
"13.3, 26.4, 52.0, 77.4"

line 3 from the bottom: "conficence" change to "confidence"

p.32, abscissa: "millimol/l" change to "millimol/100 ml"

p.33, The formula should be:

p.40, line 8 from the bottom: "increases" change to "increased"

p.43, line 3: "chapter 4.3" change to "chapter 3.3"

line 16: "previous" change to "previously"

line 3 from the bottom: "is" change to "are"

p.45, table 8, column 4, line 14 from the bottom: "0.061" change to "0.614"

p.60, line 8 from the bottom: "percentages" change to "percent"

p.62, line 4: "in" change to "for"

p.70, line 11: "Courmonts" change to "Courmont"

p.77, line 6 from the bottom: "conslusions" change to "conclusions"

p.90, line 11: "wool" change to "Wool"

To the Bibliography should be added:

Moncrieff, R.W. - Wool Shrinkage and its Prevention. London 1953.

Whewell, C.S. and Selim, A. - The Action of Halogens on Wool. Part I.

J.Soc.Chem.Ind. (London) 63 (1944), p. 121.

CONTENTS

	<u>Page</u>
INTRODUCTION	7
Terminology	9
1. PRELIMINARY INVESTIGATIONS	10
1.1 Degree of sulphonation of dye	10
1.2 "Extraction" effect of solvent	13
1.3 Concentration of alcohol	16
1.4 Temperature of dyebath	16
1.5 Surface-treatment of wool	17
1.6 Dye distribution between different fibres	17
2. INVESTIGATION OF SOME FACTORS OF IMPORTANCE TO THE DYEING MECHANISM	21
2.1 Raw material	22
2.2 Adsorption of alcohol and dyestuff on wool from aqueous solutions	24
2.3 Dyeing at different pH-values	37
2.4 Dyeing of surface-treated wool	43
2.5 Influence of solvents on stress relaxation and swelling of wool fibres	58
3. GENERAL DISCUSSION OF THE MECHANISM OF SOLVENT-ASSISTED DYEING OF WOOL	62
3.1 The effect of a solvent layer	64
3.2 Loosening of the fibre structure	70
3.3 Diffusion of dye in the adsorbed solvent	72
4. INDUSTRIAL EXPERIMENTS ON LOOSE WOOL DYEING	75
4.1 Performance of the experiments	76
4.2 Results and conclusions	77
SUMMARY	83
ACKNOWLEDGEMENTS	87
BIBLIOGRAPHY	88

INTRODUCTION

The main difficulties in open width continuous dyeing of wool fabrics arise from the low rate of dyeing and the selectivity of the wool fibre surface towards many dyestuffs, resulting in uneven dyeing. The dyeing rate may be increased either by changing the properties of the wool fibre surface by chlorination or alkaline treatments, or by using dye assistants in the dyebath. The selectivity of the wool fibre surface may be decreased by chemical treatments (Barritt, Elsworth, 1948, and Lindberg, 1953), or by using special dyestuffs (Schetty, 1955). In 1956 Peters and Stevens showed that the introduction of small amounts of an organic solvent may increase the dyeing rate of wool to an appreciable extent. Since then, a few papers on this subject have been published. Gokhale, Peters and Stevens, 1958, have used the technique for dyeing acetate fibres. The Delaware Valley Section of AATCC, 1958, has investigated the influence of different solvents in increasing the dyeing rate of hydrophilic fibres such as wool and cotton. Delmenico, 1957, has applied the method for vigoureux printing of wool, finding benzyl alcohol to be the best solvent for technical purposes.

At the beginning of this investigation in 1955, this method was an alternative to surface-modification of wool by alkali or chlorine treatments in order to increase the rate of dyeing. At that time it was known (from unpublished observations by L. Peters) only that some organic compounds, with limited solubility in water, e.g. butanol, might increase the dyeing rate of some dyes on wool. Therefore, it was considered essential to obtain some general understanding of the conditions under which the method could be used. For this purpose a preliminary investigation was made. Some of the results from this research have already been published very briefly as a letter to the Editor (Kärrholm, Lindberg, 1956), but as they are of interest for the following industrial and laboratory

experiments, they are included in this paper (chapter 1).

After the preliminary work had shown it was possible to obtain a considerable increase in the dyeing rate of technically important dyes, and at the same time a uniform distribution of the dye between different fibres, the next step was to try the method in industry. Experiments were made on loose wool dyeing, as this kind of dyeing was very easily carried out. These industrial experiments are briefly described in chapter 4, and the results show that a superior dyeing, compared with conventional methods, might be obtained. It was therefore considered justified to make a further investigation of solvent-assisted dyeings in order to obtain some understanding of the dyeing mechanism. It has been shown, both at this laboratory and by others (see e.g. the paper by Gokhale et al, 1958), that there is an adsorption of solvent by wool, and it might be assumed that this adsorption has an influence on the rate of dyeing. A special apparatus was designed to measure this adsorption quantitatively and also the increase in dyeing rate of a dye, non-aggregated in dilute solutions. These experiments, and further investigations of factors influencing the dyeing rate, are described in chapter 2.

Possible dyeing mechanisms of solvent-assisted dyeings are discussed in chapter 3, taking into consideration the results obtained from the different parts of this investigation.

Terminology

The term "solvent-assisted" dyeing, used in this investigation, means that the dyeing rate of a dye in aqueous solution is increased by the addition of an organic compound to the dyebath. The compounds found to have this effect are usually organic solvents which are sparingly soluble in water. The solvents investigated are some alcohols and one amine. The general term alcohol, when not otherwise stated, means alcohols of limited solubility in water (butanol or higher homologues). The expressions butanol, amyl alcohol, hexanol, octyl alcohol etc. without further notation refer to primary normal alcohols.

All dyes used are commercial samples without further purification. The alcohols used were obtained from Theodor Schuchardt, München, or Fluka AG, Buchs, and were of the highest grade obtainable (usually "reinst").

CHAPTER I

PRELIMINARY INVESTIGATIONS

As mentioned in the Introduction these experiments were performed to obtain some general understanding of solvent-assisted dyeing of wool. The change in dyeing rate obtained with different dyestuffs and at different concentrations of alcohol in the solution was investigated. The influence of surface treatments and the dye distribution between different fibres was also studied.

1.1 Degree of sulphonation of dye

Experiments have been performed with a series of acid dyes differing only in the degree of sulphonation. The dyes used were Naphthalene Red J (CI Acid Red 88), Naphthalene Red EA (CI Acid Red 13) and Naphthalene Scarlet 4 R (CI Acid Red 18) with the following constitution:

As these dyes have about the same equilibrium exhaustion, which is only affected to a small degree by the alcohols used (at concentrations below or not much greater than the saturation concentration of the alcohols in water), the time of half-dyeing can be used as a measure of the dyeing rate (Vickerstaff, 1954, p.147). The rate of sorption of dye by the wool fibres was determined by measuring the concentration of dye in the dyebath

after different times. The dyeing experiments were performed in a 400 ml glass beaker using a high liquor ratio (250:1), pH 2.6 and a temperature of 60°C. One gram of wool top, cut into pieces of 2 mm in length, was immersed into a small piece of glass tubing in a blank solution and brought to the test temperature in a water bath controlled by a thermostate. The fibres were then very quickly pushed through the tubing in to the dye liquor, circulated with a glass stirrer at about 1000 r.p.m. Small samples of the dye liquor were withdrawn at definite times and the concentration of dye determined, using a Beckman DU Spectrophotometer. By the addition of 3 % (v/v) amyl alcohol to the dye liquor, the dyeing rate was increased ten times (i.e. the time of half-dyeing was decreased to the same extent) for the monosulphonated dye, Naphthalene Red J. For the disulphonated dye, Naphthalene Red EA, the increase in dyeing rate was about four times, while the trisulphonated dye, Naphthalene Scarlet 4 R, was unaffected by this alcohol.

When determining the partition ratio for these dyes between water and amyl alcohol, the monosulphonated dye was completely absorbed by the alcohol phase, the trisulphonated remained in the water phase and the disulphonated was soluble in both water and alcohol (in a partition ratio of 4:1). Apparently the degree of sulphonation determines the solubility of the dye in the alcohol, and this solubility, at least to some extent, seems to be a necessary condition to obtain an increased dyeing rate.

The partition ratio for a dye between water and solvent will be discussed later in connection with dyeing experiments using bromphenol blue at different pH values.

A new group of wool dyes, known as 1:2 chrom-complex dyes, has been developed to obtain dyes with reduced hydrophilic character, but still soluble in water (Schetty, 1955). These dyes do not contain any sulphonic acid groups and should be dyed from neutral solutions. The effect of amyl alcohol on the dyeing rate of these dyes is much greater than with the monosulphonated acid dyes. In Fig.1 are shown

some exhaustion-time curves for a dye of this type (Cibalanblau BL) with various concentrations of octyl alcohol or amyl alcohol in the dye liquor. The experiments were performed as described above, but at pH 6.4, using a phosphate buffer. The dyeing rate was increased with a factor of one hundred by the addition of 3 % (v/v) amyl alcohol. In figure 1 an exhaustion-time curve referring to 5 % (v/v) of butanol in the dyebath is included for comparison with amyl alcohol. These alcohols are used in the industrial experiments, described in chapter 4.

Fig. 1 - Dyeing rate of Cibalanblau BL on wool at different concentrations of alcohols in the bath.

1.2 "Extraction effect" of solvent

A 60's Australian wool top was used for these experiments. It was kerosene-extracted in a mill, and the only other treatment was with ethyl ether at room temperature. However, it is known that the dyeing rate of wool is increased by extraction with solvents (Lindberg, 1953). The presence of a solvent in the dyebath might then increase the dyeing rate by this "extraction effect". To determine the extent to which this occurs, the ether-extracted wool top was treated with water containing 3 % by volume of amyl alcohol for one hour at 60°C. The wool was then rinsed in water, dried and cut

Fig. 2 - Dyeing rate of Naphthalene Red J on wool at different conditions.

into pieces of 2 mm length. This wool will be referred to as amyl alcohol-treated wool (AAT-wool). The time of half-dyeing was determined for AAT-wool with and without amyl alcohol in the dye liquor, using the dyes and dyeing technique described above. For all the sulphonated dyes, the dyeing rate was increased on AAT-wool compared with the ether-extracted wool.

An addition of amyl alcohol to the dye liquor further increased the dyeing rate of the monosulphonated dye on AAT-wool to the same value as that obtained on ether-extracted wool (see fig. 2). This was also true for the disulphonated dye, although the "extraction

Fig. 3 - Dyeing rate of Naphthalene Scarlet 4 R on wool at different conditions.

effect" is relatively larger for this type of dye. For the tri-sulphonated dye, however, the reverse effect was obtained; the addition of amyl alcohol to AAT-wool decreased the rate of dyeing (see Fig. 3). The net effect on the dyeing rate, when a solvent in which the dye is insoluble, is added to the dyebath, is therefore dependent on whether an increase due to the "extraction effect" is obtained that is larger than a retardation due to the presence of the solvent.

In fig. 4 is seen that the same exhaustion-time curves were obtained on the AAT-wool and ether extracted wool both with and without the

Fig. 4 - Dyeing rate of Cibalanblau BL on wool at different conditions.

addition of amyl alcohol to the dye liquor for the 1:2 chrom-complex dye (Cibalanblau BL). With this type of dye, however, the largest increase in the dyeing rate was obtained by the addition of an alcohol to the dye liquor. It must be concluded, therefore, that the "extraction" effect of an added alcohol may increase the dyeing rate in some cases, but this effect is unimportant in the mechanism of solvent-assisted dyeings.

1.3 Concentration of alcohol

In fig. 1 is shown the large effect of the concentration of alcohol in the dye liquor, the increase in dyeing rate being much greater near the saturation concentration of the alcohol. This is later shown to be dependent on the adsorption of the alcohol on wool and is considered in chapter 2.

Referring to dye - alcohol systems where an appreciable increase in dyeing rate is obtained, a concentration of alcohol above the saturation concentration will cause smaller increase in the dyeing rate, as has also been shown by Gokhale et al 1958 in the dyeing of triacetate fibres. The equilibrium concentration will also be influenced, more dye will remain in the dye bath, when the concentration of alcohol is increased above its saturation value. Thus dyeings carried out from a bath, containing the dye, dissolved in an alcohol, saturated with water, will show a very small equilibrium exhaustion of dye on the fibre. Dyeing ether-extracted wool with Cibalanblau BL (0.3 g/l) under the experimental conditions described gives a dye uptake of 20 mg per g of wool from aqueous solution after 24 hours, but only 1.8 mg per g of wool from butanol saturated with water. Fibre swelling has been measured and found to be the same in the two systems.

1.4 Temperature of dyebath

In fig. 2 are shown two curves which refer to dyeing of Naphthalene Red J at 40°C. It is obvious that the increase in dyeing rate caused by amyl alcohol is greater at 40°C than at 60°C. The investiga-

tion of solvent-assisted dyeings of hydrophilic fibres by the Delaware Valley Section of AATCC, 1958, has shown this to be generally true, the increase in dyeing rate brought about by solvent being greater at lower than at higher temperatures.

1.5 Surface treatment of wool

At an early stage of this investigation, it was considered probable that the surface properties of the wool fibres might play an important role in solvent-assisted dyeings. In order to test this, wool top was treated with sodium hydroxide in butanol-kerosene to change the hydrophobic wool surface into a hydrophilic one and to make the epicuticle easier to penetrate (Wikström et al, 1955). The surface-treated wool was then dyed with Cibalanblau BL, and the influence of amyl alcohol on the dyeing rate was compared with that obtained on untreated wool. The results are shown in fig. 4, and it is seen that the alcohols gives a lower increase in the dyeing rate of surface-treated wool than with untreated wool. No further discussion will be made at this stage as the influence of surface treatments on solvent-assisted dyeings will be discussed later in a separate chapter.

1.6 Dye distribution between different fibres

At the beginning of the dyeing period the dye is usually unevenly distributed between different fibres and also between different parts of the same fibre. Lindberg, 1953, has reported that the unevenness is greater for a disulphonated dye than for a monosulphonated one of the same constitution. This has also been found to be true for the three acid dyes mentioned above, the unevenness being greatest for the trisulphonated and least for the monosulphonated dye. It is, however, of both practical and theoretical interest to know, how the dye distribution will be influenced by the addition of a solvent to the dye liquor. For this purpose fibre samples were taken from the dyebath at different times and examined under the microscope. One hundred fibres were classified into four groups; undyed, spot dyed, lightly dyed and heavily dyed. The results shown in table 1 are for

Table 1

Dye distribution after dyeing with Naphthalene Red J.
pH 2.6; temp. 60°C; conc. 0.1 g/l; liquor ratio 250:1

Time of dyeing min.	Addition to dyebath	Dye on fibre % of available dye	% of total fibres belonging to			
			Undyed fibres	Spot-dyed fibres	Lightly dyed fibres	Heavily dyed fibres
2	none	28	48	19	27	6
10		75	9	20	48	23
40		99	0	10	40	50
2	3 % amyl alcohol	95	0	0	73	27
20		99	0	0	22	78

the monosulphonated dye, Naphthalene Red J, on ether-extracted wool with and without the addition of amyl alcohol to the dyebath. The figures given are the mean values of four samples tested by two different persons. When amyl alcohol was present in the dye liquor, about 70 % of the fibres were classed as "lightly dyed" after only 2 minutes dyeing, and after 20 minutes about 80 % were "heavily dyed". Without the addition of an alcohol, 50 % of the fibres were "undyed" after 2 minutes and the remainder were distributed among the other three groups. After 40 minutes there were still some "spot-dyed" fibres, but the majority were "lightly" and "heavily" dyed.

For the disulphonated dye an equal change in the distribution of dye between the fibres was obtained by the addition of amyl alcohol, although the change was not as great as for the monosulphonated dye. Dyeing with the trisulphonated dye resulted in the most uneven dyeing; the group of "spot-dyed" fibres was particularly large. As would be expected, there was no appreciable change in the dye distribution after the addition of amyl alcohol, because, as mentioned earlier, no change in the dyeing rate was ob-

served with this dye.

In table 1 the dye distribution after a fixed time of dyeing is compared for dyeings with and without the addition of amyl alcohol. It would also be of interest to make a similar comparison for dyeings in which the same amount of dye was present on the wool in each case. However, the dyeing rate of Naphthalene Red J is too large at pH 2.6 so a test series was made at pH 4.3. The results are given in table 2. For the same amount of dye on the fibre, the distribution was also more uniform when the dyeing was made in the presence of amyl alcohol, although the effect was less marked than when the comparison was made after equal dyeing times.

Table 2

Dye distribution after dyeing with Naphthalene Red J.
pH 4.3; temp. 60°C; conc. 0.1 g/l; liquor ratio 250:1

Time of dyeing min.	Addition to dyebath	Dye on fibre % of available dye	% of total fibres belonging to			
			Undyed fibres	Spot-dyed fibres	Lightly dyed fibres	Heavily dyed fibres
10	none	63	18	12	68	2
18		83	4	8	76	12
40		96	5	9	18	68
2	3 %	62	1	10	73	16
4	amyl	83	0	1	30	69
10	alcohol	96	0	3	17	80

The results indicate that if the dyeing rate of wool is increased by a solvent, the distribution of dye will be more uniform between different fibres and between different parts of the same fibre. This kind of unevenness is considered to be due to a variation in

surface properties of the wool; the outermost layer (the epicuticle) being intact or not modified on some fibres or some parts of the same fibre, and thus offering resistance to the dye molecules. The addition to the dyebath of an alcohol, which is adsorbed by the wool (as shown later) and in which the dye is soluble, would then give the entire fibre, and different fibres, the same permeability to the dye.

CHAPTER 2

INVESTIGATION OF SOME FACTORS OF IMPORTANCE TOTHE DYEING MECHANISM

The preliminary investigation described in the previous chapter showed that a great increase in the dyeing rate could be obtained by addition of butanol or one of its higher homologues to the dye-bath. Furthermore, the dye distribution between different fibres and different parts of the same fibre became more uniform. Further experiments are, however, necessary to obtain some understanding of the dyeing mechanism.

Soon after the discovery of solvent-assisted dyeing, it was found that the alcohols are adsorbed by the wool fibres (Stevens and Peters, 1956). It was of interest therefore to measure this adsorption quantitatively and determine if there is any simple relation between the dyeing rate and the amount of adsorption.

This adsorption, however, cannot be the only factor of importance, as the dyeing rate of many dyes is unaffected by solvents. The partition ratio of the dye between solvent and water seems to be another important factor. This factor has been studied for an indicator dye at different pH-values. A change of the surface properties of wool will also influence the dyeing rate in the presence of solvents, as shown by the preliminary investigation. This might be of importance for the dyeing mechanism and further experiments have been performed on this subject.

Valuable information concerning the dyeing mechanism might also be obtained from changes in physical properties brought about by the solvents used. The stress-relaxation properties and the swelling of single wool fibres have been investigated for this purpose.

2.1 Raw material

Ether-alcohol-water extracted wool

Australian wool tops from 60's wool was used as the raw material. It is important that, as far as possible, the wool fibres are uniform as regards dyeing rate, and that the surface layer of the wool fibres is intact. Preliminary experiments showed, that the dyeing rate may be influenced to an appreciable extent by extraction with organic solvents or water solutions and even by different methods of drying. For these reasons, a wool top was chosen which had been scoured in kerosene in a Swedish textile mill and had never been in contact with water since it left the sheep. The top was further cleaned by extraction with ethyl ether, ethanol and water. The top was cut into pieces of about 12 g each, with a thread knotted round each end to keep the fibres in position during the treatments. The thread was also used to mark the samples. Each piece was immersed in 500 ml of the solvent in separate beakers for 10 min, and was then pressed between filter papers. Three baths of each solvent were used, and after the final water treatment, the wool was dried at 50°C overnight and then conditioned at 65 % relative humidity and 20°C. All wool used was taken from the same top, and all extractions made by the same person within the shortest possible time. In all, about 200 pieces of wool top were extracted. About 6 pieces could be treated at the same time, and these were marked in the same way. Furthermore, the marking was made in such a way, that the position of the piece in the original top could be identified, as well as the number of the extraction series.

When chemical treatments were to be made, the pieces of top could then be selected so, that different treatments could be performed on pieces with the same marking. Furthermore, all investigations, where dyeing rates are compared, were made on small samples of cut wool fibres taken from the same large, general sample. An investigation of the alcohol adsorption of extracted wool, however, showed that the wool is rather uniform in this respect.

Wool top, extracted as above, is referred to as EAW-wool, but when being compared with chemically treated wool, is sometimes also referred to as untreated wool.

Chlorine treatments

The surface properties of wool fibres were modified to different degrees by dry chlorination. A degree of modification was desired which only affected the cuticular layers of the wool, leaving the cortex unchanged. This can be obtained approximately by treatment with chlorine in a solvent, e.g. carbon tetrachloride (Moncrieff, 1953). Lindberg has followed the effect of chlorination on the frictional properties of wool fibres (Lindberg, Gralén, 1949). Whewell and Selim, 1944, have also shown, that the degree of penetration of the chlorine is dependent on the amount of water present in the system. Using Lindberg's data, reaction conditions were chosen to obtain 3 different degrees of modification.

A) 8 x 12 g of EAW-wool was dried at 105°C for 1 hr and treated with 0.3 m Cl_2 in dried carbon tetrachloride for 10 min at a liquor ratio of 25:1. The samples were rinsed once with carbon tetrachloride, twice with ethanol, twice with distilled water, once with buffer solution of pH 7.7 and finally four times with distilled water using a fresh bath for each rinse. A treatment such as this increases the coefficient of friction without affecting the resistance to mechanical abrasion of the scales of the wool fibres.

B) The same treatment as A), but the EAW-wool was conditioned at 65 % relative humidity and thus contained about 13 % by weight of water. The carbon tetrachloride was not dried. This treatment increases the coefficient of friction, but also decreases the resistance to mechanical abrasion of the scales of the wool fibres.

C) The same treatment as B, but extended to 60 min. The whole cuticular layer was then removed by treatment with papain after the chlorination (Patent specification BP 546.915, 1941). For this purpose a solution of a 0.025 % commercial papain in an acetate buffer, containing 0.25 % sodium bisulphite at pH 5.0 was used. The wool tops were treated in this bath for 2 hours at 65°C. The samples

were rinsed in the usual way after chlorination, but the papain solution replaced the buffer solution of pH 7.7. After the papain treatment, the samples were rinsed in distilled water, treated with buffer of pH 7.7, rinsed again and dried overnight at 50°C.

Microscopic examination of the treated wool revealed only small changes in the appearance after treatment A) and B) but an almost completely descaled wool after treatment C). The weight loss was less than 1 % after treatment A and B but 20 % after treatment C.

The wettability of the wool samples was tested according to the method by Schuyten et al, 1949, and was found to be 72 dynes/cm, i.e. all three methods of chlorination resulted in a wool, the surface of which was wet by water.

The wool, treated as above, will be referred to as wool A, wool B and wool C.

2.2 Adsorption of alcohols and dyestuff on wool from aqueous solutions.

Preliminary experiments showed that alcohols were selectively adsorbed from aqueous solutions by wool. In order to measure the amount of adsorption, an apparatus was designed at the Institute. This apparatus could be used for dyeing experiments as well, thus making it possible to determine the amount of adsorption of alcohol and of dyestuff from the same experiment.

Apparatus

The apparatus consists of a glass cylinder about 22 mm in diameter, which is surrounded by a glass mantle for circulating water (See fig. 5 a and b).

The cylinder is grooved in both ends and can be tightly closed with teflon stoppers. A stainless steel shaft passes through the stopp-

- 1) Teflon gland
- 2) Plastic ring
- 3) Bored hole in the teflon stopper
- 4) Stainless steel shaft
- 5) Upper disc.
- 6) Fibre sample
- 7) Lower disc, fixed to the shaft
- 8) Glass mantle
- 9) Rubber packing

Fig. 5 a

Apparatus for measurement of adsorption and dyeing rate.

- 1) Gland consisting of a teflon screw (1) and teflon packing (3)
- 2) Plastic ring
- 4) Teflon stopper
- 5) Rubber packing
- 6) Upper disc.
- 7) Lower disc.

Fig. 5 b

Details of teflon stopper and discs.

ers. The fibres to be tested are held between two perforated discs of stainless steel. The lower disc is firmly connected to the shaft, but the upper disc is free and fixed to the shaft by means of a spring, which is released when the disc passes a groove in the rod. The shaft is connected to an eccentric, driven by a gear speed reducer motor. Thus the shaft is moving up and down through the stoppers. Teflon was chosen for the stoppers to obtain low friction against the shaft. After a short time, however, the motion of the shaft enlarged the holes in the stoppers and leakage occurred. A special gland was designed, consisting of small packing pieces of teflon, which were expanded against the shaft by means of a screw (See fig. 5 b). When these pieces were worn out, they were replaced by new ones. By changing the amount of wool and the distance between the discs, the bath ratio could be changed at a constant degree of packing. The distance between the discs was varied most simply by using different shafts, where the groove for the upper plate was placed at a different distance from the fixed lower plate.

Test procedure

The shaft carrying the lower disc, was put through the lower teflon stopper, and 15 ml of the test solution placed in the inner cylinder. Water of desired temperature was circulated in the outer cylinder, and the temperature of the water measured on both sides of the apparatus. The rate of flow was adjusted to give the same temperature within 0.3°C on the incoming and outgoing water. Under these conditions the temperature of the outer cylinder was also obtained in the inner cylinder. For the adsorption experiments, a weighed amount of wool, cut in 2 mm pieces, was placed in the solution, and the upper disc put in position. The distance between the discs was chosen to correspond to a degree of packing of the wool of 0.2 (Degree of packing = volume of wet fibres/total volume). After the wool had been placed between the discs, the upper teflon stopper was screwed into position, the air escaping through a narrow hole, bored in the stopper. If the experiment was not

carried out at room temperature, the final adjustment of the stopper was made when the solution had obtained test temperature. For dyeing or adsorption experiments, where the time is also measured, the test solution was first brought to the desired temperature, and the wool then entered into the solution, the stopper closed, and the shaft connected to the motor. The time elapsing from when the wool was brought into contact with the solution until the stirring could be commenced was about 22 seconds. By this procedure, experiments could be done with good reproducibility for times exceeding 2 minutes.

The test solution was forced through the plug of wool fibres as the plug was moving up and down in the closed space between the teflon stoppers. The shaft moved at a rate of 21 cycles per minute, which corresponds to a flow of liquid through the plug of about 200 ml per min. and cm^2 at a bath ratio of 30:1. After an experiment was finished, the upper stopper and the shaft with the fiber plug were removed, and the solution collected in a test tube. This procedure could be done within a few seconds.

To obtain a rate curve experimentally it is thus necessary to make a separate experiment for each time interval.

Methods for determination of alcohol concentration

Refractive index method

The amount of adsorption of alcohol or dyestuff was calculated from the difference in concentration of the test solution before and after the adsorption.

It is rather difficult to determine quantitatively the concentration of an aliphatic alcohol in aqueous solution by chemical methods. A colorimetric method using ammonium cerium nitrate was tried (Reid, Truelove, 1952), but found less accurate than a physical method, using the refractive index of a solution as a measure of concentration. This determination is simple, but a necessary condition

is that the concentration of all other substances is constant. For our purpose this limits the applicability to solutions consisting of only one solute, as other solutes may well be adsorbed by the wool at the same time, also causing a change in refractive index. For the experiments a Zeiss dipping refractometer was used. The temperature was carefully controlled by circulating the bath surrounding the samples through a thermostat. All measurements were performed at 25.0°C. The refractive index of the stock solution was measured at the same time as that of the test solution, and directly after each other, to minimize errors depending on time. Generally two adsorption experiments were carried out at each concentration of the alcohol. Calibration curves were established by measurements with known solutions. The measurement of refractive index was repeated three times on each solution.

Distilled water will dissolve some substance out of the wool. This continues for very long times, resulting in an increasing refractive index of the solution. It was, however, easy to correct for this, by making separate experiments, using distilled water, at the same time as the adsorption experiment. These corrections are highly reproducible. Alcohol solutions may remove solids from wool to a different degree than distilled water, thereby making the correction inaccurate. For benzyl alcohol this effect can be determined experimentally, and is found to be negligible, as seen from table 5, by comparison of column 2 and 3.

To test the whole procedure, especially losses due to evaporation, adsorption tests should be made on fibres with zero adsorption. Polyacrylics were suitable, as both polyamides and polyesters showed a selective adsorption of alcohols.

It was possible to carry out the adsorption experiments using a 4 % solution of butanol and polyacrylic fibres, without any change in refractive index of the solution at 60°C or 70°C. At 70°C it was necessary to introduce the fibres at room temperature, and

then increase the temperature, but at 60°C the fibres can be introduced at the test temperature. Evaporation losses from the closed apparatus were also investigated, by stirring the alcohol solutions without fibres. For times up to 1 hour at 60°C no correction has to be made, but for longer times a correction is necessary.

The 95 % confidence limits for the mean value of the refractive indices for two separate experiments have been calculated from a great number of experiments and found to be $\pm 1.3 \times 10^{-5}$. This is somewhat less than the correction introduced for the extraction of soluble compounds out of the wool fibres.

Spectrophotometric method

Some aromatic alcohols show a maximum for light absorption in the ultraviolet region, and this can be used for the determination of their concentration. Benzyl alcohol, for example, shows an absorption maximum at 257 mμ. This method has the advantage of being applicable also when other solutes are present in the solution. If the determination is made in the presence of other aromatic compounds, showing a light absorption at the wavelength used, a correction must be made for this.

The spectrophotometric method has been applied to solutions of benzyl alcohol in the presence of a dyestuff. Instead of using a blank solution of zero concentration of benzyl alcohol at the spectrophotometric determination of the concentration, the test solution (obtained after the adsorption experiment) was used as a blank and measured against the stock solution (the alcohol solution before the adsorption). In this way, the desired concentration difference was obtained, and the reading errors minimized. It was necessary to dilute the benzyl alcohol solution before measurement to get a measurable optical density. Three dilutions were made of the test solution and three of the stock solution. These solutions were then measured against each other in random order, using a Beckman DU Spectrophotometer. The mean value of these three determinations was used for calculation of

the adsorption. Two separate experiments were performed at each concentration of benzyl alcohol. The confidence limits for the mean value of the adsorption of benzyl alcohol according to above procedure was found to be $\pm 1,2$ mg/g wool and is rather independent of the magnitude of the adsorption.

Results

Adsorption of aliphatic alcohols from solutions in distilled water

The amount of adsorption was measured for various aliphatic alcohols from solutions in distilled water, using the refractive index as a measurement of concentration. In fig. 6 and table 3 some results are shown at a liquor ratio of 30:1 and a temperature of 60°C and a time of 30 min. At this temperature only a slight increase in adsorption is obtained at times longer than 30 min, but the values may not be treated as true thermodynamic equilibrium values. From these results it is seen that adsorption of alcohols will increase with the number of carbon atoms in the chain at the same concentration in the bath. For the different isomers of the same alcohols the adsorption increases with decreasing solubility.

Adsorption of alcohol and dyestuff from buffer solutions

Benzyl alcohol

The main difficulty in investigating the influence of adsorption of an alcohol on the dyeing rate is to find a suitable dyestuff. Dyestuffs are affected to different degrees by alcohols, i.e. depending on the degree of sulphonation of the dyestuff. Many sulphonic acid groups in the molecule result in high solubility in water, but usually a low solubility in alcohols, whereas other solubilizing groups (as in the 1:2 chrome complex dyes) may give the dyestuff the reverse solubility properties. The dyeing rate of the last group is most influenced by alcohols. However, these dyes are highly aggregated in aqueous solutions up to temperatures of about 90°C and therefore less suitable for comparisons of dye-

Table 3

Adsorption of alcohols on wool

temp. 60°C; time 30 min.; liquor ratio 30:1

Alcohol	Conc. in solution in millimol/l		Adsorption	
	before ad- sorption	after ad- sorption	mg/g wool	millimol/g wool
butyl alcohol (n)	13.5	13.2	5.1	0.07
	27.6	25.8	26.3	0.36
$\text{CH}_3(\text{CH}_2)_2\text{CH}_2\text{OH}$	54.4	50.8	54.5	0.74
	81.9	75.2	99.6	1.34
butyl alcohol (iso)	13.3	13.0	6.1	0.08
	40.3	38.9	31.2	0.42
$\text{CH}_3 > \text{CHCH}_2\text{OH}$	67.1	64.1	65.7	0.89
CH_3	93.2	88.0	116	1.57
butyl alcohol (sec)	13.2	12.8	7.5	0.10
	40.4	39.2	27.2	0.37
$\text{CH}_3\text{CH}(\text{OH})\text{C}_2\text{H}_5$	94.2	91.9	50.8	0.69
	135.2	132.8	52.6	0.71
amyl alcohol (n)	5.8	5.6	4.7	0.05
	11.6	11.3	8.5	0.10
$\text{CH}_3(\text{CH}_2)_3\text{CH}_2\text{OH}$	17.3	16.1	31.7	0.36
	22.1	19.9	58.7	0.67
amyl alcohol (prim.iso)	5.7	5.5	5.9	0.07
	11.5	11.1	11.1	0.13
$\text{CH}_3 > \text{CHCH}_2\text{CH}_2\text{OH}$	17.1	16.5	16.2	0.18
CH_3	23.0	21.7	33.1	0.38
amyl alcohol (sec.n)	5.7	5.6	2.2	0.02
	22.8	22.1	19.5	0.22
$\text{C}_2\text{H}_5\text{CH}_2\text{CH}(\text{OH})\text{CH}_3$	39.8	35.0	125	1.42
	46.7	36.3	276	3.13
hexyl alcohol	2.9	2.7	5.6	0.05
4-methyl pentanol-2	5.9	5.5	13.0	0.13
$\text{CH}_3 > \text{CHCH}_2\text{CH}(\text{OH})\text{CH}_3$	9.9	9.1	22.8	0.22
CH_3	14.5	11.8	81.8	0.80

The 95 % confidence limits for the adsorption values are obtained by adding to the values in the table ± 3.3 mg/g wool or ± 0.04 millimol/g wool.

1) butyl alcohol (sec), 2) butyl alcohol (iso), 3) butyl alcohol (n),
4) amyl alcohol (sec-n), 5) amyl alcohol (iso), 6) amyl alcohol (n),
7) hexyl alcohol (4-methyl pentanol-2).
(The formulas are given in table 3).

Fig. 6 - Adsorption of aliphatic alcohols on wool fibres as a function of their final concentration in solution.

ing rate and adsorption at temperature below 90°C . It is, however, possible to find a dyestuff, which has affinity for wool, is monomolecular in solution and the dyeing rate of which is influenced by alcohols. This dyestuff, tetrabromophenol sulphonphthalein, (an indicator dye known as bromphenol blue, see below), is not normally used for wool dyeing. The light absorption at different wave lengths of this dye in aqueous solutions varies with the pH of the solution in a simple way (Luck, 1958). At pH 1.2 the dye is almost completely converted to its acid modification, which is yellow, whereas at pH about 7.8 it exists in its basic modification, which is blue.

As the concentration of benzyl alcohol can be determined spectrophotometrically, the adsorption of this alcohol on wool has been measured from solutions containing bromphenol blue at pH 1.2. The adsorption of dye by the wool was measured in the same experiment, using the apparatus described before. As the dyeing rate is very high at pH 1.2, a temperature as low as 2.5°C was necessary. This temperature could be obtained by circulating ice-water through the outer mantle of the apparatus. Dye solutions of constant dye concentration, but containing different amounts of benzyl alcohol, were prepared by dissolving a weighed amount of benzyl alcohol in a buffer solution of pH 1.2, adding a desired amount of a stock solution of bromphenol blue in the same buffer solution, and finally adjusting the volume with the buffer solution. Four different concentrations of benzyl alcohol were used at dyeing times of 2.5 min, 5 min, 10 min, 30 min, 90 min, and 180 min. The experiments were repeated twice. The dye concentration was determined spectrophotometrically at a wavelength of $437\text{ m}\mu$. The same solution was then diluted, and the concentration of benzyl alcohol determined at $257\text{ m}\mu$ as described above. The results are given in table 4, and some values illustrated in fig. 7 a. Fig. 7 b gives the amount of adsorption of bromphenol blue as

Table 4

Adsorption of benzyl alcohol and bromphenol blue on wool

pH = 1.2; initial dye conc. = 0.02 g/l;

temp. = 2.5°C; liquor ratio 30:1

Conc. of benzyl alcohol g/100 ml	Adsorption of dye ¹⁾ optical density at 437 mμ	Adsorption of alcohol mg/g wool	Time of adsorption min.	Adsorption of alcohol millimol/g wool
0	0.235	-	2.5	-
2.00	0.262	6.5		0.060
3.00	0.312	29.0		0.268
4.00	0.365	47.9		0.443
0	0.320	-	5	-
1.00	0.329	4.4		0.041
2.00	0.336	10.7		0.099
3.00	0.386	42.4		0.392
4.00	0.412	60.1		0.555
0	0.395	-	10	-
2.00	0.405	13.7		0.126
4.00	0.433	70.2		0.649
0	0.438	-	30	-
2.00	0.446	16.8		0.155
4.00	0.461	81.1		0.750
0	0.465	-	90	-
2.00	0.469	21.8		0.202
4.00	0.465	90.7		0.839
0	0.465	-	180	-
4.00	0.465	102.5		0.948

1) The numbers represent the difference in optical density of dye solution before and after dyeing. Optical density of initial conc. = 0.500; optical density of equilibrium conc. = 0.035.

The 95 % confidence limits for the adsorption of benzyl alcohol is obtained by adding to the values in the table ± 1.2 mg/g or ± 0.01 millimol/g.

Fig. 7 a - Amount of bromphenol blue on wool after a fixed time at pH 1.2 as a function of the adsorbed amount of different alcohols (see Table 4).

Fig. 7 b - Amount of bromphenol blue on wool after 5 min. as a function of the concentration of different alcohols in solution.

a function of concentration of benzyl alcohol in the solution. These adsorption values are much lower than the equilibrium values, due to the rate of adsorption being low at the low testing temperature. The amount of dye taken up by the wool after a fixed time, used as ordinate in fig. 7 a and b can be used as a measure of the dyeing rate, as the equilibrium adsorption of dye is not influenced by the benzyl alcohol. The dyeing rate for this alcohol is therefore a rectilinear function of the amount of adsorption of the alcohol. The slope of the curves varies with the time of dyeing; the nearer to equilibrium dye adsorption, of course, the less will the alcohol influence the amount of dye on the fibre and the smaller will be the slope of the curve.

Aliphatic alcohols

It is of interest to find out if simple relationships between dyeing rate and adsorption also exists for other alcohols. As mentioned previously, the concentration of these alcohols must be determined by refractive index measurements, which means, that the adsorption of alcohol and dyestuff must be determined from separate experiments. The alcohol adsorption was measured from a solution in distilled water, whereas the dye adsorption was measured from buffer of pH 1.2. As benzyl alcohol could be determined both by refractive index and spectrophotometric measurements, a comparison of these two methods could be made, and also the difference in adsorption from distilled water and buffer solutions with and without dyestuff in the solution. The results are shown in table 5. All differences between the adsorption values lie within the 95 % confidence limits (with one exception). Thus for benzyl alcohol, the adsorption by wool is the same if the alcohol is dissolved in distilled water or in a buffer solution of pH 1.2, or this buffer solution contains bromphenol blue at a concentration of 0.02 g/l. Furthermore, the two different methods of determining the concentration give values in good agreement.

Assuming these results to be valid also for other alcohols, dyeing experiments have been performed with solutions of bromphenol

Table 5

Adsorption of benzyl alcohol on wool from different solutions and determined by different methods

temp. 25°C; time 5 min.; liquor ratio 30:1

Conc. of benzyl alcohol g/100 ml	<u>Adsorption in mg/g wool measured by</u>			
	refractive index	light absorption at wavelength 257 mμ		
	water solution pH~6	water solution pH~6	buffer solution pH 1.2	dye in buffer pH 1.2
1.0	3.8	4.6	4.4	4.4
2.0	11.5	10.5	11.3	10.5
3.0	37.9	43.7	43.7	42.8
4.0	62.3	61.3	62.2	61.5

The 95 % confidence limits for the adsorption values are obtained by adding to the values in the table ± 2.0 mg/g wool (refractive index method) or ± 1.2 mg/g wool (spectrophotometric method).

blue containing different amounts of n-butanol or pentanol-2. The results are given in fig. 7 a and b and refer to a time of dyeing of 5 minutes. The dyeing rate at the same adsorption are very similar for the two alcohols and agree with the values obtained for benzyl alcohol at low adsorption values. At higher adsorption values the dyeing rate is increased more by benzyl alcohol than by these alcohols.

2.3 Dyeing at different pH-values

Dyeing experiments have shown that not only the acid form of bromphenol blue but also the basic form, has an affinity for wool, although the dyeing rate is much less at higher pH values. For this reason dyeing experiments were carried out at 60°C and pH 7.7 with the same apparatus as described before and at the same concentration of dyestuff in the solution. The results are given in table 6. The dyeing rate is slightly increased by butanol but unaffected

by the presence of benzyl alcohol. This is not due to changes in the adsorption of benzyl alcohol on wool, as is shown in the table. In fact, nearly the same amount of benzyl alcohol is adsorbed as in the dyeing experiments at pH 1.2. It is thus found that two modifications of the same dye react in different ways to the same alcohol. The dyeing rate of one form is increased, while the dyeing rate of the other is unaffected. The reason for this might be of utmost interest to explain the mechanism of solvent-assisted dyeing of wool. For this reason, further investigations have been carried out with bromphenol blue at different pH values.

Table 6

Dyeing rate of the basic form of bromphenol blue in the presence of butanol, benzyl alcohol or hexylamine

initial dye conc. = 0.02 g/l; temp. = 60°C; liquor ratio 30:1

Dye solution				Dyeing time min.	Amount of dye on fibre ¹⁾ optical density at 590 mμ	Adsorption of solvent mg/g wool
	Solvent	Solvent conc. g/100ml	pH			
phosphate buffer	-	-	7.7	5	0.19	
	-	-	"	30	0.70	
"	benzyl alcohol	3.0	7.7	5	0.20	42
	"	"	"	30	0.67	51
"	butanol	6.0	7.7	5	0.29	
	"	"	"	30	0.87	
borate buffer	-	-	7.8	5	0.19	
	-	-	10.2	5	0.16	
phosphate buffer	hexylamine	0.74	10.2	5	1.21	48
	"	"	10.2	30	1.82	

1) The numbers represent the difference in optical density of the dye solution before and after dyeing. Optical density corresponding to initial concentration = 2.32 (at 590 mμ) and corresponding to equilibrium concentration = 0.20. The amount of dye on the wool at equilibrium = 2.12 in the units used.

Partition ratios of bromphenol blue between solvents and water solutions of different pH

Bromphenol blue may be considered an indicator acid HI, ionizing according to the formula:

where H I is yellow and I^- is blue. (In the pH range investigated, H I might have one negative charge, then the ion I has two negative charges. This is, however, of minor importance for the following discussion). As is known the addition of alcohols to aqueous solutions of indicator acids will shift the colour of the solution towards the acid side (Kolthoff, Rosenblum, 1937, p.203 f). If butanol or benzyl alcohol, in concentrations below the saturation point, is added to an aqueous solution of bromphenol blue, this shift is very small. However, by shaking an aqueous solution of bromphenol blue with butanol or benzyl alcohol, the solvent phase will contain a higher proportion of the unionized acid form than the water phase. Comparing butanol and benzyl alcohol solutions, saturated with water, the shift towards the acid side is larger in benzyl alcohol. Experiments have been made to determine the partition ratios of the two forms of bromphenol blue between butanol or benzyl alcohol and buffer solutions at different pH. When the same volume of buffer and alcohol are used at pH 1.2, the composition of the alcohol phase will be about the same as the original buffer phase, i.e. the dye exists almost entirely in its acid form. Making the same experiment at pH 7.7, when the dye is in its basic form to the greatest extent, will result in alcohol phases containing mainly the basic form. In the benzyl alcohol phase there is an increase in concentration of the acidic form and a decrease of the basic form compared with the original buffer solution, but still the concentration of the basic form is about 6 times as high as that of the acidic.

Remembering that the amount of adsorption of alcohol on wool is related to the dyeing rate, and assuming that the adsorbed alcohol is able to dissolve the dye out of the solution surrounding the wool

fibres, it should be of interest to study the partition ratios at liquor ratios which are related to the dyeing experiments. If we take the results from the adsorption measurements, about 0.06 g benzyl alcohol is adsorbed per g wool at a liquor ratio of 30:1 from an aqueous solution containing 4 % benzyl alcohol. If we regard the adsorbed amount of alcohol as one separate phase, and the dye solution as the other phase, the distribution of dye should be studied at liquor ratios of $30:0.06 = 500:1$.

Such a distribution study has been made, both for butanol and benzyl alcohol, in equilibrium with buffer solutions of bromphenol blue at pH 1.2 and 7.7 and the same concentration as used in the dyeing experiments. For experimental convenience the determination was made at a liquor ratio of 200:1. Some tests were also made at a ratio of 400:1 but this did not change the principal conclusions that could be drawn. The results are given in table 7 and may be summarized as follows.

At pH 1.2 when wool is dyed with the acidic form of bromphenol blue under the experimental conditions used, the partition ratio for this form in benzyl alcohol and buffer solution is about 470, i.e. the concentration in the benzyl alcohol is 470 times that in the buffer solution. For butanol the same partition ratio is obtained. At pH 7.7 wool is dyed by the basic form of bromphenol blue. The partition ratio for this form at the same experimental conditions will be 0.9 for benzyl alcohol and about 3 for butanol. The fact that the dyeing rate of bromphenol blue will be increases by the alcohols at pH 1.2 but almost unaffected at pH 7.7, makes it reasonable to believe, that there is a connection between the rate of dyeing and the partition ratios determined at high liquor ratios.

It should be valuable to test this hypothesis by trying to find a solvent giving a high partition ratio for the basic form of bromphenol blue and investigate the influence of this solvent on the dyeing rate of the basic form.

Table 7

Partition of bromphenol blue between alcohol
and buffer solutions

initial dye conc. 0.02 g/l

Solution ¹⁾	pH ²⁾	Optical density at		Volume of phase ml	R ⁵⁾ $\frac{R_{437}}{c_{alc}}$ $\frac{c_{buff.}}{c_{buff.}}$	R $\frac{R_{590}}{c_{alc}}$ $\frac{c_{buff.}}{c_{buff.}}$
		437 ³⁾ mμ	590 ⁴⁾ mμ			
initial solution	1.2	0.695	0.02	2000	474	
benzyl alcohol phase		98.6		10		
buffer phase		0.208		2000		
initial solution	1.2	0.768	0.02	2000	474	
butanol phase		107.5		10		
buffer phase		0.227		2000		
initial solution	7.7	0.048	2.13	2000		0.9
benzyl alcohol phase		0.985	1.88	10		
buffer phase		0.040	2.12	2000		
initial solution	7.7	0.029	2.30	2000		3
butanol phase		0.670	6.9	10		
buffer phase		0.025	2.27	2000		

- 1) the dye and alcohol solutions were mutually saturated with each other before the experiment
- 2) pH 1.2 was obtained with a sodium citrate-hydrogen chloride buffer solution, pH 7.7 with a phosphate buffer solution
- 3) wavelength at maximum extinction for the acidic form of bromphenol blue
- 4) wavelength at maximum extinction for the basic form of bromphenol blue
- 5) R = partition ratio.

Benzyl alcohol and butanol are weaker bases than water and rather bad solvents for the basic form of bromphenol blue. In looking for a good solvent for the latter, it was thought reasonable to try substances which are stronger bases than water, and which thus convert the acidic form of bromphenol blue to the basic. Many amines have these properties and we therefore tried hexylamine, the simplest aliphatic amine, which is partly soluble in water. The partition ratio for the basic form of bromphenol blue between hexylamine and a buffer solution of pH 7.7 is above 1000 at the same liquor ratio (200:1) and the same dye concentration as in the experiments with butanol and benzyl alcohol. Hexylamine is thus a good solvent for the basic form of bromphenol blue. Further experiments were made to determine if hexylamine was adsorbed by wool from aqueous solutions. Using the refractive index for determination of concentration, it was found that 1 g wool adsorb about 48 mg hexylamine after 5 min. at 60°C at a liquor ratio of 30:1 from an aqueous solution containing 0.74 g hexylamine/100 ml (almost saturated). Dyeing experiments have been made under the same conditions as used for the determination of influence of benzyl alcohol and butanol, and the results are found in the same table (Table 6). It is seen that the dyeing rate is very much increased by the addition of hexylamine to the basic form of bromphenol blue. As hexylamine is strongly basic, there will be an increase in pH of the buffer solution to about 10 by its addition to the dyebath. However, this will not affect the dyeing rate in this special case, as has been shown by dyeing from a borate buffer at pH 10.2. The experiments with hexylamine thus support the conclusions drawn from the dyeings with alcohols present in the dyebath.

Adsorption of the solvent onto wool, together with high solubility of the dye in the solvent used, is thus found to be of importance for obtaining an increase in the dyeing rate with this solvent. (It might also be possible to obtain an increase in the dyeing rate for dyes insoluble in the solvent, due to the "extraction" effect discussed in chapter 1.2. This latter effect is,

however, separate from the main mechanism).

The results may be used for formulating a hypothesis on the mechanism of solvent-assisted dyeings of wool given in chapter 4.3.

2.4 Dyeing of surface-treated wool

Experiments made at an early stage of this work have shown that the increase in dyeing rate by the addition of solvents is less for surface-treated wool than for untreated wool (see fig. 4). It was therefore considered of interest to investigate in what way the surface properties of wool fibres are connected with the mechanism of solvent-assisted dyeings. For this purpose, the properties of the wool surface were changed, as described earlier (chapter 2.1). The wools, chlorinated to different degrees, were dyed with bromphenol blue at pH 1.2 and 7.8 using benzyl alcohol or hexylamine as solvents. The experiments were carried out in the same apparatus used for the adsorption of alcohols and described previous in this chapter. As the dyeing rate of bromphenol blue on untreated wool is large at pH 1.2 and is further increased by the use of surface-treated wool, a high liquor ratio (150:1) and a low temperature of dyeing (2.5°C) were used, to make it possible to follow the change in concentration of the solution with time. A preliminary test series was performed on chlorinated wools B and C, i.e. on dry chlorinated moist wool and on the completely descaled wool. Dyeing experiments at pH 1.2 gave the same rate of dyeing on both types of wool (expressed as diffusion constants) if allowance was made for the difference in mean diameter. At pH 7.8, however, a difference in dyeing rate was obtained for wools B and C. Wool C was therefore included in the main experimental series at pH 7.8 but not at pH 1.2. The dyeing rate of bromphenol blue at pH 7.8 is much slower than at pH 1.2. For this reason, a temperature of 60°C was used, and a liquor ratio of 30:1. At higher liquor ratios the dyeing times is inconveniently long, and the equilibrium values are particularly difficult to obtain.

The experimental results are given in table 8 and 9. The concentration in the dye liquor, c_t , divided by the initial concentration, c_0 , at different times, and also the amount of dye on the fibre at time t , M_t , divided by the amount at equilibrium, M_∞ , are given. Fig. 8 and 9 show the values of M_t/M_∞ as a function of time. All curves approach unity as time increases to that necessary for obtaining equilibrium. Firstly, it is interesting to note that all three chlorine treatments cause an increase in the dyeing rate of the basic form of bromphenol blue (fig. 9), whereas the dyeing rate of the acid form (fig. 8) is decreased for wool A (dry chlorinated dry wool), but increased for the others. Changing the hydrophobic wool surface into a hydrophilic one seems to make it repellent to the acid form of the dye. The same effect was found when determining the rate of adsorption of benzyl alcohol on wool, the rate of adsorption being less on wool A than on untreated wool (see fig. 10 a and b).

The increase in dyeing rate brought about by solvents as seen in fig. 8 and 9 appears to be less for the surface-treated wool than for the untreated wool. There is, however, still an appreciable effect of the solvent on descaled wool fibres.

Calculation of diffusion constants

It would be of great interest to obtain a quantitative measure of the dyeing rate, in order to compare the influence of solvents on untreated and surface-treated wool. Vickerstaff (1954 p. 147) has given a summary of different methods for describing dyeing rates. The only method suitable for the experiments described in this paper is a calculation of the diffusion constant, where it must be assumed, that the fibres have a number of sites for fixation of the dye and that only the free concentration contributes to the diffusion. Furthermore, the experiments were made from a finite dyebath, the concentration of which rapidly decreased with time. Olofsson, 1956, has worked out an approximate method for the calculation of the diffusion constant for this case, if the diffusing

Table 8

Dyeing of wool with bromphenol blue

pH 1.2; temp. 2.5°C; initial conc. = 0.02 g/l;

liquor ratio = 150:1

Kind of wool	Addition to dye bath	Time min.	c_t/c_o ¹⁾	M_t/M_∞ ²⁾
EAW-wool (ether alcohol-water extracted)	none	2.5	0.820	0.184
		5	0.728	0.278
		15	0.509	0.501
		30	0.295	0.719
		60	0.228	0.788
		180	0.160	0.858
		∞	0.020	
	benzyl alcohol 4 % (w/v)	2.5	0.527	0.482
		5	0.330	0.684
		15	0.188	0.829
		30	0.113	0.906
		60	0.065	0.955
		180	0.056	0.964
		∞	0.020	
Chlorinated wool A (dry chlorinated dry wool)	none	2.5	0.814	0.190
		5	0.763	0.242
		15	0.550	0.460
		30	0.341	0.672
		60	0.234	0.782
		180	0.164	0.853
		∞	0.020	
	benzyl alcohol 4 % (w/v)	2.5	0.061	0.394
		5	0.473	0.538
		15	0.261	0.755
		30	0.182	0.835
		60	0.163	0.854
		180	0.124	0.894
		∞	0.020	
Chlorinated wool B (dry chlorinated moist wool)	none	2.5	0.508	0.502
		5	0.371	0.642
		15	0.205	0.811
		30	0.098	0.920
		60	0.077	0.949
		180	0.055	0.965
		∞	0.020	

1) concentration in solution/initial concentration

2) dye on fibre at time t/dye on fibre at equilibrium

Table 8 (continued)

Kind of wool	Addition to dye bath	Time min.	c_t/c_o ¹⁾	M_t/M_∞ ²⁾
Chlorinated wool B (dry chlorinated moist wool)	benzyl alcohol 4 % (w/v)	2.5	0.289	0.726
		5	0.200	0.817
		15	0.106	0.912
		30	0.068	0.951
		60	0.033	0.987
		180	0.020	1.000
		∞	0.020	

$S_m = 147$ for all test series.

S_m = number of sites for fixation of dye divided by initial bath concentration, c_o .

All values given are calculated from mean values of two determinations.

Table 9

Dyeing of wool with bromphenol blue

pH 7.8; temp. 60°C; initial conc. = 0.02 g/l;

liquor ratio 30:1

Kind of wool	Addition to dye bath	Time min.	c_t/c_o ¹⁾	S_m ³⁾	M_t/M_∞ ²⁾
EAW-wool (ether alcohol-water extracted)	none	5	0.921	26.7	0.088
		30	0.710		0.326
		60	0.527		0.530
		120	0.390		0.684
		300	0.224		0.870
		∞	0.107		
	hexyl-amine 1 % (v/v)	5	0.485	27.9	0.553
		15	0.300		0.753
		30	0.226		0.831
		60	0.166		0.895
		300	0.128		0.936
		∞	0.069		
Chlorinated wool A (dry chlorinated dry wool)	none	5	0.851	26.7	0.167
		30	0.558		0.495
		60	0.415		0.656
		120	0.266		0.823
		∞	0.107		

Table 9 (continued)

Kind of wool	Addition to dyebath	Time min.	c_t/c_o ¹⁾	S_m ³⁾	M_t/M_∞ ²⁾
Chlorinated wool A (dry chlorinated dry wool)	hexyl-amine 1 % (v/v)	5	0.532	27.9	0.502
		15	0.255		0.785
		30	0.194		0.863
		60	0.132		0.922
		150	0.123		0.941
		∞	0.069		
Chlorinated wool B (dry chlorinated moist wool)	none	5	0.674	26.7	0.365
		15	0.502		0.549
		30	0.407		0.665
		60	0.307		0.777
		120	0.207		0.888
		300	0.158		0.944
		∞	0.107		
	hexyl-amine 1 % (v/v)	5	0.421	27.9	0.621
		15	0.247		0.808
		30	0.179		0.881
		60	0.132		0.932
		120	0.132		0.932
		∞	0.069		
Chlorinated wool C (dry chlorinated moist wool and papain treatment)	none	5	0.693	25.0	0.366
		15	0.523		0.569
		30	0.436		0.673
		60	0.340		0.787
		120	0.264		0.876
		300	0.199		0.955
		∞	0.162		
	hexyl-amine 1 % (v/v)	5	0.379	26.3	0.705
		15	0.226		0.879
		30	0.183		0.928
		60	0.132		0.985
		135	0.120		1.000
		300	0.120		
		∞	0.120		

All values given are calculated from mean values of two determinations.

1) concentration in solution/initial concentration

2) dye on fibre at time t/dye on fibre at equilibrium

3) S_m = number of sites for fixation of dye divided by initial bath concentration c_o .

Fig. 8 - M_t/M_∞ as a function of time, at dyeing of untreated and chlorinated wool at pH 1.2.

Fig. 9 - M_t/M_∞ as a function of time, at dyeing of untreated and chlorinated wool at pH 7.8.

Fig. 10 a - Adsorption of benzyl alcohol as a function of time on untreated and chlorinated wool at pH 1.2, liquor ratio 30:1, initial conc. 4 g/100 ml, temp. 2.5°C.

Fig. 10 b
First part of fig. 10 a

substance is irreversibly adsorbed by the fibre. The calculation method given by Wilson, 1948, is founded on a rectilinear, reversible adsorption isotherm and was found to be less suitable for the above experimental data than was Olofsson's method. The latter was used therefore, and was found to be less laborious in practice than might be considered from a theoretical study.

Detailed directions for the calculations are given in Olofsson's paper (p. T470) and will not be repeated here. However, parts of the calculation method, which are of interest for the interpretation of the results, are described. The following symbols are used:

$$B = A/\pi a^2 = \text{volume of bath/volume of moist fibres}$$

c_0 = concentration of dye in solution at the time $t = 0$

c_+ = concentration of dye in solution at the time $t = t$

$$C_{e=1} = c_t / c_0$$

S_m = concentration of sites for dye fixation in the wool, divided by c_0

1 = position of moving boundary (see fig. 11)

a = fibre radius = 12.1×10^{-4} cm for EAW-wool, wool A, and wool B
= 9.7×10^{-4} cm for wool C

$$\lambda = 1/a$$

D = diffusion constant

Firstly, from the experimental data c_t/c_0 is plotted against the time t .

A series of values of λ (see fig. 11) is chosen arbitrarily (in this case 1.00, 0.95, 0.90, 0.85) and the corresponding values of $C_{f=1}$ are calculated from eq (20) p. T471 in Olofsson's paper. From the experimental curves, corresponding t - values are obtained and mean values of Δt are calculated for a fixed difference

Fig. 11

in the position of the moving boundary at time steps immediately before and immediately after time t . Two values of D/a^2 are then calculated according to eqs (21) and (22) respectively and a mean value of D/a^2 according to eq (28') is obtained as the final result. The numbers of the equations refer to Olofsson's paper.

From the experiments of interest in this case, the graphs of c_t/c_o against t , obtained from the values in table 8, are given in fig. 12 and 13 a and b. The chosen values of λ , the calculated values of $C_{s=1}$, and Δt_m obtained from the experimental curves are given in tables 10 and 11 together with the final values of D/a^2 . As the fibre radius, a , is constant, the variation obtained in D/a^2 is due to a variation in the diffusion constant, D . For some curves, D is fairly constant whilst for others it varies considerably. (When the dyeing rate is large, the first part of the curve has been drawn as a straight line, giving values of D which are too small at the beginning and too large at the end of the rectilinear portion). For

Fig. 12 - c_t/c_o as a function of time, at dyeing of untreated and chlorinated wool at pH 1.2 (see table 8).

Fig. 13 a - c_t/c_o as a function of time, at dyeing of untreated and chlorinated wool at pH 7.8 (see table 9).

Fig. 13 b - c_t/c_o as a function of time, at dyeing of descaled wool (wool C) at pH 7.8 (see table 9).

Table 10

Values of D/a^2 at different values of λ calculated from the experimental series in table 8

Δt_m is given in min., D/a^2 in min.^{-1}

λ	$C_{\mathcal{F}}=1$	EAW-wool		EAW-wool and benzyl alcohol		Chlorinated wool A		Chlorinated wool A and benzyl alcohol	
		Δt_m	D/a^2	Δt_m	D/a^2	Δt_m	D/a^2	Δt_m	D/a^2
0.95	0.904	1.25	0.318	0.25	1.59	1.65	0.241	0.45	0.883
0.90	0.813	1.85	0.465	0.50	1.72	2.20	0.391	0.55	1.56
0.85	0.727	2.63	0.536	0.45	3.12	3.35	0.419	0.60	2.34
0.80	0.646	3.08	0.665	0.40	5.12	3.68	0.556	0.85	2.41
0.75	0.570	3.73	0.756	0.40	5.76	4.03	0.699	1.08	2.58
0.70	0.499	3.93	0.956	0.40	9.40	4.20	0.896	1.68	2.24
0.65	0.433	4.03	1.21	0.60	8.14	4.48	1.09	2.28	2.14
0.60	0.372	4.38	1.44	1.38	4.57	5.35	1.18	2.48	2.54
0.55	0.316	6.0	1.35	2.50	3.25	8.53	0.952	2.88	2.83
0.50	0.264	17.8	0.59	3.25	3.22	26.0	0.401	4.28	2.44
0.45	0.218			3.83	3.52				
0.40	0.176			4.93	3.60				
0.35	0.140			6.23	3.69				

Table 10 (continued)

λ	$C_{\mathcal{F}}=1$	Chlorinated wool B		Chlorinated wool B and benzyl alcohol	
		Δt_m	D/a^2	Δt_m	D/a^2
0.95	0.904	0.35	1.13	0.13	3.06
0.90	0.813	0.43	2.00	0.20	4.30
0.85	0.727	0.40	3.51	0.28	5.01
0.80	0.646	0.40	5.12	0.30	6.83
0.75	0.570	0.60	4.70	0.33	8.55
0.70	0.499	1.20	3.13	0.30	12.5
0.65	0.433	1.38	3.54	0.40	12.2
0.60	0.372	1.83	3.45	0.40	15.7
0.55	0.316	2.70	3.01	0.63	12.9
0.50	0.264	3.35	3.11	1.10	9.50
0.45	0.218	3.93	3.42	1.90	7.07
0.40	0.176	4.63	3.79	3.20	5.47
0.35	0.140	5.73	4.01	4.20	5.48
0.30	0.108			5.43	5.76

Table 11

Values of D/a^2 at different value of λ calculated from the experimental series in table 9

Δt_m is given in min., D/a^2 in min.⁻¹

λ	$C_{\xi=1}$	EAW - wool		Chlorinated wool A		Chlorinated wool B	
		Δt_m	D/a^2	Δt_m	D/a^2	Δt_m	D/a^2
0.95	0.912	7.30	0.0099	3.0	0.0240	1.15	0.123
0.90	0.828	9.20	0.0167	3.85	0.0400	1.20	0.128
0.85	0.750	9.75	0.0254	4.95	0.0500	1.55	0.160
0.80	0.676	10.30	0.0347	6.50	0.0550	1.90	0.188
0.75	0.606	11.35	0.0426	8.0	0.0605	3.23	0.150
0.70	0.542	13.35	0.0469	9.83	0.0637	5.25	0.119
0.65	0.482	18.90	0.0423	11.95	0.0669	7.30	0.109
0.60	0.426	27.78	0.0360	14.48	0.0690	9.95	0.100
0.55	0.375	38.20	0.0325	17.53	0.0709	12.75	0.0975
0.50	0.328	45.93	0.0333	20.9	0.0730	15.60	0.0979
0.45	0.286	44.63	0.0409	26.0	0.0702	19.0	0.0961
0.40	0.249	46.25	0.0469	38.1	0.0569	22.5	0.0964
0.35	0.216					28.5	0.0915

Table 11 (continued)

λ	$C_{\xi=1}$	EAW - wool and hexylamine		Chlorinated wool A and hexylamine		Chlorinated wool B and hexylamine	
		Δt_m	D/a^2	Δt_m	D/a^2	Δt_m	D/a^2
0.95	0.908	0.80	0.0942	0.60	0.126	0.25	0.295
0.90	0.821	0.73	0.222	0.80	0.203	0.20	0.793
0.85	0.739	0.78	0.336	0.70	0.375	0.20	1.28
0.80	0.662	0.85	0.448	0.65	0.586	0.20	1.86
0.75	0.589	0.83	0.624	0.78	0.664	0.30	1.69
0.70	0.522	0.90	0.757	0.83	0.820	0.55	1.21
0.65	0.459	1.65	0.533	1.20	0.735	0.85	1.01
0.60	0.401	2.35	0.474	1.68	0.663	1.45	0.751
0.55	0.348	3.60	0.388	2.43	0.575	2.40	0.566
0.50	0.299	5.95	0.293	3.85	0.453	4.20	0.405
0.45	0.256	9.20	0.236	6.30	0.345	6.40	0.329
0.40	0.216	13.15	0.206	8.90	0.304	8.00	0.329
0.35	0.182	19.80	0.169			10.15	0.320

Table 11 (continued)

λ	Chlorinated wool C			Chlorinated wool C and hexylamine		
	$C_{\varphi=1}$	Δt_m	D/a^2	$C_{\varphi=1}$	Δt_m	D/a^2
0.95	0.917	0.80	0.0838	0.913	0.40	0.177
0.90	0.839	0.85	0.168	0.831	0.35	0.433
0.85	0.765	1.23	0.185	0.753	0.40	0.610
0.80	0.696	1.95	0.167	0.680	0.40	0.872
0.75	0.631	3.03	0.144	0.612	0.45	1.050
0.70	0.570	4.53	0.124	0.548	0.50	1.223
0.65	0.514	6.73	0.104	0.489	0.65	1.193
0.60	0.462	9.93	0.0868	0.434	0.95	1.015
0.55	0.414	12.28	0.0859	0.384	1.30	0.918
0.50	0.370	13.80	0.0917	0.338	1.90	0.766
0.45	0.331	18.33	0.0821	0.297	2.70	0.652
0.40	0.296	26.30	0.0677	0.260	4.38	0.485
0.35				0.227	5.93	0.428
0.30				0.199	7.03	0.429
0.25				0.175	8.40	0.419

comparison of diffusion constants, a mean value of D should therefore be calculated. The main purpose of this investigation is to compare the change in the diffusion constants for dyeings performed on wool with different surface properties with and without the addition of solvents. It is therefore considered as most suitable to use mean values of the diffusion constant obtained over the same range of λ -values, i.e. the same depth of penetration of dye into the fibres. Olofsson (in the cited paper) points out that his approximate method of calculation is most accurate at the beginning of the diffusion and should not be used for λ -values lower than 0.35 to 0.30. Therefore, mean values of D/a^2 have been calculated for λ -values from 0.95 to 0.50 and are summarized in table 12 and 13.

When the dyeing rate is high, the experimental accuracy will be low at the beginning of the dyeing period, and also rather small changes in the curve between $c_t/c_0 = 1$, $t = 0$, and the first experimental point, will then give rise to different mean values. For the curves referring to dyeing of wool B and wool C in the presence of hexyl-

Table 12

Mean values of D/a^2 and values of D_s/D for bromphenol blue on different types of wool

pH 1.2; temp. 2.5°C ; liquor ratio 150:1

Kind of wool	Addition to dye bath	D/a^2 mean value at λ 0.95-0.50	D_s/D ¹⁾
EAW-wool	-	0.828	5.5
	benzyl alcohol 4 % (w/v)	4.59	
Wool A	-	0.682	3.2
	benzyl alcohol 4 % (w/v)	2.20	
Wool B	-	3.27	2.8
	benzyl alcohol 4 % (w/v)	9.06	

$a = 12.1 \times 10^{-4}$ cm

Table 13

Mean values of D/a^2 and values of D_s/D for bromphenol blue on different types of wool

pH 7.8; temp. 60°C ; liquor ratio 30:1

Kind of wool	Addition to dye bath	D/a^2 mean value at λ 0.95-0.50	D_s/D ¹⁾
EAW-wool	-	0.0414	9.3
	hexylamine 1 % (v/v)	0.384	
Wool A	-	0.0583	8.4
	hexylamine 1% (v/v)	0.488	
Wool B	-	0.122	7.2 (5.0)
	hexylamine 1% (v/v)	0.876 (0.605)	
Wool C	-	0.116	6.8 (7.0)
	hexylamine 1 % (v/v)	0.783 (0.814)	

1) D_s = Diffusion constant in presence of solvent

$a = 12.1 \times 10^{-4}$ for EAW-wool, wool A and wool B

$a = 9.7 \times 10^{-4}$ for wool C

amine, the diffusion constant has been calculated from alternative curves in this first region. The mean value of D/a^2 in table 13 is then changed and these alternative values are given within brackets.

The quotients between the D/a^2 -values, D_g/D i.e. the diffusion constants for dyeings with and without solvents on the same wool sample are also given in the tables 12 and 13.

For bromphenol blue at pH 1.2 the diffusion constant is increased 5.5 times by the addition of 4 % benzyl alcohol to the dyebath when the dyeing is performed on untreated wool, but only 3.2 or 2.8 times on chlorinated wool.

The corresponding increase in diffusion constant for bromphenol blue at pH 7.8 by the addition of 1 % hexylamine is 9.3 times for untreated wool and decreases to 8.4 for wool A, 5.0 - 7.2 for wool B and 6.8 - 7.0 for the descaled wool.

The absolute magnitude of these values refer to the investigated system and should not be considered representative for solvent-assisted dyeings in general. The relative values, however, i.e. the changes in D_g/D due to surface treatments, should be valid for solvent-assisted dyeings performed on the same kind of surface-treated wool as described.

The same general picture is thus obtained from the two dyeings made under different experimental conditions. For all surface-treated wool samples, the values of D_g/D decrease compared with untreated wool. The decrease is larger for wool B and C than for wool A. Dyeing with the acid modification of bromphenol blue gives the same result on wool B and C, but there might be a slight difference for the basic modification on these two chlorinated wools, depending on which mean value of D is used.

Furthermore, it may be noted that the number of sites for dye fixation of the basic form of bromphenol blue (as expressed by the

values of S_m in table 9 is slightly less in descaled wool (wool C) than in untreated wool (EAW-wool). The number of these sites is increased by the addition of hexylamine to the dyebath. Thus hexylamine will cause a change in the equilibrium exhaustion of the dye-bath both on untreated and chlorinated wool, and a difference in equilibrium exhaustion without the addition of hexylamine will also be obtained for wool C compared with the other kinds of wool.

Benzyl alcohol has no such effect on the acid form of bromphenol blue, and the number of sites available to this form of the dye is found to be equal on untreated and descaled wool.

Summarizing, it might be stated that the rate of adsorption of the solvent is dependent on the surface properties of wool, and that solvents cause smaller increase in the dyeing rate of chlorinated wool. The surface properties of wool are thus important in solvent-assisted dyeings, although the same mechanism of dye adsorption in such dyeings may apply with both untreated and surface-treated wool.

2.5 Influence of solvents on stress relaxation and swelling of wool fibres

Stress relaxation of wool fibres

In wool fibres break-down of cross linkages between the polypeptide chains, followed by a molecular rearrangement, has been proposed to account for stress relaxation (Speakman et al, 1941). The cross-linkages present in wool fibres include covalent disulphide bonds, salt linkages, hydrogen bonds and van der Waal's forces. If the alcohols used in solvent-assisted dyeings are able to break these cross-linkages to a much higher degree than water alone, this could increase the dyeing rate. It should be possible to determine the extent to which this occurs from stress-relaxation curves, as increased bond breaking would give rise to increased stress relaxation. The method of Katz and Tobolsky, 1950, has been used for this purpose. Wool fibres were extended 15% in water at 60°C, using an Instron Textile Testing machine, and the decay of tension at constant

temperature and extension was recorded. After one hour's relaxation of the fibre, amyl alcohol (3 % by volume) or butanol (5 % by volume) was added to the water and the decay of tension followed for several hours.

However, no change in the relaxation curve could be observed after the addition of one of these alcohols to the water. Break-down of cross-links and molecular rearrangement by these alcohols thus seem to be rather improbable.

Swelling of wool fibres

When wool is immersed in water there is a diffusion of water molecules into the fibres. Because of the presence of hydrophilic groups in the fibre this causes swelling.

An increase in the degree of swelling of a fibre would indicate break-down of cross-linkages, with a consequent increased rate of diffusion of dyes. Atkinson et al, 1959, have observed a small increase in swelling of wool by an aqueous solution containing 45 % propanol.

The change in swelling of wool fibres resulting from the addition of benzyl alcohol or hexylamine to an aqueous solution has therefore been determined from the change in fibre diameter. For this purpose, EAW-wool from the same piece of top, was divided into six parts. Five of these were immersed in the following solutions at room temperature for 48 hours: 1) distilled water + 0.075 % of a nonionic wetting agent; 2) 4 % (w/v) benzyl alcohol in distilled water; 3) buffer solution at pH 7.8 + 0.075 % of the above wetting agent; 4) buffer solution at pH 10.0 + 0.075 % of the above wetting agent; 5) 1 % (v/v) of hexylamine (buffer solution of pH 7.8). As shown previously, solution 5 has a pH of about 10.

The sixth part was brought to equilibrium with an atmosphere of 65 % relative humidity at room temperature.

The diameters of the fibres were measured microscopically with a pro-

jection microscope, operating at a magnification of 500x - the procedure is the technique standardized in the Swedish standard method SIS 65 00 04. Eight samples were prepared from each of the six treatments and one hundred fibres were measured from each sample. The mean diameters of these hundred fibres are given in table 14. The 95 % confidence interval for the difference between two mean values is calculated under table 14 and found to be 0.67μ . This means that, by the technique used, a change in diameter of 2.8 % (absolute) can be detected by this method. By increasing the pH to about 10 either by addition of hexylamine or by introducing a borate buffer of this pH the fibre diameter will increase by the above amount. It has, however, been shown earlier (see table 6) that hexylamine increases the rate of dyeing, but a mere change in pH by the addition of borate has no such effect. As wool fibres are already highly swollen in water (13.3 % increase in diameter over the air dry sample), this increase in swelling of a few percentages seems to be relatively unimportant to the rate of dyeing. The addition of benzyl alcohol also seems to increase the fibre diameter to some extent (but less than the confidence interval). The increase in swelling is interesting, as it might indicate changes in the fibre due to the adsorption of benzyl alcohol or hexylamine, but it is rather improbable that this increase, as such, can affect the rate of dyeing to any great extent.

Table 14

Swelling of wool fibres in different solutions

Fibre diameter (mean diameter of 100 fibres) in μ					
in air of 65% rel. humidity	1 aq. dest.	2 4% benzyl alcohol in water	3 Buffer so- lution pH 7.8	4 Buffer so- lution pH 10	5 1% hexyl- amine in buffer of pH 7.8
23.50	26.81	27.59	26.65	28.44	27.51
23.57	28.36	26.83	26.37	26.47	27.49
22.87	25.34	27.51	26.07	27.95	27.88
23.89	26.49	26.81	27.59	26.83	27.85
23.73	26.12	27.18	26.94	26.76	26.51
23.54	27.32	26.44	26.41	26.51	27.00
23.69	26.03	27.66	26.48	27.64	27.81
23.63	26.94	27.00	26.44	28.01	26.79
Mean value	23.55	26.68	27.13	26.62	27.36
Variance, s^2, μ	0.091	0.841	0.189	0.215	0.595
Increase in diameter % of diam. in air	13.3	15.2	13.0	16.1	16.2

Mean value of $s^2 = 0.368 \mu$

The 95 % confidence interval, d_1 for the difference between two mean values of fibre diameter = $t \cdot s \sqrt{\frac{1}{n_1} + \frac{1}{n_2}}$ where $t = 2.2$, $s = \sqrt{s^2} = 0.606$, $n_1 = n_2 = 8$, which gives $d = 0.667 \mu$, which corresponds to 2.83 % of the fibre diameter in air.

CHAPTER 3

GENERAL DISCUSSION OF THE MECHANISM OFSOLVENT-ASSISTED DYEING OF WOOL

The results of interest in the mechanism of solvent-assisted dyeing, obtained from the foregoing experimental investigations may be summarized briefly as follows.

All solvents investigated are adsorbed on to the wool.

For some alcohols there exists a simple relationship between the amount of adsorption and the dyeing rate.

A particular alcohol might have no effect on the dyeing rate of a dye at a pH about 7, but increase the rate for the same dye at a lower pH, although the adsorption of this alcohol is nearly the same at both pH-values. The solubility of the dye in the alcohol is large at the low pH-value where the dyeing rate is affected, but low at the higher pH. By using an amine in which the dye has high solubility at this latter pH, an increase in the rate of dyeing can be obtained.

Solvent-assisted dyeings of surface-treated wool show that solvents cause less increase in the dyeing rate in this case than with untreated wool, although an appreciable effect of solvents may be obtained with descaled wool.

The distribution of dye between different wool fibres and also between different parts of the same wool fibre becomes more uniform when dyeing is carried out in the presence of solvents.

The presence of alcohols in the dyebath can increase the dyeing rate of some dyes by an "extraction" effect. The dyeing rate of 1:2 chrome-complex dyes are, however, unaffected by previous extraction with alcohols in aqueous solution.

The solvents may cause some swelling of the wool fibres (less than 3 % increase above the swelling in water).

No change in the stress-relaxation properties in water has been observed after the addition of an alcohol. The breaking tenacity and elongation at break are not changed by the presence of an alcohol in the dyebath.

For the same amount of dye on the wool, a higher percentage of fibres was penetrated by the dye in the presence of a solvent than in the normal aqueous system, even though the time of dyeing was much shorter.

The fastness properties of dyeings are about the same, whether solvents are used or not.

The three latter statements are obtained from results of the industrial experiments described in chapter 4.

In discussing the mechanism of solvent-assisted dyeing of wool, it seems fairly reasonable to make comparisons with carrier dyeing of synthetic fibres. This was also done by Kärrholm and Lindberg, 1956, in the previously cited paper. In that paper, reference was made to Kramer, 1955, who proposed that the carrier is adsorbed on the fibre surface, and in this layer the dye concentration is higher than in the bath, thus giving rise to a higher concentration gradient, causing a higher diffusion rate into the fibre. The solvent-layer theory of carriers is also treated by other investigators, e.g. Choquette, 1954, supporting this theory, whereas the microdyoscope studies published by Millson, 1955, might be used against the theory.

Another effect ascribed to the carrier is to open internal bonds, e.g. hydrogen bonds, thus facilitating penetration of the dye (Kramer, 1955, Fortess et al, 1958). The carrier acts on the fibre by both these mechanisms. It has, however, been proposed that the carrier might also act on the dye in the dyebath, decreasing the

degree of aggregation and thus increasing the concentration of single dye molecules, thereby increasing the dyeing rate (see e.g. Zimmerman et al, 1955).

The latter mechanism may be rejected for solvent-assisted dyeing of wool, because solvents give an increased rate of dyeing with a dye which is monomolecular in solution. Even if there should be some aggregation of this dye, the concentration of single molecules should still be so large, that any increase by disaggregation could hardly account for the increase in dyeing rate.

It may be concluded therefore that the solvent will act on the wool fibre and not on the dye in the dyebath.

Three possible mechanisms for solvent-assisted dyeing are:

- 1) the effect of a solvent layer,
- 2) loosening of the fibre structure,
- 3) supplementing of normal diffusion in fibre by diffusion in the adsorbed solvent.

These alternatives are discussed below.

3.1 The effect of a solvent layer

According to this hypothesis the solvent is considered to be adsorbed on the wool as a surface layer. The high solubility of the dye in this layer gives a high concentration which should cause more dye molecules to diffuse into the fibre per unit time.

However, if this hypothesis is treated thermodynamically as a system in equilibrium then, for the reasons given below, no increase in the dyeing rate is to be expected.

Equilibrium treatment

It is assumed that a dye is dissolved in the solution with an activity a_c and in the solvent layer with the activity a_s . The sol-

vent layer is in equilibrium with the outer solution and has the same activity in all parts. Furthermore, it is assumed that the fibre in contact with the solvent layer has attained its equilibrium activity, a_f .

The chemical potential of the dye in solution, μ_c , in the solvent layer, μ_s , and on fibre, μ_f , is given by the following equations:

$$\mu_c = \mu_c^0 + RT \ln a_c$$

$$\mu_s = \mu_s^0 + RT \ln a_s$$

$$\mu_f = \mu_f^0 + RT \ln a_f$$

where μ^0 is the standard chemical potential in the respective phase, R is the gas constant and T the absolute temperature.

At equilibrium, $\mu_c = \mu_s = \mu_f$

and thus, $\mu_c^0 - \mu_f^0 = RT \ln a_f - RT \ln a_c$.

For the same system without a solvent layer,

$$\mu_c^0 - \mu_f^0 = RT \ln a_f' - RT \ln a_c'$$

where a_f' and a_c' are the activities of dye on fibre and in solution in this case.

As the outer concentration is unaffected, or might be decreased, by the presence of a solvent layer

$a_c \leq a_c'$, which means that $a_f \leq a_f'$;

The activity of dye on the fibre when a solvent layer is present is thus equal to, or less than that in the absence of such a layer.

This treatment presupposes equilibrium conditions. However, as the rate of dyeing is being considered, a kinetic treatment would be more correct.

Kinetic treatment

It is assumed that the fibre has a surface layer of different properties (e.g. an epicuticle on a wool fibre) and there is an outer solvent layer in contact with a dyebath. This is shown in fig. 14.

Fig. 14

From consideration of diffusional flow across the boundaries, the following expression has been deduced by B. Olofsson (unpublished).

$$L = \frac{a}{D \left[\frac{\delta_{ep}}{D_{ep}} \cdot F_{ep} + \frac{\delta_s}{D_s} F_s \right]}$$

where a is the fibre radius, D is the diffusion constant of dye in the fibre, D_{ep} and D_s are the diffusion constants in the surface barrier and solvent layer respectively. F_{ep} and F_s denote the partition constants of dye concentrations at equilibrium between the surface barrier and water, or solvent and water. L is a dimensionless parameter, proportional to the combined permeability of the surface layers.

From the above expression, different L -values might be calculated for a fibre with and without epicuticle, and also with and without a solvent layer. Sorption and desorption curves for different L -values at infinite liquor ratio are given by Crank, 1956, and shown in fig. 15. From these curves, the influence of the parameters of interest on the uptake of dye might be obtained.

A quantitative treatment is questionable as many rather uncertain assumptions must be made, but the qualitative treatment below gives some valuable information.

Fig. 15 - M_t/M_∞ as a function of $[Dt/a^2]^{1/2}$. Numbers on curves are values of L (from Crank, 1956, p. 74).

I. Fibre without surface barrier (epicuticle)

In this case $\delta_{ep} = 0$ and the expression for L becomes:

$$L_s = \frac{a}{D \delta_s / D_s F_s} = \frac{D_s F_s}{D} \cdot \frac{a}{\delta_s}$$

When calculating L for fibres without a solvent layer, this layer is replaced by water of the same thickness:

$$L_w = \frac{D_w \cdot F_w \cdot a}{D \cdot \delta_w} = \frac{D_w}{D} \cdot \frac{a}{\delta_s}$$

as $F_w = 1$ and $\delta_w = \delta_s$. The quotient

$$L_s/L_w = \frac{D_s}{D_w} \cdot F_s = F_s$$

as D_s may be assumed to have about the same value as D_w .

The partition ratio of dye between solvent and water is usually high in solvent-assisted dyeings. If a value of $F_s = 100$ is assumed then $L_s = 100 L_w$.

From fig. 15 it is seen that the effect of an increase of L on the uptake of dye (M_t/M_∞) is greater, the smaller the value of L . Therefore an attempt is made to find the lowest possible value of L_w .

The lowest value of D_w/D will be 1; very probably the diffusion constant of dye in water is higher than in the fibre, although not necessarily much higher, as D denotes the true diffusion constant of the free dye in the fibre. The highest value of the thickness of the solvent layer δ_s is obtained by assuming that all of the adsorbed solvent is on the surface of the wool. For an adsorption of 6 % on the weight of the wool, a value of

$$\delta_s/a = 3 \times 10^{-2}$$

is obtained.

Substitution in the above expression for L_w gives $L_w \leq 33$.

From fig. 15 is seen that if $L = 10$ an increase to $L = \infty$ will only give a low increase in the uptake of dye as a function of time.

II. Fibre with surface barrier (epicuticle)

A) Without solvent layer

The solvent layer is replaced by a water layer of the same thickness. If the epicuticle is assumed to have a thickness of about 0.1μ , and the fibre radius, a , to be about 10μ , then

$$\delta_{ep}/a \simeq 10^{-3}; \quad \delta_s/a = 3 \times 10^{-2}; \quad F_s = 1; \quad D_s = D_w; \quad D \leq D_w.$$

The expression for L will be dependent on the nature of the surface barrier. It might be assumed that the affinity for the dye and also the diffusion constant are low. This means that $F_{ep} \leq 1$ and $D_{ep} \leq D$. The value of L will then be less than 30. As seen from fig.

15 a decrease of L from this value might cause an appreciable decrease in the uptake of dye as a function of time. By assuming that $F_{ep} = 0.01$ and $D_{ep} = D$, then $L = 10$; for $F_{ep} = 0.01$ and $D_{ep} = 0.01 D$, then $L = 0.1$.

The retarding effect of a surface barrier upon the rate of dyeing is thus demonstrated by this treatment.

II B. With solvent layer

In the expression

$$L = \frac{a}{D \left[\delta_{ep}/D_{ep} F_{ep} + \delta_s/D_s F_s \right]}$$

the first term in the denominator referring to the surface barrier will increase with the efficiency of the barrier (decreasing F_{ep} and D_{ep}). The second term in the denominator referring to the solvent layer will decrease with a higher concentration and higher diffusion constant of dye in the solvent layer (increasing F_s and D_s). It is thus theoretically possible that the two expressions might balance each other, the decrease in dyeing rate caused by a surface barrier being counteracted by the increase caused by a solvent layer. However, by using the constants given above for this actual case, a rather small influence of the solvent layer is found. The value of $\delta_s/D_s F_s$ will be small as F_s increases compared with $\delta_{ep}/D_{ep} F_{ep}$, and the latter will determine the magnitude of L .

The effect of a solvent layer in increasing the rate of dyeing when a surface barrier is present, can therefore be expected to be rather small.

The above kinetic treatment thus demonstrates that a solvent layer with high concentration of dye theoretically might cause some increase in the rate of dyeing, but this increase is small, and cannot account for the large increases in dyeing rate obtained experimentally with solvent-assisted dyeings. The effect of a surface

barrier in decreasing the rate of dyeing is, however, demonstrated and this effect might be appreciable.

An experimental and theoretical treatment of the influence of a surface barrier on the dyeing rate of wool based on assumptions other than those above, has been published recently and shows a definite effect of a barrier in decreasing the rate of dyeing at the beginning of the dyeing period (Medley and Andrews, 1959).

The solvent layer theory as stated above is thus an unsatisfactory explanation of solvent-assisted dyeings of wool.

3.2 Loosening of the fibre structure

An investigation by Rochas and Courmonts, 1959, of the action of a carrier in dyeing polyester fibre with disperse dyes has shown that the carrier functions by loosening the fibre structure. After total elimination of the carrier by treatment with steam, the increase in dyeing rate remains, although not quite to the same extent. The Delaware Valley section of the AATCC in a previously cited publication also proposes that the carrier acts on the fibre, and rejects both the solvent layer theory and action on the dye in the dyebath.

An extensive investigation of accelerant dyeing of hydrophobic fibres, published by the Piedmont Section of the AATCC, 1959, discusses nine mechanisms for carrier dyeing published to date and rejects them all for different reasons, with the exception of theories involving changes in the internal structure of the fibre. The carrier is considered to form "fibre-carrier" bonds, thereby breaking the "fibre-to-fibre" bonds. The "fibre-carrier" bonds, being looser bonds, give greater accessibility of the fibre.

The experimental data on solvent-assisted dyeing of wool do not contradict this theory, although it might be difficult to explain some results, if this theory alone is used. When wool is treated with a solution of amyl alcohol in water, and the alcohol washed out com-

pletely, an increased dyeing rate is obtained for some dyes, as shown in chapter 1. This is called the "extraction effect" and corresponds to the effect of carriers on polyester fibres described by Rochas et al. However, no "extraction effect" was obtained with Cibalanblau BL as can be seen from fig. 4 and yet, with this dye, a large increase in the dyeing rate was caused by solvents.

As shown in chapter 2.5 the stress-relaxation curve in water was unchanged by the addition of solvents. This would indicate that breaking of cross-bonds did not occur to any large extent. It might be possible, however, that the number of cross-linkages that must be broken to obtain an increase in the rate of dyeing, is smaller than that necessary to cause a change in the stress-relaxation curve.

Furthermore, there is an increase in the swelling of wool by adsorption of benzyl alcohol or hexylamine from aqueous solutions, indicating a loosening of the fibre structure. However, the additional swelling is small (less than 3 %).

By assuming the above theory to be the only one valid, it is difficult to explain why benzyl alcohol should increase the dyeing rate of bromphenol blue at pH 1.2 and not at pH 7.8 as it is adsorbed to about the same extent at these two pH-values.

Furthermore, it is difficult to see why the same carrier could not be used for all dyes of about the same size, irrespective of their chemical constitution. Neither is the condition of high solubility of the dye in the solvent or carrier explained by assuming only a loosening of the fibre structure. These aspects of the theory are overlooked in the paper cited above (Piedmont Section of AATCC).

In conclusion it might be stated that, for the hydrophobic fibres with a very compact internal structure, loosening of the fibre structure seems to be the most important function of the carrier in increasing the dyeing rate. Hydrophilic fibres, such as wool, however, are already highly swollen in water, so that further loosen-

ing of the structure by solvents might not be as important as with hydrophobic fibres. Furthermore, the theory cannot account for all the experimental data. For example, it does not explain why a high solubility of dye in solvent is necessary to obtain an increase in dyeing rate. If we accept the fact that solvents change the internal structure of the fibre, we still need another explanation for the dyeing mechanism.

3.3 Diffusion of dye in the adsorbed solvent

In this paper, it is shown that the solvent is adsorbed by the wool, and that this adsorption is one necessary condition for obtaining an increased dyeing rate. Another condition is, that the solubility of the dye in the solvent used must be high. As a first approximation we consider the solvent adsorbed on the wool as a separate phase. This phase is then small compared with the water phase. Under the experimental conditions used the ratio of the volume of the water phase to that of solvent phase is of the order of 500:1. Furthermore, it must be assumed that the dye molecules can be transported into the wool fibres in the adsorbed solvent phase at the same time as the normal dye transportation takes place by means of diffusion in the water-swollen fibre phase. If the dye concentration in the solvent phase is much higher than in the water phase, a large proportion of the dyestuff is transported by means of the solvent phase and an appreciable increase in dyeing rate is obtained. However, with about the same concentration in both phases there will only be small changes in the dyeing rate.

The difficulty with this hypothesis, however, is the assumption that the adsorbed solvent forms a separate phase. For dyes, the dyeing rate of which is increased by solvents, the affinity for the fibre from a solvent solution is low, as is also the partition ratio of dye between water and solvent, as shown in chapter 1. Although the dye might be transported in the solvent phase, it is not very probable that it will leave this phase and be adsorbed by the fibre.

These difficulties might be overcome by a slight change in the hypothesis.

Diffusion of dye in a fibre is assumed to take place through a system of canals. Part of the dye is in aqueous solution, while the remainder is adsorbed on the walls of the canals. It is usually assumed that the adsorbed dye is so firmly held that surface diffusion along the walls of the pores can be considered negligible as compared with the diffusion in solution (Vickerstaff, 1954, p. 141). However, a theoretical treatment is given by Standing et al, 1947, for the case when diffusion along the walls of the pores is significant.

When a solvent is adsorbed on wool we might assume that the pore walls, to some extent, are covered with solvent molecules. Dye molecules, adsorbed on these solvated walls, may be assumed to have greater mobility than when adsorbed on the fibre molecules. Either a diffusion takes place along the solvated walls, or the concentration of "free" dye molecules in solution is increased by breaking the weak fibre-solvent bonds. In both cases an increase in the rate of diffusion is obtained. A high solubility of the dye in the solvent would then result in a high degree of adsorption of the dye molecules on the solvated walls. By this treatment we do not need to assume a separate solvent phase with a phase boundary at the fibre.

This theory is supported by the microscopical studies of cross-sections from the industrial dyeing experiments (see chapter 4). The ring-dyed fibres obtained after conventional dyeing give evidence of a strong attraction between fibre and dye. The dyeings in the presence of butanol show rapid penetration, pale in the beginning, but growing darker as the dyeing proceeds. This behaviour is also obtained by dyes with low affinity for the fibre.

According to the above theory the more uniform dye distribution obtained in the presence of solvents indicates that the adsorption of the solvents is also rather uniform. A change in dyeing conditions

resulting in all parts of a fibre surface becoming accessible to the dye will, in itself, cause an increase in the dyeing rate. Such a uniform dye distribution at the beginning of a dyeing can be obtained by surface-treatment of wool (Millson et al, 1950, Lindberg, 1953). However, as surface-treated wool still shows an increase in dyeing rate in the presence of solvents, it is unlikely that the more uniform dye distribution is responsible for the increase, although it might be in the case of untreated wool. For these reasons, solvents can be expected to cause a greater increase in dyeing rate on untreated wool than on chlorinated wool.

However, even in the case where no change in dye distribution occurs, a relation between the increase in, and the magnitude of, the dyeing rate in a given system is to be expected from the theory given above. Under conditions where the amount of dye diffusing into the fibre is increased by changing, for example, the fibre properties or temperature of dyeing, without any change in the adsorption of solvent or solubility of dye in solvent, the relative effect of the solvent would be less in increasing the rate of dyeing.

Under the experimental conditions used in chapter 2.4 the increase in the rate of dyeing caused by solvents was about twice as great on untreated wool as on chlorinated wool. This is probably due to both factors described above. The results of dyeing untreated and alkali-treated wool with Cibalanblau BL given in fig. 4 might also be explained by these two factors.

However, the effect of some solvents in causing a more uniform dye distribution might have as much practical importance as an increase in the dyeing rate, although it is more difficult to express this in a quantitative manner.

CHAPTER 4

INDUSTRIAL EXPERIMENTS ON LOOSE WOOL DYEING

When loose wool is dyed industrially, care is usually taken to obtain a dyeing rate which is low enough to give level dyeing. The levelness will depend on the properties of the dyestuff and also on the design of the dyeing machinery.

In an ideal loose wool dyeing process all fibres should be subjected to the same concentration of dye liquor at the same time. In a conventional loose wool dyeing machine, however, the dye liquor is circulated through a large plug of wool fibres. If the rate of flow of the liquor is slow compared with the dyeing rate, the concentration of dye in solution may decrease considerably in the initial stages of dyeing, causing an uneven dye distribution. Subsequently, a redistribution will take place from more to less coloured parts of the wool. This is, however, a rather slow process, especially for dye with high affinity for wool.

The more uniform distribution of dye between different wool fibres in the presence of a solvent as described in the previous chapter is a clear advantage in technical dyeing processes. It is, however, important to investigate whether the increased dyeing rate brought about by solvents, can be utilized in technical dyeings.

For this reason experiments were carried out in a Swedish mill; loose wool was dyed by conventional methods and also with butanol or amyl alcohol added to the dyebath. Time and temperature of dyeing were varied, and the following properties were studied: levelness and fastness properties of the dyeing, penetration of dye into the fibre and change in mechanical properties of the wool fibres due to the dyeing process. The result of this investigation has been reported, but a brief summary will be given below (Kärrholm, 1956 and 1958, in Swedish).

4.1 Performance of the experiments

Raw material

Two types of wool were used. Cape wool, from 8 - 10 months old sheep, and Australian wool (58's). The wool was scoured in a textile mill by their usual methods. The Cape wool was used for the main experiments and the results given below refer to this type of wool.

Apparatus

A stainless steel dyeing machine for loose wool containing 10 kg wool and 170 l dye liquor was used. The liquor was circulated in only one direction (from bottom to top of the packed wool).

Dyestuff

All dyeings reported here were performed with Cibalanblau BL (1:2 chrome-complex dye).

Procedure

The wool was packed in a perforated stainless steel container with the addition of cold water, and the container then placed in the dyeing machine. Liquor containing ammonium sulphate (3 % on the weight of the wool) and acetic acid, at a pH of 6.2 - 6.4 was circulated through the wool. The temperature was adjusted to 40°C. When an alcohol was used, it was then added to the bath, and some minutes afterwards, the dye (2 % on the weight of the wool) dissolved in water, was also added. The temperature was raised to the desired value and dyeing was continued for a fixed time. The bath was then emptied, and the wool rinsed in the machine four times with cold water. Small samples were taken from the top, the middle and the bottom layer in order to compare the colours for levelness. The wool was then centrifuged and dried.

Dyeing was carried out either at 70°C for different times in the presence of butanol (5 % by volume) or amyl alcohol (3 % by volume),

or at 95° C for 5 minutes with butanol in the dyebath. In one series, the wool was dyed at 70° C for 20 min. and the temperature then raised to 95° C and kept there for about 5 min. A conventional dyeing without the addition of alcohols was made by circulating the dye liquor through the wool at 95° C for 45 min. In all cases exhaustion of the dyebath was almost complete. The dyeing conditions are summarized in table 15.

Table 15

Dyeing conditions used in the industrial dyeing experiments

Cibalanblau BL 1.18 g/l; liquor ratio 17:1; pH 6.2 - 6.4

Test series nr	Addition to dyebath	Time in min. at a temperature of				Exhaustion of dyebath % of available dye
		40-70° C	70° C	70-95° C	95° C	
1	none	←	45	→	45	
2	amyl alcohol 3% by volume	17	20			~ 99
3	butanol 5% by volume	16	20			> 95
4	- " -	17	40			~ 99
5	- " -	16	80			~ 99
6	- " -	17	20	10	6	~ 99
7	- " -	←	30	→	5	~ 99

4.2 Results and conclusions

Results

Levelness

In all test series, where the alcohol was added at 40° C, only small differences in depth of colour were obtained between the top and bottom layers of the wool. Practical dyers considered that the overall level-

ness was at least as good as a conventional dyeing.

Penetration of dye into the fibres

The degree of penetration was determined by microscopical examination of cross-sections of the fibres. These were divided into two classes; ring-dyed and completely penetrated fibres (no undyed fibres were detected). The results are given in table 16 and represent the mean values from 500 fibres.

Table 16

Penetration of dye into wool fibres
at different dyeing conditions

Test series	Time and temp. of dyeing	Addition to dye bath	% completely penetrated fibres	% ring-dyed fibres
1	45 min. at 95°C	none	13	87
2	20 min. at 70°C	amyl alcohol 3%	35	65
3	20 min. at 70°C	butanol 5 %	14	86
4	40 min. at 70°C	butanol 5 %	23	77
5	80 min. at 70°C	butanol 5 %	65	35
6	20 min. at 70°C + + 5 min. at 95°C	butanol 5 %	85	15
7	5 min. at 95°C	butanol 5 %	80	20

From the table it is seen that conventional dyeing gives the lowest proportion of completely penetrated fibres. Further, dyeing for a short time at 95°C gives a higher percentage of completely penetrated fibres than longer times at 70°C. Increasing the dyeing time at the same temperature, in the presence of butanol, results in a higher percentage of penetrated fibres. Amyl alcohol gives a higher degree of penetration than does butanol under the same conditions.

The cross-sections also reveal a difference in appearance of the

dyed fibres. Cibalanblau BL penetrates the wool fibres as a sharp boundary, slowly moving inwards. After conventional dyeing, the fibres are either completely undyed in the centre, or the whole cross-section has the same strength of colour. When the dyeing was performed in the presence of alcohols, however, complete penetration is rapidly obtained. The cross sections show a pale but uniform distribution of colour growing darker as dyeing proceeds. At the same time a sharp boundary of dye slowly moves inwards.

Fastness properties

The fastness properties of the dyeings to rubbing, washing and light were tested. Swedish standard methods were used for the determinations: SIS 65 00 14 for the fastness to rubbing, SIS 65 00 17 for the fastness to washing at 40° C and SIS 65 00 13 for the fastness to light, using the Fade-Ometer for testing. In table 17 the values obtained are summarized. For fastness to rubbing and washing, the scale runs from 1 to 5, the lowest rating being 1, and 5 the highest. For light fastness the scale is F 1 to F 8, F 1 being the lowest and F 8 the highest fastness.

Table 17

Fastness ratings to rubbing, washing and light
of wool dyed at different conditions

Nr	Time and temp. of dyeing	Addition to dyebath	Fastness ratings to				
			rubbing		washing at 40°C staining on		light
			dry	wet	cotton	wool	
1	45 min at 95°C	none	4	4	5	4-5	F7
2	20 min.at 70°C	amyl alcohol 3%	3	5	4-5	4	F6
3	20 min at 70°C	butanol 5 %	3-4	4-5	4-5	4-5	F6
4	40 min at 70°C	-"-	4	4-5	5	4-5	F6
5	80 min at 70°C	-"-	4	4-5	5	4-5	F6
6	20 min at 70°C + + 5 min at 95°C	-"-	4-5	5	5	4-5	F7
7	5 min at 95°C	-"-	4-5	4-5	5	4-5	F7

About the same fastness to rubbing as by conventional dyeing is obtained in the presence of butanol, but amyl alcohol in the dyebath causes a lower fastness to rubbing in the dry state, probably due to the lower solubility of the alcohol in water, which makes it more difficult to remove from the wool. The fastness to washing of the dyeings is hardly influenced by using alcohols in the dyebath.

Fastness to light is also unaffected provided the dyeings are performed at 95° C. Dyeings at 70° C, however, give a lower fastness rating to light.

Mechanical properties

The influence of the dyeing process on breaking tenacity and elongation at break of the fibres was determined on an Instron textile testing machine. 30 fibres from each sample were tested and the diameter of each fibre was measured by the resonance frequency method (Gonsalves, 1947). The results are given in table 18 together with the standard deviations. The confidence interval, d , for the difference between two mean values of the breaking tenacity has been calculated from $d = t s \sqrt{1/n_1 + 1/n_2}$, where s is the standard deviation obtained as the square root of the mean value of s^2 in table 18, n = number of tests. In this case $n_1 = n_2 = 30$. t is obtained from statistical tables. The 95 % confidence interval obtained = 0.14 g/den for the breaking tenacity and 7 % for the elongation at break. Thus, there is no change in the breaking tenacity and elongation for dyeings 2, 3 and 4 i.e. the batches dyed at 70°C for 40 min. or less in the presence of butanol or amyl alcohol. For the other dyeings there may be a tendency for both breaking tenacity and elongation at break to be reduced. The largest loss of tenacity and elongation is, however, given by a conventional dyeing process.

Table 18

Mechanical properties of wool fibres,
dyed at different conditions

Test series	Time and temp. of dyeing	Addition to dyebath	Breaking tenacity g/den.	s ¹⁾	Elongation at break %	s ¹⁾
1	45 min at 95°C	none	1.07	0.30	32.2	17.3
2	20 min at 70°C	amyl alcohol 3 %	1.23	0.19	47.5	19.2
3	20 min at 70°C	butanol 5%	1.23	0.31	42.2	15.0
4	40 min at 70°C	"-	1.29	0.21	47.7	11.4
5	80 min at 70°C	"-	1.13	0.25	38.5	15.2
6	20 min at 70°C + +5 min at 95°C	"-	1.14	0.29	42.0	13.7
7	5 min at 95°C	"-	1.14	0.27	40.8	14.3
	undyed	-	1.24	0.27	45.3	12.2

Mean value 0.264 13.7

1) s = standard deviation

The mean value of the standard deviation determined from the mean value of the variance is 0.26 g/den for the breaking tenacity; and 13.7 % for the elongation at break.

The 95 % confidence interval for the difference between two mean values is 0.14 g/den for the breaking tenacity and 7 % for the elongation at break.

Conclusions

The increased dyeing rate of wool, brought about by some alcohols, could be technically utilized in two ways, either by lowering the temperature of dyeing with normal dyeing times, or by decreasing the time of dyeing at normal dyeing temperature. From the above experiments it was found that, when butanol was used in the dyebath, the wool always appeared darker after dyeing at 95°C than at 70°C , although the amount of dye on the fibres was the same in each case.

This difference is explained by the higher degree of penetration obtained after dyeing at 95°C . Garrett and Peters, 1956, have shown that an increase in penetration from 10 per cent to 100 per cent has the same effect as a 33 per cent increase in dye concentration. The fastness properties are also slightly better after dyeing at the higher temperature. For these reasons a solvent-assisted dyeing process performed at about 95°C for a short time (5 min.) is superior to one at 70°C for a longer time (40 min).

Comparing conventional loose wool dyeing with a process using solvents (e.g. butanol) to increase the rate of dyeing, the latter process gives the same over-all levelness and the same fastness properties after a much shorter time of dyeing and with less fibre degradation. These results justify an interest in the method of solvent-assisted dyeing of wool.

SUMMARY

It was previously known that the addition of sparingly soluble alcohols or amines to an aqueous solution of a dye can cause an appreciable increase in the dyeing rate of wool. In this paper such an effect is referred to as "solvent-assisted" dyeing. It was the aim of this investigation to determine under what conditions an effect of solvents was obtained, in order to try the method industrially, and also to obtain some understanding of the dyeing mechanism.

A preliminary investigation showed, that the increase in dyeing rate is dependent on the degree of sulphonation of the dye. The greatest increase was obtained with an unsulphonated dye and no change in the dyeing rate was observed with a trisulphonated dye.

The dyeing rate increases with the concentration of solvent in the dye liquor, but a maximum is obtained at the saturation concentration. No change in equilibrium exhaustion of a dye was observed when butanol, or amyl alcohol, was added to an aqueous solution in a concentration lower than the saturation concentration. The equilibrium exhaustion of a dye from a solvent solution, saturated with water was, however, found to be much lower than from an aqueous solution.

The "extraction" effect of the solvent is discussed. It was found that the dyeing rate of some acid dyes was increased by pretreatment of the wool with a solvent, which was washed out again before dyeing. However, this effect was not observed with a 1:2 chrome-complex dye.

The distribution of dye between different fibres has been studied microscopically. The results indicate that, if the dyeing rate of wool is increased by a solvent, the distribution of dye will be more uniform between different fibres and different parts of the same fibre.

In addition to this preliminary investigation, more extensive experimental work was carried out on factors of importance to the dyeing mechanism.

The adsorption of alcohols on wool from aqueous solution was measured quantitatively. A special apparatus was designed for this purpose and by means of this it was possible to determine the adsorption of alcohols and dyes on wool in the same experiment. By using a monomolecular dye, it was shown that the uptake of dye on wool after a fixed time is a rectilinear function of the adsorbed amount of benzyl alcohol. The same rectilinear function is valid also for the uptake of dye as a function of the adsorbed amount of some aliphatic alcohols at low adsorption values.

Adsorption isotherms were determined for some aliphatic alcohols, and showed an increase in adsorption with decreasing solubility of the alcohol in water.

The influence of benzyl alcohol on the dyeing rate of an indicator dye, bromphenol blue, was determined at pH 1.2 (acid modification of dye) and at pH 7.8 (basic modification of dye). This alcohol increased the dyeing rate at pH 1.2 but had no effect at pH 7.8. The same amount of alcohol was adsorbed on the wool in both cases. It was shown, however, that the solubility of the acid form in benzyl alcohol is much greater than that of the basic one. By using an amine as solvent, in which the basic form has high solubility, a great increase in the dyeing rate was obtained.

The influence of the surface properties of wool on solvent-assisted dyeings have been investigated. For this purpose, wool was chlorinated to different degrees and dyed with bromphenol blue at pH 1.2 using benzyl alcohol to increase the dyeing rate, and at pH 7.8 using hexylamine for the same purpose. The dyeing rate was described in terms of diffusion coefficients, calculated according to Olofsson's method. It was found that solvents cause a smaller increase in the

dyeing rate of chlorinated wool than of untreated wool, but there is still a large effect with completely descaled wool.

It has been shown that the stress-relaxation properties of wool fibres in aqueous solution are unchanged by the addition of butanol or amyl alcohol to the dyebath.

Compared with that in water, a small increase in the swelling of wool fibres by benzyl alcohol and hexylamine has been observed.

The mechanism of solvent-assisted dyeing of wool is discussed on the basis of the experimental results obtained.

It was concluded that the solvent acts on the fibre and not on the dye in the dyebath.

The solvent layer theory is treated both as an equilibrium problem and as a kinetic one. It is shown, that this theory cannot explain the observed increase in the dyeing rate.

The experimental results do not contradict the theory of loosening of the fibre structure, which several workers believe to be the main mechanism for carrier-dyeing of hydrophobic fibres. However, this is considered to be of less importance for hydrophilic fibres, and this theory alone cannot account for all experimental data.

A new theory, which assumes a supplementing of normal diffusion in the fibre by diffusion in the adsorbed solvent, or possibly by an increase in the "free" concentration of solute in the fibre, is discussed.

The more uniform dye distribution obtained with solvent-assisted dyeing is considered in relation to the surface properties of wool.

Industrial dyeings on loose wool have been carried out using butanol or amyl alcohol as additions to the dyebath. Two different methods

were used; dyeing at 70° C for normal dyeing times, or dyeing at 95° C for very short times. The latter process gave the best result. In both cases, a greater proportion of the fibres were found to be penetrated by the dye than after conventional dyeing. The same fastness properties of the dyeings were obtained with and without solvent in the dyebath. There is, however, less-fibre degradation during a solvent-assisted dyeing.

ACKNOWLEDGEMENTS

The author wishes to thank Dr Joel Lindberg for many interesting and stimulating discussions and advice on surface treatment, Dr Bertil Olofsson for valuable collaboration in diffusion problems, and Dr Martin Sandelius for advice regarding statistical questions.

Mr John Holmström helped to design the apparatus. The experimental work was skilfully carried out by Mrs Gunvor Svensson and Miss Ann-Marie Andersson, and the microscopy by Mr Rolf Nilsson. The drawings were made by Miss Inga-Lisa Carlström. Miss Linéa Björnsson took great care in typing the manuscript. The English text was revised by Dr Arthur J. Farnworth. To all these persons, I wish to express my appreciation and thanks.

The industrial experiments were carried out at Aktiebolaget Förenade Yllefabrikerna, Norrköping, and the stimulating co-operation with their technical staff is gratefully acknowledged.

I am also much indebted to the head of the institute, Professor Nils Gralén, for his great interest in this investigation.

This work was partly financed by a grant from the International Wool Secretariat, to whom grateful acknowledgement is made.

BIBLIOGRAPHY

The following abbreviations are used:

American Association of Textile Chemists and Colorists	AATCC
American Dyestuff Reporter	Am.Dyestuff Rep.
International Federation of Associations of Textile Chemists and Colourists	IFATCC
Journal of the Textile Institute	J.Text.Inst.
Journal of the Society of Dyers and Colourists	J.Soc.Dyers Col.
Philosophical Magazine and Journal of Science	Phil.Mag.
Meddelanden från Svenska Textilforskningsinstitutet	Medd.Sv.Textilforskn.inst.
Proceedings of International Wool Textile Research Conference	Proc.Int.Wool Text.Res.Conf
Textile Research Journal	Text.Res.J.

- AATCC, Delaware Valley Section - Carrier-assisted Dyeing of Hydrophilic Fibers. Am.Dyestuff Rep. 47 (1958), p. P789.
- AATCC, Piedmont Section - Accelerant Dyeing of Hydrophobic Fibers - Principles and Mechanisms. Am.Dyestuff Rep. 48:22 (1959), p. 23.
- Atkinson, J.C., Filson, A. and Speakman, J.B. - Action of Mixed Solvents on Wool. Nature 184 (1959), p. 444.
- Baritt, J. and Elsworth, F.F. - The Dyeing Properties of Chlorinated Wool. J.Soc.Dyers Col. 64 (1948), p. 19.
- Crank, J. - The Mathematics of Diffusion. Oxford 1956.
- Choquette, R.P. - Progress in the Dyeing of the Newer Synthetic Fibers. Text.Res.J. 24 (1954), p. 387.
- Delmenico, J. - Melange or Vigoreux Printing of Wool: A Method for Increasing the Rate of Dye Fixation. Text.Res.J. 27 (1957), p. 899.
- Fortess, F. and Salvin, V.S. - Factors Influencing the Dyeing of Acetate Fibers with Disperse Nonionic Dyes. Text.Res.J. 28 (1958), p. 1009.
- Garrett, D.A. and Peters, R.H. - Effect of Penetration on Reflectance of Dyed Textile Fibres. J.Text.Inst. 47 (1956), p. T166.

- Gokhale, M.K., Peters, L. and Stevens, C.B. - Dyeing Hydrophobic Fibres in Solutions of Solvents. *J.Soc.Dyers Col.* 74 (1958), p. 236.
- Gonsalves, V.E. - Determination of Denier and Strength of Single Filaments by Vibroscope and Heim Tensile Tester. *Text. Res.J.* 17 (1947), p. 369.
- Katz, S.M. and Tobolsky, A.V. - The Relaxation of Stress in Wool Fibers. *Text.Res.J.* 20 (1950), p. 87.
- Kolthoff, I.M. and Rosenblum, C. - Acid-Base Indicators. New York 1937.
- Kramer, B. - Über die Vorgänge beim Färben vollsynthetischer Fasern mit Dispersionsfarbstoffen. *Reyon Zellwolle* 10 (1955), p. 682.
- Kärrholm, E.M. and Lindberg, J. - The Effect of Solvents on Wool Dyeing. *Text.Res.J.* 26 (1956), p. 528.
- Kärrholm, E.M. - Teknisk färgning av ull i närvaro av butanol och amlalkohol. *Medd.Sv. Textilforskn.inst.* (1956), nr 11.
- Kärrholm, E.M. - Teknisk färgning av lösull i närvaro av butanol och amlalkohol. *Textil och Konfektion* (1958), nr 6, p. 22.
- Lindberg, J. and Gralén, N. - *Medd.Sv.Textilforskn.inst.* (1949), nr 10.
- Lindberg, J. - Relationship Between Various Surface Properties of Wool Fibers. Part III: Sorption of Dyes and Acids in Wool Fibers. *Text.Res.J.* 23 (1953), p. 573.
- Luck, W.J. - The Mode of Action of Non-Ionic Levelling Agents. *J.Soc.Dyers Col.* 74 (1958), p. 221.
- Medley, J.A. and Andrews, M.W. - The Effect of a Surface Barrier on Uptake Rates of Dye into Wool Fibers. *Text.Res.J.* 29 (1959), p. 398.
- Millson, H.E. and Turl, L.H. - Studies on Wool Dyeing: The Influence of the Cuticle in the Dyeing of the Wool Fiber. *Am.Dyestuff Rep.* 39 (1950), p. P647.
- Millson, H.E. - The Microdyeoscope, Microscopical Observations on Dyeing. *Am.Dyestuff Rep.* 44 (1955), p. P417.
- Olofsson, B. - A Method of Calculating Diffusion in Fibres Coupled with Irreversible Adsorption or Rapid Reaction. *J.Text. Inst.* 47 (1956), p. T464.
- Peters, L. and Stevens, C.B. - A New Approach to Dyeing. *Dyer* 115 (1956), p. 327.
- Reid, V.W. and Truelove, R.K. - The Colorimetric Determination of Alcohols. *Analyst* 77 (1952), p. 325.
- Rochas, P. and Courmont, M. - The Mechanism of the Action of "Carriers" in the Dyeing of Polyester Fibres with Disperse Dyes. Developments in Dyeing, Printing and Finishing. IFATCC-Congress, London 1959.

- Schetty, G. - The Irgalan Dyes - Neutral-dyeing Metal-Complex Dyes. J.Soc.Dyers Col. 71 (1955), p. 705.
- Schuyten, H.A., Weaver, J.W. and Reid, J.D. - An Index of the Water-Repellency of Textiles from the Surface Tension of Aqueous Solutions. Am.Dyestuff Rep. 38 (1949), p. 364.
- Standing, H.A., Warwicker, J.O. and Willis, H.F. - The Diffusion of Direct Dyes in Cellulose. J.Text.Inst. 38 (1947), P. T335.
- Stevens, C.B. and Peters, L. - The Effect of Organic Solvents on the Absorption of Dyes by wool from Aqueous Solutions at Low Temperatures. J.Soc.Dyers Col. 72 (1956), p. 100.
- Speakman, J.B. and Shah, S.Y. - The Plasticity of Animal Fibres. J.Soc.Dyers Col. 57 (1941), p. 108.
- Vickerstaff, Th. - The Physical Chemistry of Dyeing. London 1954.
- Wikström, L., Sörvik, E., Cednäs, M. and Olofsson, B. - Chemical Modifications of the Surface Layer of Wool and Their Effect on Wettability and Sorption Properties. Proc.Int. Wool Text.Res.Conf., Australia, 1955, C 257.
- Wilson, A.H. - A Diffusion Problem in which the Amount of Diffusing Substance is Finite. Part I. Phil.Mag. 32 (1948), p. 48.
- Zimmerman, C.L., Mecco, J.M. and Carlino, A.J. - A Study of Carriers in Dyeing Dacron Polyester Fiber. Am.Dyestuff Rep. 44 (1955), p. P296.

B.P. Patent Specification 546915 (1941). - Process for Imparting to Wool a Gloss similar to that of Natural Silk.

The calculations of confidence limits and confidence intervals have been made according to conventional statistical methods, see for example:

Davies, O.L. - Statistical Methods in Research and Production With Special Reference to the Chemical Industry, 3rd. ed., London 1957.

The Swedish standard methods for testing textiles referred to in this paper are obtainable from

Sveriges standardiseringskommission, Box 3295, Stockholm 3.

CHALMERS BIBLIOTEK

1203515846

A. RYDBERG & Co. GÖTEBORG

1960