CHALMERS
UNIVERSITY OF TECHNOLOGY

Crystal electric field splitting and f -electron hybridization in heavy-fermion CePt₂In₇

Downloaded from: <https://research.chalmers.se>, 2023-04-26 10:14 UTC

Citation for the original published paper (version of record):

Duan, Y., Zhang, C., Rusz, J. et al (2019). Crystal electric field splitting and f -electron hybridization in heavy-fermion CePt₂In₇. Physical Review B, 100(8).
<http://dx.doi.org/10.1103/PhysRevB.100.085141>

N.B. When citing this work, cite the original published paper.

Crystal electric field splitting and f -electron hybridization in heavy-fermion CePt_2In_7

Yu-Xia Duan,¹ Cheng Zhang,¹ Ján Rusz,² Peter M. Oppeneer,² Tomasz Durakiewicz,³ Yasmine Sassa,^{2,4} Oscar Tjernberg,⁵ Martin Månsson,⁵ Magnus H. Berntsen,⁵ Fan-Ying Wu,¹ Yin-Zou Zhao,¹ Jiao-Jiao Song,¹ Qi-Yi Wu,¹ Yang Luo,¹ Eric D. Bauer,⁶ Joe D. Thompson,⁶ and Jian-Qiao Meng^{1,7,*}

¹*School of Physics and Electronics, Central South University, Changsha 410083, Hunan, People's Republic of China*

²*Department of Physics and Astronomy, Uppsala University, Box 516, S-75120 Uppsala, Sweden*

³*Institute of Physics, Maria Curie Skłodowska University, 20-031 Lublin, Poland*

⁴*Department of Physics, Chalmers University of Technology, 41296 Göteborg, Sweden*

⁵*Department of Applied Physics, KTH Royal Institute of Technology, Electrum 229, SE-16440, Stockholm, Kista, Sweden*

⁶*Condensed Matter and Magnet Science Group, Los Alamos National Laboratory, Los Alamos, New Mexico 87545, USA*

⁷*Synergetic Innovation Center for Quantum Effects and Applications (SICQEA), Hunan Normal University, Changsha 410081, People's Republic of China*

(Received 22 March 2019; revised manuscript received 7 August 2019; published 26 August 2019)

We use high-resolution angle-resolved photoemission spectroscopy to investigate the electronic structure of the antiferromagnetic heavy fermion compound CePt_2In_7 , which is a member of the CeIn_3 -derived heavy fermion material family. Weak hybridization among $4f$ electron states and conduction bands was identified in CePt_2In_7 at low temperature much weaker than that in the other heavy fermion compounds like CeIrIn_5 and CeRhIn_5 . The Ce $4f$ spectrum shows fine structures near the Fermi energy, reflecting the crystal electric field splitting of the $4f_{5/2}^1$ and $4f_{7/2}^1$ states. Also, we find that the Fermi surface has a strongly three-dimensional topology, in agreement with density-functional theory calculations.

DOI: [10.1103/PhysRevB.100.085141](https://doi.org/10.1103/PhysRevB.100.085141)

I. INTRODUCTION

The physics underlying the formation of superconductivity from a coherent heavy fermion (HF) state has persisted as a central mystery despite more than four decades of intensive experimental and theoretical study [1,2]. HF superconductivity, similar to traditional Bardeen-Cooper-Schrieffer (BCS) superconductivity, is more likely to occur in compounds with particular crystal structures [3,4], and for magnetically mediated superconductivity, quasi-two-dimensional (2D) compounds are likely to have a higher transition temperature than a three-dimensional counterpart [5]. This expectation appears to be borne out in a family of tetragonal HF compounds $\text{Ce}_m\text{M}_n\text{In}_{3m+2n}$ ($M = \text{Co}, \text{Rh}, \text{and Ir}$) in which the quasi-2D members with $m = 1$, $n = 1$ have T_c 's [6] up to an order of magnitude higher than the maximum pressure-induced T_c of 0.25 K found in cubic building block CeIn_3 [7]. Recent polarized soft x-ray absorption and nonresonant inelastic x-ray scattering experiments find that, in addition to the crystal structure, details of anisotropic hybridization of f and itinerant electrons play a nontrivial role in determining the ground state of the $m = 1$, $n = 1$ family members [8,9]. Understanding how superconductivity originates from a strongly correlated ground state which must be associated with structure, dimensionality, and orbital anisotropy requires detailed high-resolution techniques that allow studying quantitatively a system's electronic structure.

Low-dimensional Ce-based systems hold a promise for the successful angle-resolved photoemission spectroscopy

(ARPES) exploration of the HF electronic structure with high momentum and energy resolution. Most prior ARPES investigations of Ce-based HFs have been done on 3D systems but significant k_z broadening [10–14] limits the intrinsic accuracy of 3D band measurement. Low photon energies produce high-energy and in-plane momentum resolutions; however, the $4f$ signal is quite low and sits atop a relatively large background. The part of the reciprocal-space spectrum where the nearly flat $4f$ bands, split by spin-orbit interaction, intersect with conduction bands is the site of interest for detailed inquiry. A Ce-based HF system, as close to 2D as possible, is needed to extract this information and that would provide a level of detail comparable to what is provided by ARPES measurements on the cuprate high-temperature superconductors.

The HF compound, CePt_2In_7 , is an antiferromagnetic superconductor identified in 2008 [15]. It belongs to the $\text{Ce}_m\text{M}_n\text{In}_{3m+2n}$ ($m = 1$, $n = 2$) family. CePt_2In_7 bulk superconductivity can be induced by applying pressure, reaching a maximum of $T_c = 2.1$ K near 3.5 GPa [16]. Compared to other family members, such as CeIn_3 and CeMIn_5 , the distance between adjacent CeIn_3 blocks in CePt_2In_7 increases greatly and the f/spd hybridization decreases [16,17], making it toward the 2D limit in CeIn_3 -derived HF material family [18,19]. The crystal structure of CePt_2In_7 , however, is body-centered tetragonal ($I4/mmm$) in contrast to the primitive tetragonal structure ($P4/mmm$) adopted by the $m = 1$, $n = 1$ family members [20]. Though the separation between CeIn_3 units is greater in CePt_2In_7 , promoting a more 2D-like band character, the insertion of a PtIn_2 layer between CeIn_3 units modifies the f/d hybridization pathway and produces a notable 3D character that is absent in the simpler $m = 1$, $n = 1$ members [19–21].

*Corresponding author: jqmeng@csu.edu.cn

Quantum oscillation [19] and earlier ARPES measurements at fixed low-energy ($h\nu = 21.2$ eV) [21] are consistent with a complex Fermi-surface (FS) topology composed of sheets with both 2D and 3D character and with relatively weak many-body renormalization effects implied from optical spectroscopy [22]. Commensurate [23] or coexistence of commensurate and incommensurate [24,25] antiferromagnetism orders were revealed by nuclear quadrupolar resonance as well as muon spin rotation/relaxation [26]. None of these earlier experiments, however, directly probed the $4f$ electron states that are essential to the physics of this family of materials. Definitely, it is of great importance to address the nature of $4f$ states and f/d hybridization via on-resonance ARPES. Recent DFT/GGA calculations, which are in good agreement with ARPES measurements, suggest that the FSs near the $M(A)$ (zone corner) show a nearly 2D nature and FSs at other momenta show a strong 3D nature [21]. The k_z dispersion must be considered when analyzing and interpreting ARPES data. Here we report APRES at variable photon energies, which allows us to probe both the $4f$ states as well as the rest of the electronic structure of CePt_2In_7 at various k_z .

From these ARPES measurements on high-quality single crystals CePt_2In_7 [27] and employing Ce $4d$ - $4f$ on-resonance spectroscopy, we have identified fine structures of spin-orbit splitting and crystal electric field (CEF) splitting of Ce $4f$ bands. Furthermore, we have determined the k_z -dependent band structures at various photon energies. We find that the experimental FS topology and band structures are in good agreement with our DFT calculations.

II. EXPERIMENTAL DETAILS

The high-resolution ARPES experiments were performed on SIS X09LA beamline at the Swiss light Source, using a VG-SCIENIA R4000 photoelectron spectrometer. All samples were cleaved *in situ* and measured in an ultrahigh vacuum with a base pressure better than 4×10^{-11} mbar. The Ce $4f$ state characteristics were obtained by on-resonance spectra ($h\nu = 123$ eV) at a low temperature of 10 K. A variety of photon energies were used to investigate the 3D nature of the electron bands. An angular resolution of 0.2° was used for all measurements. High-quality single CePt_2In_7 crystals were grown from In flux [27].

III. RESULTS AND DISCUSSIONS

Tuning the photon energies toward 123 eV, a strengthening of Ce $4f$ spectral weight near the Fermi energy is expected. Figure 1(a) shows the on-resonance ($4d \rightarrow 4f$) spectra taken from a freshly cleaved, single CePt_2In_7 crystal as measured along the high-symmetry [110] direction at a temperature of 10 K with a total energy resolution ~ 30 meV. The energy distribution curve (EDC) integrated over a momentum range along the measured cut appears in Fig. 1(b). A high-intensity, nondispersive structure at around -2.5 eV corresponds to the f^0 final state [12–14,28–30]. Weak heavy quasiparticle bands close to E_F correspond to the f^1 final state. These low-energy peaks originate from the spin-orbit splitting of the f^1 final state [12–14,28–31]. The $f_{5/2}^1$ final state is located near E_F . The $f_{7/2}^1$ final-state peak is located at about -300 meV. The Ce

FIG. 1. (a) CePt_2In_7 on-resonance valence band structure at 10 K and 123 eV. (b) Angle-integrated photoemission spectroscopy of the intensity plot in (a). Inset: A 3D Brillouin zone with high-symmetry momentum points (red dots) marked. The locations of Γ , M , N , and X points are at the $k_z = 0$ plane while the Z , A , and R points are at $k_z = 2\pi/c$ plane. (c) Calculated Ce $4f$, Pt $5d$, and In $4p$ density of state (DOS) vs energy E .

$4f$ on-resonance spectrum, even at these intensities enhanced via $4d \rightarrow 4f$ resonance, shows only limited spectral weight in the vicinity of Fermi energy.

Our DFT calculations [32,33] suggest that most $4f$ states are located about 0.5 eV above E_F , see Fig. 1(c). Only a very small fraction appears below E_F , which would explain why the intensity of f^1 state in CePt_2In_7 is so low compared to the U-based heavy fermions with different f occupations [10,34]. The EDC shows a structure similar to the $4d \rightarrow 4f$ resonant photoemission spectra of the HF materials CeRhIn_5 [12,14] and CeIrIn_5 [12,13,29]. These spectral features observed in CeIrIn_5 compounds were previously understood within a single-impurity Anderson model (SIAM) framework [35], suggesting that the $4f$ electrons are nearly localized [12] or dominated by the localized character with a small itinerant component [13]. While recent temperature dependence of f spectral weight studies found a stronger cf electron hybridization in CeIrIn_5 [29].

According to SIAM, the f^1 peak intensity increases as hybridization strength increases between f electrons and conduction electrons. Our ARPES measurements here reveal that the f^1 to f^0 intensity ratio is smaller for CePt_2In_7 than for either CeIrIn_5 or CeRhIn_5 [12]. This suggests that hybridization between $4f$ electrons and conduction electrons in CePt_2In_7 is significantly weaker than in CeIrIn_5 and CeRhIn_5 . This is consistent with prior results [22] and is in line with expectations [16,17]. Attempts to perform DFT calculations in $4f^1$ localized configuration failed to stabilize such state, providing further support to observed reduced $4f^1$ peak intensity.

We carried out higher-energy resolution ARPES measurements along the [110] direction at an overall energy resolution better than 20 meV in order to study CePt_2In_7 $4f$ state-related low-energy band structures. As expected, the $f_{5/2}^1$ and $f_{7/2}^1$ states become clearer in Fig. 2(a), and their fine structures can be found if look closely. Also, it can be found that the spectral intensities of both the $f_{5/2}^1$ and $f_{7/2}^1$ states show strong momentum dependence. Figure 2(b) shows the band structures reduced with the second derivative to enhance the weak bands while maintaining band dispersion. Four flat bands can be seen in the figure, which means that both the $f_{5/2}^1$ and $f_{7/2}^1$

FIG. 2. CEF splitting of CePt_2In_7 4f states. (a) High-energy resolution of on-resonance valence band structure plot along [110] direction near Fermi energy is taken at 10 K with 123 eV. (b) Measured structure reduced with the 2D second derivative to enhance the weak bands while maintaining band dispersion. (c) EDCs of the spectral show in (a). The purple and aqua shadows are indicated the positions of the $f_{5/2}^1$ and $f_{7/2}^1$ states, respectively. The red curve represents the EDC at the M point. (d) EDCs at different momentum locations in (a). The brown, cyan, black, red, and green curves are obtained by integrating the regions between two brown, cyan, black, red, and green dashed lines, as indicated in (a), respectively.

states have undergone CEF splitting. Figure 2(c) shows the EDCs corresponding to Fig. 2(a). The lower $f_{7/2}^1$ final state splits into two peaks. They are located at about -325 and -270 meV. The upper $f_{5/2}^1$ final-state fine structures were resolved and constitute two peaks: one at around -75 meV, the other at -15 meV. The weak, but observable, -75 meV feature can be seen more clearly in Fig. 2(d), as indicated by a red arrow. Recently, $4f_{7/2}^1$ and $f_{5/2}^1$ peak splitting has been detected by ARPES [28,29] along with inelastic neutron scattering [36–38] in other Ce-based HF compounds.

In the HF system, due to the hybridization between the conduction band and the Ce 4f state, it is expected that a dispersive quasiparticle band can be observed near E_F at a position where the f band intersects the conduction band. Figure 2(d) display the integrated EDCs at different momentum locations in Fig. 2(a), including crossing high-intensity f band regions where the conduction bands cross the Fermi level and adjacent low-intensity regions where no conduction bands cross the Fermi level. From the top and middle sets of EDCs in Fig. 2(d), we can find that the peak positions of EDCs near the E_F that cross two different regions have shifted a little. The observation of weak dispersive f band and locally enhanced f band intensity imply the possible hybridization between f

band and conduction band. Hybridization occurs at where the conduction band crosses or approaches the Fermi level (brown and red lines), whereas no band hybridization is observed in other regions (cyan, green, and black lines). This indicates that dispersive and hybridized 4f electron densities contribute to bonding and FS formation. This has been suggested, too, by quantum oscillation measurements [19]. The hybridization between $f_{5/2}^1$ electron and conduction bands also has been reported in other Ce-based heavy fermions [13,14,29–31,39]. As shown in Fig. 2(d), the energy dispersion of the hybridized band is about 5 meV, which is much smaller than that of other HF compounds. The energy dispersion of the hybridized quasiparticle bands is more than 10 meV for CeIrIn_5 [13] and CeCoIn_5 [31]. According to the periodic Anderson model, the stronger the hybridization between the f electrons and the conduction electrons, the larger the energy dispersion of the hybridized quasiparticle band. Again, this means the hybridization between f bands and conduction bands in CePt_2In_7 is weak compared to CeIrIn_5 and CeCoIn_5 . Comparison of theoretical band structures and Fermi surface contours for CePt_2In_7 and LaPt_2In_7 also support this point (see Fig. S1 of the Supplemental Material [40] for more details).

Figure 3(a) shows high-resolution FS mapping of CePt_2In_7 measured at 10 K using a constant photon energy of 100 eV. This corresponds to a cut close to the Γ point ($k_z \sim 0.2 \times 2\pi/c$), estimated based on an inner potential of 11 eV [40]. FS contours are drawn with false colors. To compare to DFT calculations, the calculated FS contours were overlaid on top of the experimental FS. Here the FS contour at $k_z = 0$ is selected to capture features around X point, because the end of the final-state arc of 100 eV has already touched the X point. Multiple FS sheets were revealed in the momentum space covered. Three electron pockets can be found around the zone corners, and a small hole pocket can be found located around the X point, agrees well with the band structure predictions. Figures 3(b1) and 3(c1) show the detailed band structures along the two high-symmetry directions as indicated by dashed yellow and dashed green arrows in Fig. 3(a).

The EDC bands [Figs. 3(b2) and 3(c2)] and momentum distribution curve (MDC) bands [Figs. 3(b3) and 3(c3)] were extracted by taking the second derivatives of the original ARPES data [shown in Figs. 3(b1) and 3(c1)] with respect to energy and momentum, respectively. Possible band dispersions become thereby easier to distinguish. Our calculated band structures (red-dashed lines) were overlaid onto the EDC band [Figs. 3(b2) and 3(c2)]. It can be found that the measured and computed band structure are in good agreement, especially along the $N'-X'-N'$ direction. Along the $N'-X'-N'$ direction, where the FSs are nearly 2D [Fig. 4(d)] (see Fig. S2 of the Supplemental Material for more details [40]), experimental data and calculated results are highly consistent [Fig. 3(b2)]. While along the $X'-\Gamma'-X'$ direction, where the FSs show strong 3D nature [Fig. 4(d)], the experimental results are more complex than theoretical calculations (red dashed lines) [Fig. 3(c2)]. It has been pointed out that there is a very significant k_z broadening in Ce-based HF materials [14]. As we know, the k_z broadening has a great influence on the 3D FS but little influence on the 2D FS. Dispersions along $R'-Z'-R'$ direction (green dashed lines, $k_z = 2\pi/c$) were also overlaid on top of Fig. 3(c2). It can be found that some of the

FIG. 3. FS and corresponding CePt₂In₇ band structure. (a) Symmetrized FS in the k_x - k_y plane of CePt₂In₇ measured at 10 K with 100 eV (close to Γ point). The intensity is integrated over $[-10$ meV, 10 meV] energy window with respect to the Fermi level E_F . [(b1)–(b3)] Measured band structures along the N' - X' - N' direction, indicated by the dashed yellow arrow in (a). [(c1)–(c3)] Measured band structure along X' - Γ - X' direction, indicated by the dashed green arrow in (a). (b1) and (c1) are the original data. (b2) and (c2) are second-derivative images from the original data with respect to energy. [(b3) and (c3)] Second-derivative images from the original data with respect to momentum. Red dashed lines in (b2) and (c2) represent DFT band structure. Green dashed lines represent DFT band structure along R - Z - R line.

other dispersions are consistent with the dispersion from R - Z - R . All these results strongly suggest that the k_z broadening should carefully be taken into account when discussing the origin of photon energy-dependent spectral features.

Figure 4 shows ARPES spectra measured at 10 K along the N' - X' - N' and X' - Γ - X' directions. The energy resolutions were set at 22 and 15 meV for 80- and 34-eV photon energies, respectively. Figures 4(a1) and 4(a2) show original and EDC

band structure taken along the N' - X' - N' direction with 80-eV photon energy, respectively. Obviously, at the zone boundary, although the measured k_z positions are different, the band structures for 80 and 100 eV [Fig. 3(b1)] are very similar, four bands crossing or approaching the Fermi level. Figures 4(b1) and 4(c1) show original band structure measurements taken along X' - Γ - X' direction with 80- and 34-eV photon energies, respectively. Figure 4(b2) and 4(c2) are EDC bands from the

FIG. 4. Band structure of CePt₂In₇ at 10 K. [(a1) and (a2)] Original photoemission image and corresponding EDC second derivative image measured along the N' - X' - N' direction with 80-eV photon energy. [(b1) and (c1)] Photonemission data taken along X' - Γ - X' direction with 80- and 34-eV photon energies, respectively. [(b2) and (c2)] Corresponding EDC second derivative images of (b1) and (c1), respectively. Red dashed lines in (a2), (b2), and (c2) represent DFT band structure. (d) Calculated FS of CePt₂In₇. The 3D FS is presented in the body-centered tetragonal Brillouin zone, in which one unit cell contains one Ce atom. (e) DFT-calculated Fermi surface contours in the Γ - X - R - Z plane (k_x - k_z). The colors used for different Fermi surfaces are consistent with (d). The red, green, and brown arcs indicate the final-state arcs for 100-, 80-, and 34-eV photon energies, respectively.

original data. The band structures show significant photon-energy $h\nu$ dependence, which indicates a very strong k_z dispersion. Thus, our ARPES measurements are consistent with a strong 3D FS topology, in good agreement with the DFT calculation [Fig. 4(d)]. And in the Supplemental Material [40], we display the detailed calculated FS contours of CePt₂In₇ at different k_z s. Similarly to earlier results from another research group [21], our experimental and theoretical results show that the FSs near the $M(A)$ (zone corner) show a good 2D nature and FSs at other momenta show a significant 3D nature.

IV. CONCLUSIONS

In conclusion, CePt₂In₇ FS topology and low-energy band structures were investigated at 10 K using high-resolution ARPES. We directly observed heavy $4f$ -derived quasiparticle bands via on-resonance ARPES. Our study show that the hybridization between $4f$ electrons and conduction bands are weak, and the hybridized $4f$ electrons contribute to bonding and FS formation. The CEF splitting of $4f_{5/2}^1$ and $4f_{7/2}^1$ states was directly observed via on-resonant measurements. We also confirm that the FS has a strong 3D topology, well supported by DFT calculations. These findings provide key insight into understanding the electronic structure of an unconventional superconducting Ce-based HF.

ACKNOWLEDGMENTS

We acknowledge helpful discussions with Prof. Jian-Xin Zhu. This work was supported by the National Natural Science Foundation of China (Grant No. 11574402), ZDXKFZ (Grant No. XKFZ201703), and the Innovation-driven Plan in Central South University (Grant No. 2016CXS032). J.R. and P.M.O. acknowledge support through the Swedish Research Council (VR) and the Swedish National Infrastructure for Computing (SNIC) for computing time on computer cluster Triolith at the NSC center Linköping. Y.S. acknowledges the support from the Swedish Research Council (VR) through a Starting Grant (Dnr. 2017-05078). O.T. acknowledges support from the Swedish Research Council (VR) and the Knut and Alice Wallenberg foundation. M.M. is partly supported by a Marie Skłodowska-Curie Action International Career Grant through the European Commission and Swedish Research Council (VR), Grant No. INCA-2014-6426, as well as a VR neutron project grant (BIFROST, Dnr. 2016-06955). Further support was also granted by the Carl Tryggers Foundation for Scientific Research (Grants No. CTS-16:324 and No. CTS-17:325). Work at Los Alamos was performed under the auspices of the U.S. Department of Energy, Office of Basic Energy Sciences, Division of Materials Sciences and Engineering.

-
- [1] C. Pfleiderer, *Rev. Mod. Phys.* **81**, 1551 (2009).
 - [2] L. Taillefer, *Nat. Phys.* **9**, 458 (2013).
 - [3] R. H. Heffner and M. R. Norman, *Comments Condens. Matter Phys.* **17**, 361 (1996).
 - [4] C. Petrovic, P. G. Pagliuso, M. F. Hundley, R. Movshovich, J. L. Sarrao, J. D. Thompson, Z. Fisk, and P. Monthoux, *J. Phys.: Condens. Matter* **13**, L337 (2001).
 - [5] P. Monthoux and G. G. Lonzarich, *Phys. Rev. B* **63**, 054529 (2001).
 - [6] J. D. Thompson, R. Movshovich, Z. Fisk, F. Bouquet, N. J. Curro, R. A. Fisher, P. C. Hammel, H. Hegger, M. F. Hundley, M. Jaime, P. G. Pagliuso, C. Petrovic, N. E. Phillips, and J. L. Sarrao, *J. Magn. Magn. Mater.* **226-230**, 5 (2001).
 - [7] I. R. Walker, F. M. Grosche, D. M. Freye, and G. G. Lonzarich, *Physica C* **282-287**, 303 (1997).
 - [8] T. Willers, F. Strigari, Zhiwei Hu, V. Sessi, N. B. Brookes, E. D. Bauer, J. L. Sarrao, J. D. Thompson, A. Tanaka, S. Wirth, L. H. Tjeng, and A. Severing, *Proc. Natl. Acad. Sci. USA* **112**, 2384 (2015).
 - [9] M. Sundermann, A. Amorese, F. Strigari, M. W. Haverkort, L. H. Tjeng, M. Moretti Sala, H. Yavaş, E. D. Bauer, P. F. S. Rosa, J. D. Thompson, and A. Severing, *Phys. Rev. B* **99**, 235143 (2019).
 - [10] J. D. Denlinger, G.-H. Gweon, J. W. Allen, C. G. Olson, M. B. Maple, J. L. Sarrao, P. E. Armstrong, Z. Fisk, and H. Yamagami, *J. Electron Spectrosc. Relat. Phenom.* **117-118**, 347 (2001).
 - [11] R. Jiang, D. Mou, C. Liu, X. Zhao, Y. Yao, H. Ryu, C. Petrovic, K.-M. Ho, and A. Kaminski, *Phys. Rev. B* **91**, 165101 (2015).
 - [12] S. I. Fujimori, T. Okane, J. Okamoto, K. Mamiya, Y. Muramatsu, A. Fujimori, T. Narimura, K. Kobayashi, K. Shimada, H. Namatame, M. Taniguchi, H. Harima, D. Aoki, S. Ikeda, H. Shishido, Y. Tokiwa, Y. Haga, and Y. Onuki, *Physica B* **329-333**, 547 (2003).
 - [13] S. I. Fujimori, A. Fujimori, K. Shimada, T. Narimura, K. Kobayashi, H. Namatame, M. Taniguchi, H. Harima, H. Shishido, S. Ikeda, D. Aoki, Y. Tokiwa, Y. Haga, and Y. Onuki, *Phys. Rev. B* **73**, 224517 (2006).
 - [14] Q. Y. Chen, D. F. Xu, X. H. Niu, R. Peng, H. C. Xu, C. H. P. Wen, X. Liu, L. Shu, S. Y. Tan, X. C. Lai, Y. J. Zhang, H. Lee, V. N. Strocov, F. Bisti, P. Dudin, J. X. Zhu, H. Q. Yuan, S. Kirchner, and D. L. Feng, *Phys. Rev. Lett.* **120**, 066403 (2018).
 - [15] Zh. M. Kurenbaeva, E. V. Murashova, Y. D. Seropegin, H. Noel, and A. I. Tursina, *Intermetallics* **16**, 979 (2008).
 - [16] E. D. Bauer, H. O. Lee, V. A. Sidorov, N. Kurita, K. Gofryk, J. X. Zhu, F. Ronning, R. Movshovich, J. D. Thompson, and T. Park, *Phys. Rev. B* **81**, 180507(R) (2010).
 - [17] V. A. Sidorov, X. Lu, T. Park, Hanoh Lee, P. H. Tobash, R. E. Baumbach, F. Ronning, E. D. Bauer, and J. D. Thompson, *Phys. Rev. B* **88**, 020503(R) (2013).
 - [18] E. D. Bauer, V. A. Sidorov, H. Lee, N. Kurita, F. Ronning, R. Movshovich, and J. D. Thompson, *J. Phys.: Conf. Ser.* **200**, 012011 (2010).
 - [19] M. M. Altarawneh, N. Harrison, R. D. McDonald, F. F. Balakirev, C. H. Mielke, P. H. Tobash, J. X. Zhu, J. D. Thompson, F. Ronning, and E. D. Bauer, *Phys. Rev. B* **83**, 081103(R) (2011).
 - [20] T. Klimczuk, O. Walter, L. Muehler, J. W. Krizan, F. Kinnart, and R. J. Cava, *J. Phys.: Condens. Matter* **26**, 402201 (2014).
 - [21] B. Shen, L. Yu, K. Liu, S. Lyu, X. Jia, E. D. Bauer, J. D. Thompson, Y. Zhang, C. Wang, C. Hu, Y. Ding, X. Sun, Y. Hu, J. Liu, Q. Gao, L. Zhao, G. Liu, Z. Xu, C. Chen, Z. Lu, and X. J. Zhou, *Chin. Phys. B* **26**, 077401 (2017).

- [22] R. Y. Chen, S. J. Zhang, E. D. Bauer, J. D. Thompson, and N. L. Wang, *Phys. Rev. B* **94**, 035161 (2016).
- [23] N. apRoberts-Warren, A. P. Dioguardi, A. C. Shockley, C. H. Lin, J. Crocker, P. Klavins, and N. J. Curro, *Phys. Rev. B* **81**, 180403(R) (2010).
- [24] H. Sakai, Y. Tokunaga, S. Kambe, H.-O. Lee, V. A. Sidorov, P. H. Tobash, F. Ronning, E. D. Bauer, and J. D. Thompson, *Phys. Rev. B* **83**, 140408(R) (2011).
- [25] H. Sakai, Y. Tokunaga, S. Kambe, H. Lee, V. A. Sidorov, P. H. Tobash, F. Ronning, E. D. Bauer, and J. D. Thompson, *J. Phys.: Conf. Ser.* **391**, 012057 (2012).
- [26] M. Månsson, K. Prša, Y. Sassa, P. H. Tobash, E. D. Bauer, C. Rusu, D. Andreica, O. Tjernberg, K. Sedlak, M. Grioni, T. Durakiewicz, and J. Sugiyama, *J. Phys.: Conf. Ser.* **551**, 012028 (2014).
- [27] P. H. Tobash, F. Ronning, J. D. Thompson, B. L. Scott, P. J. W. Moll, B. Batlogg, and E. D. Bauer, *J. Phys.: Condens. Matter* **24**, 015601 (2012).
- [28] S. Patil, A. Generalov, M. Güttler, P. Kushwaha, A. Chikina, K. Kummer, T. C. Rödel, A. F. Santander-Syro, N. Caroca-Canales, C. Geibel, S. Danzenbächer, Yu. Kucherenko, C. Laubschat, J. W. Allen, and D. V. Vyalikh, *Nat. Commun.* **7**, 11029 (2016).
- [29] Q. Y. Chen, C. H. P. Wen, Q. Yao, K. Huang, Z. F. Ding, L. Shu, X. H. Niu, Y. Zhang, X. C. Lai, Y. B. Huang, G. B. Zhang, S. Kirchner, and D. L. Feng, *Phys. Rev. B* **97**, 075149 (2018).
- [30] Y. Zhang, W. Feng, X. Lou, T. Yu, X. Zhu, S. Tan, B. Yuan, Y. Liu, H. Lu, D. Xie, Q. Liu, W. Zhang, X. Luo, Y. Huang, L. Luo, Z. Zhang, X. Lai, and Q. Chen, *Phys. Rev. B* **97**, 045128 (2018).
- [31] Q. Y. Chen, D. F. Xu, X. H. Niu, J. Jiang, R. Peng, H. C. Xu, C. H. P. Wen, Z. F. Ding, K. Huang, L. Shu, Y. J. Zhang, H. Lee, V. N. Strocov, M. Shi, F. Bisti, T. Schmitt, Y. B. Huang, P. Dudin, X. C. Lai, S. Kirchner, H. Q. Yuan, and D. L. Feng, *Phys. Rev. B* **96**, 045107 (2017).
- [32] P. Blaha, G. Madsen, K. Schwarz, D. Kvasnicka, and J. Luitz, *WIEN2K, An Augmented Plane Wave + Local Orbitals Program for Calculating Crystal Properties* (Vienna University of Technology, Vienna, 2001).
- [33] DFT calculations were performed in nonmagnetic state using GGA exchange correlation functional including spin-orbital coupling effects in second variational treatment. $RK_{\max} = 7.5$ led to approximately 1000 basis functions. Brillouin zone integration was performed with modified tetrahedron method using 1000 k points.
- [34] J.-Q. Meng, P. M. Oppeneer, J. A. Mydosh, P. S. Riseborough, K. Gofryk, J. J. Joyce, E. D. Bauer, Y. Li and T. Durakiewicz, *Phys. Rev. Lett.* **111**, 127002 (2013).
- [35] O. Gunnarsson and K. Schönhammer, *Phys. Rev. B* **28**, 4315 (1983).
- [36] A. D. Christianson, J. M. Lawrence, P. S. Riseborough, N. O. Moreno, P. G. Pagliuso, E. D. Bauer, J. L. Sarrao, W. Bao, E. A. Goremychkin, S. Kerm, F. R. Trouw, and M. P. Hehlen, *J. Neutron Res.* **13**, 179 (2005).
- [37] T. Willers, Z. Hu, N. Hollmann, P. O. Körner, J. Gegner, T. Burnus, H. Fujiwara, A. Tanaka, D. Schmitz, H. H. Hsieh, H. J. Lin, C. T. Chen, E. D. Bauer, J. L. Sarrao, E. Goremychkin, M. Koza, L. H. Tjeng, and A. Severing, *Phys. Rev. B* **81**, 195114 (2010).
- [38] A. D. Christianson, E. D. Bauer, J. M. Lawrence, P. S. Riseborough, N. O. Moreno, P. G. Pagliuso, J. L. Sarrao, J. D. Thompson, E. A. Goremychkin, F. R. Trouw, M. P. Hehlen, and R. J. McQueeney, *Phys. Rev. B* **70**, 134505 (2004).
- [39] S. I. Fujimori, *J. Phys.: Condens. Matter* **28**, 153002 (2016).
- [40] See Supplemental Material at <http://link.aps.org/supplemental/10.1103/PhysRevB.100.085141> for crystal electric field splitting and f -electron hybridization in heavy fermion CePt₂In₇, which includes Refs. [41–45].
- [41] S.-i. Fujimori, M. Kobata, Y. Takeda, T. Okane, Y. Saitoh, A. Fujimori, H. Yamagami, Y. Matsumoto, E. Yamamoto, N. Tateiwa, and Y. Haga, *Phys. Rev. B* **96**, 125117 (2017).
- [42] V. N. Strocov, *J. Electron Spectrosc. Relat. Phenom.* **130**, 65 (2003).
- [43] H. Wadati, T. Yoshida, A. Chikamatsu, H. Kumigashira, M. Oshima, H. Eisaki, Z.-X. Shen, T. Mizokawa, and A. Fujimori, *Phase Trans.* **79**, 617 (2006).
- [44] X.-F. Tang, Y.-X. Duan, F.-Y. Wu, S.-Y. Liu, C. Zhang, Y.-Z. Zhao, J.-J. Song, Y. Luo, Q.-Y. Wu, J. He, H. Y. Liu, W. Xu, and J.-Q. Meng, *Phys. Rev. B* **99**, 125112 (2019).
- [45] D. Ehm, F. Reinert, G. Nicolay, S. Schmidt, S. Hufner, R. Claessen, V. Eyert, and C. Geibel, *Phys. Rev. B* **64**, 235104 (2001).