

Quantum bath suppression in a superconducting circuit by immersion cooling

Downloaded from: https://research.chalmers.se, 2024-04-27 05:37 UTC

Citation for the original published paper (version of record):

Lucas, M., Danilov, A., Levitin, L. et al (2023). Quantum bath suppression in a superconducting circuit by immersion cooling. Nature Communications, 14(1). http://dx.doi.org/10.1038/s41467-023-39249-z

N.B. When citing this work, cite the original published paper.

research.chalmers.se offers the possibility of retrieving research publications produced at Chalmers University of Technology. It covers all kind of research output: articles, dissertations, conference papers, reports etc. since 2004. research.chalmers.se is administrated and maintained by Chalmers Library

Article

Quantum bath suppression in a superconducting circuit by immersion cooling

Received: 13 January 2023

Accepted: 2 June 2023

Published online: 14 June 2023

Check for updates

M. Lucas \mathbb{O}^1 , A. V. Danilov², L. V. Levitin \mathbb{O}^1 , A. Jayaraman \mathbb{O}^2 , A. J. Casey \mathbb{O}^1 , L. Faoro³, A. Ya. Tzalenchuk $\mathbb{O}^{1,4}$, S. E. Kubatkin², J. Saunders¹ & S. E. de Graaf $\mathbb{O}^4 \boxtimes$

Quantum circuits interact with the environment via several temperaturedependent degrees of freedom. Multiple experiments to-date have shown that most properties of superconducting devices appear to plateau out at $T \approx 50$ mK - far above the refrigerator base temperature. This is for example reflected in the thermal state population of qubits, in excess numbers of quasiparticles, and polarisation of surface spins - factors contributing to reduced coherence. We demonstrate how to remove this thermal constraint by operating a circuit immersed in liquid ³He. This allows to efficiently cool the decohering environment of a superconducting resonator, and we see a continuous change in measured physical quantities down to previously unexplored sub-mK temperatures. The ³He acts as a heat sink which increases the energy relaxation rate of the quantum bath coupled to the circuit a thousand times, yet the suppressed bath does not introduce additional circuit losses or noise. Such quantum bath suppression can reduce decoherence in quantum circuits and opens a route for both thermal and coherence management in quantum processors.

Thermal management is a central problem in computer engineering. This is true for classical processors, where the inability to remove heat from transistors resulted in a stalled clock frequency for the last 20 years¹, and this is also true for superconducting quantum processors where various temperature-dependent factors limit their coherence. Scaling up quantum processors² inevitably exacerbates this problem and minimising the impact from all decoherence mechanisms at play is essential for achieving fault-tolerant quantum computing^{3,4}.

Cooling of devices operated in cryogenic vacuum represents a significant challenge because all solid-state cooling pathways—through quasiparticles in the superconducting material and phonons both there and in the substrate—become inefficient. A large body of experimental data indicates physical observables becoming temperature-independent below ~50 mK, well above the dilution

refrigerator base temperature of -10 mK. This is consistently seen in qubit state population⁵⁻⁸, qubit coherence times⁹, frequency flicker noise^{10,11}, surface electron spin polarisation¹², and qubit flux noise¹³. Improvement may be achieved by reducing the heat load from various external sources, such as ionising radiation^{3,14}, cosmic particles^{15,16}, and high-frequency photons^{17–19}, by careful shielding and filtering. This approach has had a lot of success over the years and is still a subject of intense research and technical development. However, further progress cannot be achieved without taking due care of the circuit's material environment, for which, unexpectedly, further cooling can lead to increased noise and decoherence.

Although naively one would think that cooling a superconducting circuit to the lowest possible temperature would freeze out any noisy environment, this is only partly true. To suppress decoherence

¹Physics Department, Royal Holloway University of London, Egham, UK. ²Department of Microtechnology and Nanoscience MC2, Chalmers University of Technology, SE-412 96 Göteborg, Sweden. ³Google Quantum AI, Google Research, Mountain View, CA, USA. ⁴National Physical Laboratory, Teddington TW11 OLW, UK. ¹Ce-mail: sdg@npl.co.uk

originating from equilibrium quasiparticles¹⁷ or residual thermal qubit excitations⁵⁻⁸ the temperature shall be significantly below relevant energy scales, i.e. $T \ll 300$ mK for a device operating at 6 GHz. However, well below these temperatures other decoherence mechanisms, in particular that associated with the dielectric environment of the devices, come into play. Dielectrics contain defects, which act as two-level systems (TLS) and counter-intuitively, noise due to TLS increases upon cooling^{10,20}.

Here we present a radically different route to approach these challenges by immersion cooling of a superconducting circuit in liquid ³He. The Fermi liquid ³He has a thermal conductivity that increases with decreasing temperature, and its cooling to below 1 mK is well established²¹. Thermalisation of liquid ³He to the immersion cell's metal body is ensured by silver heat exchangers, where the thermal boundary resistance is known to be significantly smaller than the prediction of acoustic mis-match theory. By contrast, liquid ⁴He is superfluid in this temperature regime and is an excitation vacuum with poor thermal conductivity and relatively high boundary resistance.

We show that ³He provides an efficient heat sink for the circuit environment and dramatically increases the energy relaxation rate of the TLS bath, while otherwise appearing essentially inert to the quantum circuit itself. ³He immersion thus opens up multiple ways in which significant improvement in circuit coherence may be achieved, both by cooling and by suppressing coherence in the noisy environment. Future optimisation of such quantum bath suppression using ³He may lead to significantly reduced noise also at dilution refrigerator base temperatures.

Experimentally, our approach is to use planar superconducting resonators, which have emerged as a convenient platform to interrogate the decohering environment^{10,12,22-27}. In particular, the amplitude of the low-frequency 1/*f* fluctuations in resonator center frequency (1/*f* frequency noise) is very sensitive to the TLS temperature²⁰. Additionally, the temperature of the surrounding spin bath reveals itself in the electron spin resonance (ESR) spectrum measured via field-dependent losses of the same resonators. When the resonator is immersed in ³He, we observe improved thermalisation of the TLS in the noise measurements and of the spin bath in the ESR measurements, as illustrated in Fig. 1.

Results and discussion

Derived from recent advances in ultra-low temperature technology and the cooling of electronic systems to sub-mK temperatures^{28,29} we construct an immersion cell suitable for a superconducting quantum circuit. Cooling is achieved by placing the circuit, in our case an NbN superconducting resonator³⁰ on a sapphire substrate, inside the immersion cell, as shown in Fig. 1d. The superfluid leak-tight copper cell with RF feed-throughs and extensive RF filtering provides a wellcontrolled microwave environment. It is thermally anchored to the experimental plate of an adiabatic nuclear demagnetisation refrigeration (ANDR) stage attached via a superconducting heat switch to the lowest temperature plate (10 mK) of a dry dilution refrigerator³¹. The experimental plate of the ANDR (located in the field-compensated region of the ANDR superconducting magnet) can reach temperatures of $\approx 400 \,\mu\text{K}$, as measured using SQUID noise thermometry³¹. The cell can be filled with ³He via a thin capillary. To ensure good thermalisation of the liquid ³He to the cell's metal enclosure silver sinter heat exchangers are implemented (see Supplementary Note 1 for further details). For ESR spectroscopy experiments a magnetic field (B) up to 0.5 T parallel to the sample surface could be applied. We refer to the section "Methods" for details on our measurement techniques.

Reliable thermometry is an essential prerequisite for the interpretation of ultra-low temperature data. On-chip ESR not only reveals the presence of unwanted surface spins coupling to the resonator through their magnetic moments (a source of flux noise^{13,32}) but also serves as an intrinsic thermometer in the relevant temperature range.

To this end, we show in Fig. 2 that, unlike previous experiments on spins coupled to quantum circuits where the spin polarisation was saturated at about $T = 50 \text{ mK}^{12}$, surface spins are cooled to much lower temperatures in the presence of ³He, with no other apparent change in the ESR spectra. The measured ESR spectrum is rather complex, consisting of many different species, and has been discussed in detail previously^{12,33}. Here we focus on the species that are most suitable for intrinsic thermometry at these low temperatures, namely the two peaks labeled 1 and 3 that arise from atomic hydrogen¹². The hyperfine interaction in the hydrogen atom results in two electronic spin transitions separated in energy by 1.42 GHz (=68 mK), with a relative intensity that follows the Boltzmann distribution. Thus if spins are cooled to zero temperature the transition involving the higher energy





containing the sample is thermally anchored to an adiabatic nuclear demagnetisation stage that reaches $T = 400 \,\mu$ K. The nuclear stage is mounted to the mixing chamber plate of a dry dilution refrigerator. **e** Energy relaxation pathway from the TLS bath to the cold plate via ³He and silver sinter. The link between TLS medium and liquid ³He is the bottleneck for further quantum bath suppression.



Fig. 2 | **Cooling of surface electron spins.** Continuous wave electron spin resonance spectra of surface spin intrinsic to a 5.85 GHz resonator, measured with an average number of photons circulating in the resonator of $\langle N \rangle \approx 200$. Q_B^{-1} is the change in inverse quality factor (loss) measured in a magnetic field, with zero field losses subtracted. Inset: Normalised intensity of the hyperfine-split atomic hydrogen peaks (labeled 1 and 3) versus nuclear stage noise thermometer temperature. Empty symbols represent measurement in a vacuum and filled symbols in ³He. Error bars are propagated errors from fitting the peak intensities. Solid lines are the expected peak intensities based on the thermal population of ESR levels hyperfine-split by A = 1.42 GHz. The dashed line is an estimate of the minimum sensitivity of our technique, below which we could not detect the third peak. This sets an upper bound on the temperature of the H spins of around 15 mK.

level transition (peak 3) will vanish, the trend clearly seen in Fig. 2 in the presence of ³He. See also Fig. S15 for further ESR results demonstrating cooling by a thin ³He film. Having established improved thermalisation of surface spins we now turn to the TLS bath that couples through charge dipoles to the same circuit.

Figure 3a compares the temperature dependence of the 1/f frequency noise of a 6.45 GHz resonator with vacuum or ³He in the sample cell (for more data on different devices, see Supplementary Note 4). Similar to many previous experiments^{10,11,34–36}, in vacuum the noise increases on cooling according to a power law $T^{-1.5}$ followed by saturation to a constant level below ~80 mK due to insufficient thermalisation.

When the cell is filled with ³He the situation is very different. The noise changes with fridge temperature all the way down to 1 mK. Above 100 mK the magnitude and temperature dependence of the noise is the same in vacuum and in ³He, but below a certain crossover temperature $T_x \sim 80$ mK the noise instead starts to decrease with reduced temperature according to a power law $T^{0.25}$. Remarkably, ³He immersion appears to break the predicted²⁰ trend of increasing noise with cooling (otherwise expected to persist to well below 10 µK, see below). The noise measured at 1 mK is more than three orders of magnitude below this expected $T^{-1.5}$ trend.

A further striking effect of immersing the circuit in ³He is revealed in the dependence of the internal quality factor Q_i of the resonators on the microwave power (photon number, $\langle N \rangle$), presented in Fig. 4a for three temperatures. Noticeably, ³He does not affect Q_i at the single photon level, meaning that the number of TLS present and their coupling to the resonator remains unchanged. Both for resonators in vacuum and in ³He the microwave excitation power increases Q_i -a well-known effect of TLS saturation-but for resonators immersed in ³He the same Q_i is achieved with -1000 times higher power; i.e. we find a dramatic increase in the characteristic TLS saturation power by three orders of magnitude. Figure 4b showing the Q_i extracted at a fixed d-



Fig. 3 | Cooling the TLS bath by immersion into ³He reduces noise. a The magnitude of the 1/*f* frequency noise power spectral density $S_y(f)$ of a $v_0 = 6.45$ GHz superconducting resonator evaluated at f = 0.1 Hz versus nuclear stage temperature for two selected microwave drive powers (average photon number $\langle N \rangle$) with the cell full of ³He (filled markers) and empty cell (empty markers). The latter has been scaled by a factor 20 for better visualisation (see Supplementary Note 4 for an unscaled version). Each dataset is a single temperature ramp taking ≈ 6 days. Solid and dashed slopes show T^{β} in the low and high-temperature regimes respectively, with $\beta = 0.25$ and -1.5, respectively. Horizontal dashed line is a guide for the eye. The shaded region indicates the high-temperature regime where the noise is

expected to deviate from the indicated scaling law. For more details on the noise around the ³He superfluid transition temperature (-0.9 mK) (see Supplementary Note 4F). **b** Photon number dependence of the noise with ³He at selected temperatures taken across shorter timescales (5 h per temperature). Solid lines are fits to the expected dependence of the noise ($\propto (1 + \langle N \rangle / N_c)^{-1/2}$) where the weak fields regime with a leveling-off to a constant noise versus $\langle N \rangle$ is evident at high temperatures. Full noise spectra across all timescales can be found in Supplementary Note 4. For a description of error bars, we refer to Supplementary Note 3. Error bars in temperature indicate the whole range of temperature drift during data collection.

r-



Fig. 4 | ³**He increases TLS relaxation. a** Comparison of the TLS-limited internal quality factor Q_i for a 6.26 GHz resonator with and without ³He in the cell, for three temperatures. ³He increases the power needed to saturate to a given Q_i by a factor -1000. **b** The change in internal Q vs. temperature for a fixed drive power of $\langle N \rangle - 10^4$. **c** Extracted critical photon number N_c times a prefactor c, from fitting the

 $Q_t(N)$ data to $1/Q_i \propto (cN_c/\langle N \rangle)$. Solid line shows $T^{1.25}$, the expected scaling of Γ_2 . Error bars for all panels are 95% confidence bounds from fits to experimental data, and error bars in temperature indicate the whole range of temperature drift during data collection.

ive power in the saturated regime indicates that there is a weak but steady dependence (and hence cooling) down to < 1 mK. Furthermore, we also here observe a crossover occurring around $T_x \sim 80$ mK.

A notorious challenge in noise measurements (and more generally in operating quantum circuits requiring long-term stability^{2,37-39}) is the inherent instabilities of TLS energies on longer timescales (spectral drift). This is particularly evident in the low power data in Fig. 3a. To circumvent this problem, we measure noise at a somewhat higher photon number which saturates the most strongly coupled fluctuators⁴⁰. Yet, we stay in a moderately weak fields regime²⁰, as evidenced by the power dependence of the noise shown in Fig. 3b. In the low power data in Fig. 3a the measured noise level varies on top of the general trend by a factor of 2–3 during the course of the measurement, which takes -6 days; however, the overall trend remains unchanged.

To understand the full body of experimental data we first focus on the region 100–250 mK where the noise is well understood. Here the noise is increasing upon cooling both in a vacuum and in ³He, consistent with previous observations and fully captured by the generalised tunneling model (GTM)²⁰ for interacting TLS defects.

In the GTM both energy loss and 1/f noise arise from the resonator coupling to a large number of coherent (near-)resonant TLS defects. These TLS drain energy from the resonator and dissipate it to substrate phonons, a process that determines Q_i , a measure of the average energy loss into the whole TLS bath. They also, through their coherent coupling, mediate frequency fluctuations from the environment: the resonant coherent TLS are subjected to thermally activated spectral diffusion due to the interaction with a bath of incoherent, low energy $(E \ll k_{\rm B}T)$ TLS ("thermal two-level fluctuators", TLF) that incoherently flip-flop between two states, giving rise to both noise and the coherent TLS width Γ_2 . Strongly coupled TLS contribute more strongly to the noise and they are also more easily saturated by microwave fields. In the weak microwave field regime (small $\langle N \rangle$) the magnitude of the noise is governed by the TLS dephasing rate $\Gamma_2 \propto T^{1+\mu}$ arising from the coupling to the TLF bath (and independent of the TLS relaxation rate Γ_1), which yields a temperature dependence $S_v \propto T^{-1-2\mu 11,20}$ (for $k_{\rm B}T < hv_0$). Here μ is a small positive number characterising the density of states of TLS arising from their interactions. From the data in Fig. 3, we find $\mu = 0.25$, consistent with previous experiments^{10,11,34}. Since the magnitude and the temperature dependence of the noise are the same in vacuum and in ³He above 100 mK we conclude that ³He does not influence Γ_2 .

This leads to the remarkable conclusion that the enormous change in saturation power observed, Fig. 4a, reflects a ³He increase in the average TLS relaxation rate $\Gamma_1 \sim 1000$ times,

Nature Communications | (2023)14:3522

because the critical number of photons for saturation of the TLS bath scales as $N_c \propto \Gamma_1 \Gamma_2$.

We now turn to the low-temperatures regime, below $T_x \sim 80$ mK. First, we consider the implications of a significantly increased Γ_1 of the TLS bath. In dielectrics, the TLS excitation and relaxation occur via interaction with phonons which couple via strain field. The relaxation rate can be expressed using the Golden rule formula as $\Gamma_1^{ph} = (M^2 \Delta_0^2 E)/(2\pi \rho h^4 v^5) \times \operatorname{coth} \frac{E}{2k_B T}^{41}$, where *M* is the deformation potential, Δ_0 is the TLS tunnelling matrix element, *E* is the TLS energy, ρ is the density and *v* is the speed of sound of the material. For a resonator in a vacuum, the dissipation is through the emission of phonons into the dielectrics hosting the TLS, and at the relevant temperatures, this process is temperature independent with a rate that can be estimated to $\Gamma_1^{ph} \approx 10^2 - 10^3 \text{ Hz}^{20}$. This is much smaller than the TLS dephasing rate due to interactions Γ_2 : Previous estimates^{11,34} yielded $\Gamma_2 \approx 10^6$ –10⁷ Hz at T = 50–100 mK in similar devices.

Assuming the $\Gamma_2 \propto T^{1+\mu}$ dependence persists to lower temperatures means that in vacuum we would reach the regime of relaxation limited dephasing, $\Gamma_2 \simeq 2\Gamma_1$, of the TLS bath below 10 µK, which is experimentally inaccessible. ³He immersion increases the average Γ_1 to ~ $10^5 - 10^6$ Hz, which shifts this crossover temperature to 10-100 mK. This agrees with the observed $T_x \sim 80 \text{ mK}$ in the noise and in the dependence of the quality factor on power $Q(\langle N \rangle)$. Furthermore, within the GTM $1/Q_i \propto (cN_c/\langle N \rangle)^{42}$, where c is a constant. The $Q(\langle N \rangle)$ data fits remarkably well to this logarithmic power dependence (see Supplementary Note 5). In Fig. 4c we show that the temperature dependence of cN_c follows the predicted $N_c \propto \Gamma_1 \Gamma_2(T) \sim T^{1+\mu}$ scaling at high temperatures. However, below T_x , this trend changes abruptly and becomes temperature independent. In the relaxation-limited regime, the noise is not expected to increase upon cooling, yet a temperature dependence may be inherited from mechanisms contributing to Γ_1 , such as the ³He-TLS interaction. ³He immersion thus prevents the TLS noise from rising more than three orders of magnitude upon cooling to 1 mK.

A second scenario that in addition may account for the apparent reduction in the noise is TLS saturation. Such a situation could arise because the measurement is conducted at a fixed driving power. As Γ_2 (and hence N_c) reduces on cooling the applied power more easily saturates the TLS because they become more coherent^{20,43}. The GTM predicts a universal $T^{(1-\mu)/2} = T^{0.375}$ scaling of the noise in this regime, and power broadening would also result in the observed crossover in N_c from $T^{1+\mu}$ to constant in temperature⁴² (Fig. 4c) as for the relaxation limited scenario. Because we have significantly increased the average

https://doi.org/10.1038/s41467-023-39249-z

 Γ_1 of TLS in the bath, one would think that this scenario is of less relevance in ³He. Indeed, another important observation is that for saturation in the regime $\Gamma_1 \ll \Gamma_2$ the crossover temperature T_x should depend on driving power, contrary to our data.

Yet, in any practical device the spatial variations in electric fields, the distribution of TLS parameters, and the fact that not all TLS are located in proximity to the exposed surface where they can couple to ³He means there still will exist TLS that are not suppressed by ³He and are therefore easily saturated. This prompts device improvements where surfaces and edges with strong electric fields should be placed in proximity to ³He.

As a first step to understand the ³He–TLS interaction, we note the long-standing problem of the thermal boundary resistance between solids and helium liquids, where the details of the interface, such as surface roughness⁴⁴ and the nature of the surface boundary layer, including the presence of 1-2 atomic layers of solid helium at the interface due to van der Waals attraction^{45,46}, play a key role⁴⁷. Perhaps more closely related to this work are earlier acoustic and thermal measurements on strongly disordered⁴⁸ and porous^{49,50} materials immersed in helium that also found evidence of faster TLS relaxation. It has been suggested⁵¹ that one mechanism by which phonons in helium couple to TLS is via van der Waals interaction. The upper bound for the relevant deformation potential in ⁴He was deduced to be $M \lesssim 2 \text{ meV}^{48}$ compared to $\approx 1 \text{ eV}$ for phonons in a solid. Using these numbers we can attempt to roughly estimate the enhanced TLS relaxation rate in ³He, compared to the sapphire substrate. For sapphire we use $\rho = 4 \times 10^3$ kg/m³, $\nu = 1 \times 10^4$ m/s, M = 1 eV. Similar values are also expected for TLS in the NbN surface oxide. For ³He we use $\rho = 60 \text{ kg/m}^3$, $\nu = 200 \text{ m/s}$ and $M = 1 \text{ meV}^{50}$. This yields $\Gamma_1^{3\text{He}} / \Gamma_1^{\text{sap}} \approx 10^4 - 10^{10} \text{ meV}^{10}$ an order of magnitude larger than experimentally observed. This is not very surprising given the crudeness of the estimates and the fact that we measure the average for the whole TLS bath. Moreover, we note that below ~100 mK the propagating acoustic modes in ³He are that of zero sound⁵². Zero sound modes and the nuclear magnetism⁵³⁻⁵⁵ of ³He offer various interaction mechanisms with relevant degrees of freedom and a much richer spectrum of low energy excitations than in ⁴He⁵⁶. To the best of our knowledge, the TLS-³He coupling has not been studied in detail before, and at low temperatures, other types of interactions may become as important as phonons, such as direct interaction between surface TLS and quasiparticles in ³He^{51,57}.

Understanding the mechanism at play is crucial for future improvements, and two further experiments (details in Supplementary Note 4D and E) suggest that phonon relaxation into ³He following the Golden rule alone does not capture the full picture. (i) Measurements with only a thin (-4 nm) film of ³He covering the sample allow us to separate the two roles played by ³He, namely to enhance TLS relaxation and to mediate cooling. For a thin ³He film we still observe the big change in saturation power (³He–TLS interaction) but a plateaued noise as in a vacuum, indicating poor thermalisation. (ii) Increasing the pressure of the ³He to 5 bar, whereupon both ρ and v increase by -30% compared to saturated vapour pressure⁵⁶, should result in an almost five-fold reduction of Γ_1 . Contrary, we observed a very moderate increase in saturation power (<20%).

Finally, we turn to the dielectric properties of ³He to understand its compatibility with state-of-the-art qubit circuits. The resonator frequency shift due to filling the cell agrees with the ³He dielectric constant ε_r =1.0426⁵⁸ within 1 part in 1000 (see Supplementary Note 4). Liquid ⁴He has a low-temperature dielectric loss tangent tan $\delta < 5 \times 10^{-6}$ at 9 GHz⁵⁹. Similar values are expected for ³He, however, to the best of our knowledge this value has not been reported at GHz frequencies. From the change in single-photon Q_i at 10 mK as the cell is filled with ³He we estimate an upper bound for the loss tangent of tan $\delta \ll 1.5 \times 10^{-5}$ at 5.8 GHz, comparable to the best substrate dielectrics used. Likely tan δ is much lower as significant TLS-induced parameter drift occurs between measurements, the main source of error in our estimate. The bound on the loss tangent translates to a limit for qubit coherence times of $T_1 \gg 110 \,\mu\text{s}$ for a 6 GHz qubit, i.e. ³He is compatible with state-of-the-art quantum circuits. The potential impact of the nuclear magnetism of the solid ³He surface boundary layer on a qubit is an open question, addressable by its elimination through ⁴He plating^{53,60}. Our immersion cell is compatible with quantum processor enclosure design principles and can straightforwardly be scaled to cells having large numbers of microwave ports.

In conclusion, we have shown that ³He is an efficient, low-loss cooling medium for quantum circuits and can cool down environmental degrees of freedom of the circuit: namely surface spins and the TLS bath. We also discovered the crucial role of ³He in suppressing the coherence of the TLS bath while otherwise being essentially inert to the circuit itself. Understanding the details of the mechanisms at play will require further theoretical and experimental work. The rich phase diagram of ³He provides an exciting playground for bath engineering of quantum circuits, with multiple in situ tuning parameters to unpick the underlying physical mechanisms. ³He immersion thus opens up a new avenue for exploring the origins of decoherence in quantum circuits and a promising pathway to further suppressing it, and our results show that ³He immersion cooling can be beneficial even at standard dilution refrigerator temperatures of 10 mK.

Methods

Experimental platform

To access temperatures below -10 mK we mount the cell at the experimental plate of an adiabatic nuclear demagnetisation refrigeration stage fitted inside a dry dilution refrigerator. This allows to cool the experimental plate to \approx 400 µK. Cooling to this temperature introduces a number of engineering challenges around our microwave readout setup, thermometry, and suppression of heat leaks from higher temperature stages in the cryostat. Here we summarise our solutions to these challenges and refer to Supplementary Note 1 for further details.

The circuit's enclosure is well thermalised to the experimental plate of the ANDR via clean high conductivity copper links. The copper parts were not annealed to limit the eddy-current heating during ESR field sweeps. Compared to a typical vacuum enclosure with a well-controlled RF environment our immersion cell has several additional features: The cell is made completely leak-tight (superfluid tight) by the use of hermetic RF feed-throughs and indium seals. The cell is similar to that implemented in ref. 29 developed for low-temperature low-frequency transport measurements on quantum materials and devices, and the two cells share many features. As in ref. 29 the capillary connecting the cell to the ³He gas handling system was interrupted with a silver sinter filter. To thermalise the ³He liquid to the enclosure (and the ANDR experimental plate temperature) part of the cell's internal volume is filled with silver sinter. Combined, these measures allow us to fill the cell with ³He and thermalise it to the experimental plate of the fridge. The experimental setup is carefully designed and screened such that at full field (6 T) the demagnetisation magnet only induces ~2 mT in plane stray field on the sample (deduced from ESR measurements). All measurements presented here were performed with the nuclear stage demagnetised to 35 mT, corresponding to 13 µT field at the sample. For details on the microwave setup and heat loads, we refer to Supplementary Note 1.

Thermometry

The temperature of the immersion cell (or any of its components) was not measured directly, but instead was deduced from a SQUID-read current sensing noise thermometer (CSNT) anchored to the ANDR experimental plate (details in Supplementary Note 1). CSNT allows us to accurately measure temperatures down to $100 \,\mu K^{61,62}$.

ESR measurements

We obtain the continuous wave ESR spectrum of the surface spins coupling to the resonators by measuring resonator transmission S_{21} at each magnetic field using a VNA. We fit this to $S_{21}(f) = 1 - (1 - Q/Q_i)e^{i\phi}$ $(1+2iQ\delta f)$ with $\delta f = (v_0 - f)/v_0$ to extract the resonator's center frequency v_0 , coupled (Q) and uncoupled (Q_i) quality factors, and a phase factor ϕ . From the uncoupled quality factor we then obtain the additional losses induced by spins coupling to the device as a function of the magnetic field: $Q_{\rm B}^{-1}(B) = Q_{\rm i}^{-1}(B) - Q_{\rm i}^{-1}(B = B_{\rm ref})$. Here $B_{\rm ref}$ is the field the spectra is normalised to. We take the first few data points plus the last few data points as this reference. The latter is to better align the high field tail to better facilitate the comparison of the weak third peak. For each point in the magnetic field $S_{21}(f)$ of the resonator is measured at multiple excitation powers. Each magnetic field sweep takes about 8 hours, about half of the time is slow ramping of the magnet to minimise heating from eddy currents at the lowest temperatures, and during this time the temperature may drift as the nuclear stage warms up. We record the temperature during the measurement, and quoted temperatures in the figures are those relevant at the time of measuring specific features discussed.

To extract the hydrogen peak intensities in Fig. 3 we first fit the background to two broad Gaussians plus a Gaussian for the central peak (peak 2) while excluding the regions of the spectra containing the hydrogen peaks. We subtract this fitted background from the spectra and then finally fit two Gaussians to the two remaining hydrogen peaks. The error bars reported are 95% confidence bounds to these peak fits, which are propagated in the calculation of the normalised peak intensity.

Noise measurements

To measure the intrinsic 1/f noise of the resonators we use the Poundlocking technique⁶³ to track the resonance frequency with high bandwidth. We record the gap-free time series of $v_0(t)$ with a sampling rate of 0.05 s. We then analyse this time series to extract the 1/f noise magnitude from the overlapping Allan deviation. For the temperature sweeps presented in Fig. 2a we cool down the fridge to the lowest temperature and start recording $v_0(t)$ as the fridge slowly warms up (over 6–7 days) to -300 mK. We ramp the power applied to a heater to control the warm-up rate. The full time-series $v_0(t)$ is then analysed piece-wise, in segments of 2 h, sufficient to obtain a clear 1/f noise contribution to the noise spectra. We indicate the temperature as the average temperature during this time interval, and error bars indicate the whole temperature range for the segment.

For a detailed description of the measurement technique, setup, analysis, and extended data, see Supplementary Notes 1–5.

Data availability

The data generated in this study have been deposited in the Zenodo database under accession code https://doi.org/10.5281/zenodo. 7937067.

References

- Denning, P. J. & Lewis, T. G. Exponential laws of computing growth. Commun. ACM 60, 54–65 (2016).
- Arute, F. et al. Quantum supremacy using a programmable superconducting processor. *Nature* 574, 505–510 (2019).
- Vepsäläinen, A. P. et al. Impact of ionizing radiation on superconducting qubit coherence. *Nature* 584, 551–556 (2020).
- McEwen, M. et al. Removing leakage-induced correlated errors in superconducting quantum error correction. *Nat. Commun.* 14, 1761 (2021).
- 5. Lane, J. R. et al. Integrating superfluids with superconducting qubit systems. *Phys. Rev. A* **101**, 012336 (2020).
- 6. Jin, X. Y. et al. Thermal and residual excited-state population in a 3d transmon qubit. *Phys. Rev. Lett.* **114**, 240501 (2015).

- Kulikov, A., Navarathna, R. & Fedorov, A. Measuring effective temperatures of qubits using correlations. *Phys. Rev. Lett.* **124**, 240501 (2020).
- 8. Sultanov, A., Kuzmanović, M., Lebedev, A. V. & Paraoanu, G. S. Protocol for temperature sensing using a three-level transmon circuit. *Appl. Phys. Lett.* **119**, 144002 (2021).
- 9. Paik, H. et al. Observation of high coherence in Josephson junction qubits measured in a three-dimensional circuit QED architecture. *Phys. Rev. Lett.* **107**, 240501 (2011).
- J. Burnett, J. et al. Evidence for interacting two-level systems from the 1/f noise of a superconducting resonator. *Nat. Commun.* 5, 4119 (2014).
- de Graaf, S. E. et al. Suppression of low-frequency charge noise in superconducting resonators by surface spin desorption. *Nat. Commun.* 9, 1143 (2018).
- 12. de Graaf, S. E. et al. Direct identification of dilute surface spins on Al2O3: Origin of flux noise in quantum circuits. *Phys. Rev. Lett.* **118**, 057703 (2017).
- Quintana, C. M. et al. Observation of classical-quantum crossover of 1/f flux noise and its paramagnetic temperature dependence. *Phys. Rev. Lett.* **118**, 057702 (2017).
- 14. Cardani, L. et al. Reducing the impact of radioactivity on quantum circuits in a deep-underground facility. *Nat. Commun.* **12**, 2733 (2021).
- 15. Wilen, C. D. et al. Correlated charge noise and relaxation errors in superconducting qubits. *Nature* **594**, 369–373 (2021).
- Martinis, J. M. Saving superconducting quantum processors from decay and correlated errors generated by gamma and cosmic rays. *npj Quantum Inf.* 7, 90 (2021).
- 17. Serniak, K. et al. Hot nonequilibrium quasiparticles in transmon qubits. *Phys. Rev. Lett.* **121**, 157701 (2018).
- Barends, R. et al. Minimizing quasiparticle generation from stray infrared light in superconducting quantum circuits. *Appl. Phys. Lett.* 99, 113507 (2011).
- Krinner, S. et al. Engineering cryogenic setups for 100-qubit scale superconducting circuit systems. *EPJ Quantum Technol.* 6, 2 (2019).
- 20. Faoro, L. & loffe, L. B. Interacting tunneling model for two-level systems in amorphous materials and its predictions for their dephasing and noise in superconducting microresonators. *Phys. Rev. B* **91**, 014201 (2015).
- 21. Pobell, F. Matter and Methods at Low Temperatures, Vol. 2 (Springer, 2007).
- 22. Brehm, J. D., Bilmes, A., Weiss, G., Ustinov, A. V. & Lisenfeld, J. Transmission-line resonators for the study of individual two-level tunneling systems. *Appl. Phys. Lett.* **111**, 112601 (2017).
- 23. Béjanin, J. H. et al. Fluctuation spectroscopy of two-level systems in superconducting resonators. *Phys. Rev. Appl.* **18**, 034009 (2022).
- Hung, C.-C. et al. Probing hundreds of individual quantum defects in polycrystalline and amorphous alumina. *Phys. Rev. Appl.* 17, 034025 (2022).
- 25. de Graaf, S. E., Mahashabde, S., Kubatkin, S. E., Tzalenchuk, A. Y. & Danilov, A. V. Quantifying dynamics and interactions of individual spurious low-energy fluctuators in superconducting circuits. *Phys. Rev. B* **103**, 174103 (2021).
- Kirsh, N., Svetitsky, E., Burin, A. L., Schechter, M. & Katz, N. Revealing the nonlinear response of a tunneling two-level system ensemble using coupled modes. *Phys. Rev. Mater.* 1, 012601 (2017).
- 27. de Graaf, S. E., Un, S., Shard, A. G. & Lindström, T. Chemical and structural identification of material defects in superconducting quantum circuits. *Mater. Quantum Technol.* **2**, 032001 (2022).
- Jones, A. T. et al. Progress in cooling nanoelectronic devices to ultra-low temperatures. J. Low Temp. Phys. 201, 772–802 (2020).
- 29. Levitin, L. V. et al. Cooling low-dimensional electron systems into the microkelvin regime. *Nat. Commun.* **13**, 667 (2022).

Article

- 30. Mahashabde, S. et al. Fast tunable high-q-factor superconducting microwave resonators. *Phys. Rev. Appl.* **14**, 044040 (2020).
- 31. Nyéki, J. et al. High performance cryogen-free microkelvin platform. *Phys. Rev. Appl.* **18**, L041002 (2022).
- 32. Anton, S. M. et al. Magnetic flux noise in dc squids: Temperature and geometry dependence. *Phys. Rev. Lett.* **110**, 147002 (2013).
- 33. Un, S., de Graaf, S. E., Bertet, P., Kubatkin, S. E. & Danilov, A. V. On the nature of decoherence in quantum circuits: Revealing the structural motif of the surface radicals in α -al2o3. *Sci. Adv.* **8**, eabm6169 (2022).
- Burnett, J., Faoro, L. & Lindstrom, T. Analysis of high quality superconducting resonators: consequences for tls properties in amorphous oxides. *Superconductor Sci. Technol.* 29, 044008 (2016).
- Ramanayaka, A. N., Sarabi, B. & Osborn, K. D. Evidence for universal relationship between the measured 1/f permittivity noise and loss tangent created by tunneling atoms. arxiv preprint https://doi.org/ 10.48550/arXiv.1507.06043 (2015).
- de Graaf, S. E. et al. Two-level systems in superconducting quantum devices due to trapped quasiparticles. *Sci. Adv.* 6, eabc5055 (2020).
- Klimov, P. V. et al. Fluctuations of energy-relaxation times in superconducting qubits. *Phys. Rev. Lett.* **121**, 090502 (2018).
- Burnett, J. et al. Decoherence benchmarking of superconducting qubits. npj Quantum Inf. 5, 54 (2019).
- Schlör, S. et al. Correlating decoherence in transmon qubits: low frequency noise by single fluctuators. *Phys. Rev. Lett.* **123**, 190502 (2019).
- Niepce, D., Burnett, J. J., Kudra, M., Cole, J. H. & Bylander, J. Stability of superconducting resonators: motional narrowing and the role of Landau–Zener driving of two-level defects. *Sci. Adv.* 7, abh0462 (2021).
- Phillips, W. A. Two-level states in glasses. *Rep. Prog. Phys.* 50, 1657 (1987).
- Faoro, L. & Ioffe, L. B. Internal loss of superconducting resonators induced by interacting two-level systems. *Phys. Rev. Lett.* **109**, 157005 (2012).
- Burin, A. L., Matityahu, S. & Schechter, M. Low-temperature 1/ f noise in microwave dielectric constant of amorphous dielectrics in Josephson qubits. *Phys. Rev. B* 92, 174201 (2015).
- Ramiere, A., Volz, S. & Amrit, J. Thermal resistance at a solid/ superfluid helium interface. *Nat. Mater.* 15, 512–516 (2016).
- Scholtz, J. H., McLean, E. O. & Rudnick, I. Third sound and the healing length of He ii in films as thin as 2.1 atomic layers. *Phys. Rev. Lett.* **32**, 147–151 (1974).
- Birchenko, A. P., Maidanov, V. A., Mikhin, N. P., Sokolov, S. S. & Sopelnyk, Y. Y. Observation of a solid phase under measuring the 3he diffusion coefficient in the nanopores of the mcm-41 adsorbent. *Low Temp. Phys.* 48, 589–593 (2022).
- Nakayama, T. Kapitza thermal boundary resistance and interactions of helium quasiparticles with surfaces. In Progress in Low temperature Physics Vol. XII (Elsevier Science Publishers B.V., 1989).
- Schubert, H., Leiderer, P. & Kinder, H. Saturation of the anomalous Kapitza conductance. *Phys. Rev. B* 26, 2317–2319 (1982).
- Beamish, J. R., Hikata, A. & Elbaum, C. Effects of helium on two-level systems in porous vycor glass. *Phys. Rev. Lett.* 52, 1790–1793 (1984).
- Cheng, Z. G. & Chan, M. H. W. Threefold reduction in thermal conductivity of vycor glass due to adsorption of liquid ⁴He. *New J. Phys.* **15**, 063030 (2013).
- 51. Kinder, H. Kapitza conductance of localized surface excitations. *Physica B+C* **107**, 549–550 (1981).
- Landau, L. D. The theory of a fermi liquid. Sov. Phys. JETP 3, 920 (1957).

- 53. Freeman, M. R. & Richardson, R. C. Size effects in superfluid ³He films. *Phys. Rev. B* **41**, 11011–11028 (1990).
- Avenel, O. et al. Improved thermal contact at ultralow temperatures between ³He and metals containing magnetic impurities. *Phys. Rev. Lett.* **31**, 76–79 (1973).
- Hu, Y., Stecher, G. J., Gramila, T. J. & Richardson, R. C. Magnetic coupling in thermal-boundary resistance between thin silver films and liquid ³He in the millikelvin regime. *Phys. Rev. B* 54, R9639–R9642 (1996).
- 56. Dobbs, R. Helium Three (OUP Oxford, 2001).
- Golding, B., Graebner, J. E., Kane, A. B. & Black, J. L. Relaxation of tunneling systems by conduction electrons in a metallic glass. *Phys. Rev. Lett.* 41, 1487–1491 (1978).
- Saitoh, M., Ikegami, H., Mukuda, H. & Kono, K. Measurement of superfluid 3he film flow by inter-digitated capacitors. *J. Low Temp. Phys.* **134**, 357–362 (2004).
- Smorodin, A. V., Rybalko, A. S. & Konstantinov, D. Measurements of the complex permittivity of liquid helium-4 in the millimeter wave range by a whispering gallery mode resonator. *J. Low Temp. Phys.* 187, 361–368 (2017).
- 60. Heikkinen, P. et al. Fragility of surface states in topological superfluid 3he. *Nat. Commun.* **12**, 1574 (2021).
- 61. Lusher, C. et al. Current sensing noise thermometry using a low tc dc squid preamplifier. *Meas. Sci. Technol.* **12**, 1 (2001).
- 62. Shibahara, A. et al. Primary current-sensing noise thermometry in the millikelvin regime. *Philos. Trans. R. Soc. A* **374**, 20150054 (2016).
- Lindström, T., Burnett, J., Oxborrow, M. & Tzalenchuk, A. Y. Poundlocking for characterization of superconducting microresonators. *Rev. Sci. Instrum.* 82, 104706 (2011).

Acknowledgements

We thank X. Rojas for his help with the design of the microwave setup. This work was supported by the UK government's Department for Business, Energy and Industrial Strategy through the UK national quantum technologies programme, The Swedish Research Council (VR) (grant agreements 2016-04828, 2019-05480 and 2020-04393) and Knut and Alice Wallenberg Foundation via the Wallenberg Center for Quantum Technology (WACQT). The research leading to these results has also received funding from the European Union's Horizon 2020 Research and Innovation Programme, under Grant Agreement Nos. 824109 and 766714/HiTIMe. S.D.G. acknowledges support from the Engineering and Physical Sciences Research Council (EPSRC) (Grant Number EP/W027526/1).

Author contributions

S.E.K., J.S., A.Y.T. and S.D.G. designed and planned the experiment. M.L. and L.V.L. designed the immersion cell, ESR magnet and gas handling system. A.V.D., A.J. and S.E.K. designed and made the sample. M.L. and S.D.G. conducted the measurements with support from L.V.L. and A.J.C. S.E.D.G. and M.L. analysed the data with support from A.V.D. and A.Y.T. A.V.D., A.Y.T., L.F., S.E.K., J.S. and S.E.D.G. made significant contributions towards the interpretation of the data. S.E.D.G., A.Y.T., M.L. and J.S. wrote the manuscript with inputs from all authors. All authors discussed the results and the manuscript.

Competing interests

A patent application (N39249-GB1) concerning some of the technical implementations to achieve cooling by ³He immersion has been filed by NPL Management Ltd, Royal Holloway and Bedford New College, and A.V.D. and S.E.K. There are no other competing interests.

Additional information

Supplementary information The online version contains supplementary material available at https://doi.org/10.1038/s41467-023-39249-z.

Correspondence and requests for materials should be addressed to S. E. de Graaf.

Peer review information *Nature Communications* thanks the anonymous reviewers for their contribution to the peer review of this work. A peer review file is available.

Reprints and permissions information is available at http://www.nature.com/reprints

Publisher's note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations. **Open Access** This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons license, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons license and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this license, visit http://creativecommons.org/ licenses/by/4.0/.

© The Author(s) 2023