

# Biodegradation of synthetic plastics by the extracellular lipase of Aspergillus niger

Downloaded from: https://research.chalmers.se, 2025-05-09 08:05 UTC

Citation for the original published paper (version of record): Safdar, A., Ismail, F., Imran, M. (2024). Biodegradation of synthetic plastics by the extracellular lipase of Aspergillus niger. Environmental Advances, 17. http://dx.doi.org/10.1016/j.envadv.2024.100563

N.B. When citing this work, cite the original published paper.

research.chalmers.se offers the possibility of retrieving research publications produced at Chalmers University of Technology. It covers all kind of research output: articles, dissertations, conference papers, reports etc. since 2004. research.chalmers.se is administrated and maintained by Chalmers Library





## **Environmental Advances**



journal homepage: www.sciencedirect.com/journal/environmental-advances

## Biodegradation of synthetic plastics by the extracellular lipase of *Aspergillus niger*

Ayesha Safdar<sup>a</sup>, Fatima Ismail<sup>a,\*</sup>, Muhammad Imran<sup>b,\*\*</sup>

<sup>a</sup> Department of Biochemistry, The Islamia University of Bahawalpur 63100, Punjab, Pakistan
<sup>b</sup> Chalmers University of Technology Kemigården 4, SE-412 96, Göteborg, Sweden

Keywords: Lipase Polyethylene Polyethylene terephthalate Polystyrene Biodegradation

#### ABSTRACT

A rapid increase in plastic pollution is a major threat to the environment. One intriguing group of enzymes that can act as biocatalysts for the breakdown of polymers is lipase. This study reports the production of lipase from *Aspergillus niger* MG654699.1 utilizing agro-industrial residue (wheat bran) through solid-state fermentation. The produced lipase showed 176.55 U/mL of activity, 7.18 mg/mL of protein content, and 24.60 U/mg of specific activity under the optimal conditions of 37°C and pH 7.0. The biocatalytic activity of 30 KDa lipase resulted in 3.8%, 3.6%, and 5% weight loss of PE (polyethylene), PET (polyethylene terephthalate), and PS (polystyrene), respectively. Application of Fourier transform infrared spectroscopy (FTIR) and scanning electron microscopy (SEM) confirmed the lipase-mediated deterioration of treated polymer samples. The alterations in functional groups and surface structures of the samples showed the chemical and physical impact of the applied enzyme. The findings of this study showed that lipase can be employed as an eco-friendly and green biocatalyst for effective depolymerization and deterioration of environmental plastic waste.

## 1. Introduction

Plastics are primarily the polymeric materials included in every aspect of life. In the past seventy years, it has been estimated that 8.3 billion tons of plastic have been produced (Rhodes, 2018). Plastics have been created at an increased rate since their manufacturing in order to fulfill the daily demand worldwide. According to a study carried out in 2019, it was estimated that global plastic manufacturing was around 400 million tons per year, with approximately 8 to 13 million tons discarded straight into the oceans each year (Dominik et al., 2019). Out of this, 12% of plastic is burned, 79% is dumped into landfills, and only 9% is recycled (Taghavi et al., 2021). Polyethylene (PE), polyethylene terephthalate (PET), and polystyrene (PS), with 30.3%, 8.4%, and 6.1% usage, respectively, are the most widely used polymers (Temporiti et al., 2022). The majority of existing waste management practices include recycling, burning, and dumping into landfills. Even some plastic is recycled, but a large portion still harms the environment by being burned or dumped into landfills (Safdar et al., 2024). Over the previous few years, studies have concentrated on ways to break down PET by enhancing the characteristics of enzymes that hydrolyze PET, such as lipases, esterases, and cutinases (Patel and Lee, 2022). Enzyme-mediated hydroxylation can target C-H bonds within plastics, such as those in the main chain (-CH<sub>2</sub>) and at the terminals (-CH<sub>3</sub>), including the tertiary C-H bonds within branches of carbon (Jin et al., 2023). A study (Gao and Sun, 2021) has proposed many enzymes that degrade PET and PE, such as lipases, hydrolases, esterases, and cutinases. The most researched and widely used enzyme for aminolysis, alcoholysis, transesterification, esterification, and hydroxylation processes is lipase (Otari et al., 2020).

Lipases, which are triacylglycerol acyl hydrolases (EC: 3.1.1.3), are pervasive enzymes produced naturally by a wide range of plants, insects, animals, and microbes, but fungi, yeasts, and bacteria are the major sources of lipases (Reyes-Reyes et al., 2022). Yeast and fungi are the major and economical source of lipase production (Kumar et al., 2023). The enzyme is a member of the hydrolase class, which is recognized for breaking the carbon framework of several commonly utilized polymers.

https://doi.org/10.1016/j.envadv.2024.100563

Received 12 April 2024; Received in revised form 22 June 2024; Accepted 26 June 2024 Available online 29 June 2024

2666-7657/© 2024 The Authors. Published by Elsevier Ltd. This is an open access article under the CC BY license (http://creativecommons.org/licenses/by/4.0/).

Abbreviations: PE, Polyethylene; PS, Polyetyrene; PET, Polyethylene terephthalate; A. niger, Aspergillus niger; SSF, Solid state fermentation; pNPP, p-Nitrophenyl palmitate; SDS-PAGE, Sodium dodecyl-sulfate polyacrylamide gel electrophoresis; KDa, kilodalton; SEM, Scanning Electron Microscopy; FTIR, Fourier Transform Infrared Spectroscopy.

<sup>\*</sup> Corresponding author at: Department of Biochemistry, The Islamia University of Bahawalpur 63100, Punjab, Pakistan.

<sup>\*\*</sup> Corresponding author at: Chalmers University of Technology Kemigården 4, SE-412 96, Göteborg, Sweden.

E-mail addresses: fatima.ismail@iub.edu.pk (F. Ismail), Imranmuh@chalmers.se (M. Imran).

An environmentally acceptable substitute for conventional plastic recycling methods is the use of polymer-degrading enzymes (Temporiti et al., 2022). Lipases are gaining popularity because of their numerous applications in several industries like drug, detergent, pharmaceutical, and biodiesel (Kumar et al., 2019), dairy, animal feed, agrochemicals, food and beverage, flavor industry, fine chemical manufacture, perfumery (Safdar et al., 2023), textile, leather, paper and pulp, biosensors, cosmetics, amino acid and ester derivatives, cleaning, and bioremediation (Kumar et al., 2023).

Solid-state fermentation (SSF) is an economical method for the production of industrial enzymes since it uses cheaper substrates, requires less space and energy, requires less complicated equipment, produces more enzymes per unit of time, and is simpler to process (Demir and Tari, 2016). Additionally, there is a growing tendency towards utilizing agro-industrial byproducts effectively to produce the enzyme with additional value via SSF. Particularly, lipases from microbial sources are better due to their affordability, ease of manufacture, responsiveness to express in host systems, variety of specificity, broad pH, and thermal range (Melani et al., 2020). The lipase-producing fungi commonly include A. niger, Mucor miehei, Candida cylindracea, Rhizopus arrhizus, and Humicola lanuginose (Ismail and Baek, 2020). Aspergillus, Penicillium, and Fusarium have the ability to degrade PE (Restrepo-Flórez et al., 2014), PET, and PS foam (Umamaheswari and Murali, 2013). Mishandled plastic waste has negative impacts on the surroundings, human health, and animal life. The primary objectives of the current work were to observe the ability of A. niger lipase to degrade commonly used plastics, including PE, PET, and PS. Wheat bran was used for the production of crude lipase under SSF. The molecular weight of the produced enzyme was determined by SDS-PAGE (sodium dodecyl-sulfate polyacrylamide gel electrophoresis) before its application in polymer degradation. Lipase-mediated degradation of selected polymers was analyzed by weight loss, FTIR (Fourier transform infrared spectroscopy), and SEM (scanning electron microscopy) analyses. Evaluating the use of fungal lipases for waste management will probably offer a novel and eco-friendly way to address the extensive plastic pollution detrimental to the environment and will reduce the negative consequences of plastic pollution on aquatic, animal, and human life, thereby enabling economic growth and improved living quality.

## 2. Materials and methods

#### 2.1. Strain, chemicals, and samples

All the chemicals and a previously identified strain of *A. niger* (accession number MG654699.1) were obtained from the Department of Biochemistry, The Islamia University of Bahawalpur, Pakistan (Ismail et al., 2021) and cultured on SDA (Sabouraud dextrose agar) medium. SDA plates were made with 40, 10, 20, and 0.5 g/L of dextrose, peptone, agar, and chloramphenicol, respectively. The strain was cultured on these plates and incubated in an incubator (Velp Scientifica, model FTC 90E, Usmate, Italy) at 37°C. The substrate (wheat bran) and the plastic samples, including PE, PET, and PS, were obtained locally from Bahawalpur, Pakistan. The characteristics of selected samples are explained in Table 1. The primary sources of polymers included the polyethylene shopping bag, the polyethylene terephthalate water bottle, and the polystyrene food plate (Fig. 1a-c).

#### 2.2. Inoculum and enzyme production

Spores were collected aseptically from one-week-old culture plates by using the method of (Mehmood et al., 2019) and were transferred into 100 mL of SDA (Sabouraud dextrose broth) media with 40 and 10 g/L of dextrose and peptone. The pH of the media was set at 7.0, and it was incubated for 48 hours at 37°C and 120 rpm on a shaking incubator (model SI4, SHEL LAB, Sheldon). Five grams of wheat bran and five milliliters of mineral growth medium (MGM) with the following

#### Table 1

Characteristics of polymeric samples selected for treatment with A. niger MG654699.1 lipase.

Polymer sample	Polyethylene	Polyethylene terephthalate	Polystyrene
Abbreviation	PE	PET	PS
Sample source	Shopping bag	Water bottle	Food plate
Sample size	$2 \times 2 \text{ cm}$	$2 \times 2 \text{ cm}$	$2 \times 2 \ cm$
Sample color	Whitish grey	Transparent white	Pure white
Sample density	0.94 g/cm <sup>-3</sup>	1.35 g/cm <sup>-3</sup>	0.98 g/cm <sup>-3</sup>
Sample shape	Square pieces	Square pieces	Square pieces
Sample physical	Flexible, water	Strong,	Soft, inert,
properties	proof, translucent, thin	lightweight, transparent	good insulator

compositions were added to each of the three 250-mL Erlenmeyer flasks (g/L): 12 g of NaH<sub>2</sub>PO<sub>4</sub>; 2.0 g of KH<sub>2</sub>PO<sub>4</sub>; 0.3 g of MgSO<sub>4</sub>.7H<sub>2</sub>O; 0.25 g of CaCl<sub>2</sub>; 1% (NH<sub>4</sub>)<sub>2</sub>SO<sub>4</sub>; and 2% olive oil. The flasks were cooled after being autoclaved. Each flask with 5 mL of inoculum was then incubated at 30°C for a week. Following the incubation time, each flask with 100 mL of distilled water was shaken at 37°C for 30 minutes in order to extract the enzyme from the fermentation media. Filtration was done using two layers of muslin fabric. Following filtration, centrifugation was carried out for five minutes at 12000 rpm (HERMLE, model Z36HK, Germany). The enzyme source, which is the supernatant, was collected after centrifugation and was used for screening, activity, and protein content determination (Supplementary, Fig. S1).

#### 2.3. Lipase assay and activity determination

The presence of lipase in the supernatant was confirmed with a qualitative screening assay. The media plates for this purpose were made with 0.01% indicator (methyl red), 2% agar, and 2% Tween 80. The media was allowed to solidify on autoclaved petri plates, and a circular well of 1 cm in diameter was produced. The supernatant containing the lipase (10  $\mu$ L) was added into the wells, and the color change was observed after the incubation of 24, 48, and 72 hours. The main purpose of this analysis is the release of fatty acids after the lipolytic action of the added enzyme, causing the change in media color (Samad et al., 1989). The UV spectrophotometer (model LABINDIA UV-3000+) was used to assess lipase activity quantitatively in the presence of pNPP (p-Nitrophenyl palmitate) as a substrate (Paluzar et al., 2021). Under assay conditions, one unit of enzyme activity was measured as an amount of enzyme liberating one µmol of *p*-nitrophenol per minute. The protein content of crude enzyme was also determined using the Bradford assay (Bradford, 1976). Enzyme specific activity was also calculated by employing equation 1 (A'yuni and Ilmi, 2021):

Enzyme specific activity = 
$$\frac{Lipase activity (U/mL)}{Protein content (mg/mL)}$$
 (1)

#### 2.4. SDS-PAGE

After the confirmation of lipase from different assays, it was subjected to SDS-PAGE in order to find out the molecular weight. An electrophoretic method (LAEMMLI, 1970) was utilized for separating (12%) and stacking (5%) gels. The obtained lipase from *A. niger* was precipitated further using the method of (Ha et al., 2021). The processed sample was mixed with sample buffer and loaded into the gel along with 10-250 KDa of protein marker. The gel was run at a constant voltage (120 volts) and stained with Coomassie dye.

## 2.5. Biodegradation analysis

## 2.5.1. Lipase-mediated degradation

The primary sources of selected polymer samples, including PE, PET, and PS, were converted to  $2\times 2$  cm pieces with an initial weight of 0.5 g



**Fig. 1.** Visual observation of polymer samples selected for enzyme treatment. (a) PE shopping bag, (b) PET water bottle, (c) PS food plate, (d)  $2 \times 2$  cm pieces of PE, (e)  $2 \times 2$  cm pieces of PE, (f)  $2 \times 2$  cm pieces of PS, (g) Lipase produced from *A. niger* MG654699.1, (h) Lipase-mediated degradation of PE, PET, and PS.

(Fig. 1d-f). All the samples were then sterilized for 1 hour with 70% ethanol, washed three times with distilled water, and finally dried overnight. The 25 mL of lipase extract along with 25 mL of 0.1 M phosphate buffer (pH 7.0) was used to individually inoculate PE, PET, and PS samples in separate 250 mL Erlenmeyer flasks at 37°C and 150 rpm for 30 days (Fig. 1g-h). After the completion of the incubation period, the treated samples were analyzed in terms of their biodegradation mechanisms, weight loss, and structural and physical variations.

## 2.5.2. Weight loss

The weight-loss method can be used as a simple indicator of polymer biodegradation. Additionally, treatments lacking the enzyme were carried out as blanks. The weight of control and lipase-treated samples was determined using an analytical balance (model Shimadzu AUX-320). To determine the degradation by lipase, the weight of the treated polymer samples was deducted from the blank, and the overall weight loss was determined in terms of percentages (Li et al., 2022). Following a 30-day incubation period, the samples were removed from the flasks, rinsed with ethanol, and then washed thoroughly using distilled water in order to obtain results. The following equation 2 was used to calculate the degree of biodegradation as a percentage of sample weight loss:

Weight loss (%) = 
$$(W_0 - W_t) \times 100/W_0$$
 (2)

where  $W_0$  is the weight of the untreated samples and  $W_t$  is the weight of enzyme-treated samples after the degradation.

## 2.5.3. FTIR

FTIR spectroscopy creates a chemical scan of the specimen under study and provides the chance to gather dynamic images. It is particularly helpful for researching heterogeneous and complex materials (Fan et al., 2021). To assure polymer linkage destruction, an Agilent Cary 630-FTIR spectrometer was used, and FTIR spectra of specimens were acquired before and after the degradation process in the frequency range of 4000-400 cm<sup>-1</sup>.

## 2.5.4. SEM

Surface alterations in polymers were examined in most of the investigations through observable changes in control and treated SEM images and were mostly characterized as the emergence of pores, cracks, and holes (Matjašič et al., 2021). A Hitachi S2380N scanning electron microscope was used to study the changes in surface morphologies and biodegradation impacts of untreated and enzyme-treated polymers.

## 2.6. Instrumental

SDA plates with A. niger MG654699.1 culture was incubated in an incubator (Velp Scientifica, model FTC 90E, Usmate, Italy), and a shaking incubator (model SI4, SHEL LAB, Sheldon) was used to obtain the fungal inoculums. The fermentation media was centrifuged at 12000 rpm (HERMLE, model Z36HK, Germany), and the supernatant (crude lipase) was separated for assay determination through a UV spectrophotometer (model LABINDIA UV-3000+). The weight of plastic samples before and after the lipase treatment was determined using an analytical balance (model Shimadzu AUX-320). All these instruments were available at the Department of Biochemistry, The Islamia University of Bahawalpur, Pakistan. The structural alterations of plastic samples were observed through an Agilent Cary 630-FTIR spectrometer at the Department of Chemistry, The Islamia University of Bahawalpur, Pakistan, within the frequency range of 4000 to 400  $\text{cm}^{-1}$ . The background noise was eliminated by performing a blank scan in the same frequency range. The surface changes before and after the lipase treatment were examined with a scanning electron microscope (Hitachi S2380N SEM) at the Central Hi-Tech Laboratory, University of Agriculture, Faisalabad, Pakistan. The gold-coated dried samples and controls were examined at 1.8 kV using a Hitachi S2380N SEM. The micrographs of the control and treated samples were then obtained.

## 2.7. Statistical analysis

Three replications of each experiment were performed. The data was displayed as the mean  $\pm$  standard deviation (SD). Utilizing Statistics 8.1 software, the ANOVA was conducted. Tukey's HSD (honestly significant difference) test was utilized to ascertain the differences, and P < 0.05 was determined to be statistically significant. The graphs were made with software programs, including OriginPro 9.0 and Microsoft Excel.

#### 3. Results

#### 3.1. Enzyme production and activity assays

The strain of A. niger with accession number MG654699.1 was previously identified by (Ismail et al., 2021) and used for the production of lipase. The crucial step in SSF is to choose an appropriate substrate since it serves as a support matrix, a source of nutrients, an inducer for the growth of microbes, and the generation of the required product. The lipase from A. niger was obtained after using the substrate of wheat bran in the fermentation process. The plate screening method was utilized to verify the production of lipase from the chosen strain. Indicator (methyl red) and substrate (Tween-80) were used to make the screening media plates. The findings showed that over an incubation period of 24 hours, the red color in the surroundings of wells containing it changed to yellow. As seen in Fig. 2a-d, these areas in the surroundings of wells became larger with time. The lipolytic action of the enzyme caused the release of fatty acids from triacylglycerols and resulted in color change. As a result, this technique for confirming the presence of lipase is thought to be simple, quick, and effective. The quantitative analysis of lipase obtained from A. niger MG654699.1 displayed 176.55 U/mL of enzyme activity, 7.18 mg/mL of protein content, and 24.60 U/mg of specific activity at the optimum conditions of pH 7.0 and 37°C (Fig. 2e). Each experiment was run in triplicate, and the results were found to be statistically significant at p < 0.05 (Supplementary, Table S1).

## 3.2. SDS-PAGE

Lipases have been produced and studied by numerous scientists, and their size varies depending on the microorganisms that synthesize them. The size of the lipase produced from *A. niger* MG654699.1 was confirmed using the technique by (LAEMMLI, 1970). The bands of protein were seen using Coomassie dye, and their size was evaluated



**Fig. 2.** The assays for the confirmation and quantification of lipase produced from *A. niger* MG654699.1. (a) Screening assay control plate with no lipase added, (b) Screening assay plate with added lipase for 24 hours, (c) Screening assay plate with added lipase for 48 hours, (d) Screening assay plate with added lipase for 72 hours, (e) Graph showing the activity, protein content, and specific activity of the produced lipase. Each point of the graph, along with error bars, shows the mean value of experiments performed in triplicate. Means showing identical characters are at par, while those with different ones are statistically significant (p < 0.05).

using the protein marker of 10–250 kDa. The lipase that was extracted from *A. niger* showed a size of 30 kDa, as shown in Fig. 3.

## 3.3. Enzymatic degradation of PE, PET, and PS

Lipases are members of the hydrolase group. They attack the ester bonds and facilitate the disintegration of triglycerides (Kaushal et al., 2021). Hydrolases play a crucial role in the breakdown of the carbon backbones of synthetic polymers. Although the degradative procedures are not fully known until now, the lipase produced from *A. niger* MG654699.1 can be a useful basis for more research. Polymers having C-C bonds can potentially be broken down by lipases in a way that is harmless for the surroundings. Techniques like analyzing the weight loss, FTIR spectra, and SEM images are used to assess how effective these enzymes are at breaking down plastics. These methods help to ascertain the advantageous impact of lipase on the disintegration of polymers. The produced lipase aided in the hydrolysis of chemical linkages, causing the degradation of polymeric materials. The hydrolases convert the substrates into products, as illustrated by equation 3:

$$AB + H_2O = Lipase => AOH + BH$$
(3)

Lipases degrade the lengthy carbon chains present in polymeric materials. The synthetic polymers found in our surroundings have a hydrophobic nature. The lipase produced by *A. niger* attaches hydrophobically to the surface of polymers. Most of the hydrolases have hydrophobic fissures near the site of action that can accommodate hydrophobic groups found in polymers. This property improves the ability of lipase to interact successfully with polymeric materials. The lengthy polymeric chains were hydrolytically split by the active site of



Fig. 3. Molecular size of lipase produced from *A. niger* MG654699.1. Lane 1 shows the protein marker, while Lane 2 shows the size of the produced lipase.

lipase and converted into smaller pieces. The schematic illustration in Fig. 4a-c displays the anticipated lipase degradation pathway for PE, PET, and PS.

#### 3.4. Weight loss

The results obtained on the biodeterioration ability of lipase are shown in Table 2. After a 30-day incubation period, all the samples were removed from the flasks and observed for weight loss. Out of the three treatments, PS showed the best biodegradability of 5%, followed by PE and PET, which showed 3.8% and 3.6% of biodegradability, respectively. The system was kept intact for the incubation period of thirty days, and no nutrients were added or subtracted from the medium. The enzyme attacked the ester bonds within the polymers, causing them to break down. According to the results of this experiment, it is reasonable to believe that polymers served as the catalyst for the respective enzyme.

## 3.5. FTIR

The Agilent Carv 630-FTIR spectrometer was used to examine the polymer films before and after the biodegradation treatment. Changes in bond scission, chemical transformation, and the production of new functional groups have all been seen in polymer degradation. FTIR spectra of A. niger MG654699.1 lipase-treated samples of PE (polyethylene), PET (polyethylene terephthalate), and PS (polystyrene) confirmed the weight loss measurements (Fig. 5). As a result of identical but sharper peaks (reduced transmittance), it was determined that the associated functional groups were more present in that region of the spectrum. The results indicate the formation of new intense peaks attributed to alkoxy groups (C-O) at 1204  $\text{cm}^{-1}$  in PE samples (Fig. 5a), 1016 and 1238  $\text{cm}^{-1}$  in PET samples (Fig. 5b), and 1025  $\text{cm}^{-1}$  in PS samples (Fig. 5c). The attributing peaks to the carbonyl bonds (C=O) were not formed in the incubated PE and PS; however, these were formed in PET at  $1714 \text{ cm}^{-1}$ . The alkene peaks (C=C) at 1490, 1600, and 1654 cm<sup>-1</sup> were also formed (Fig. 5c). It was observed that C-H bonds were also formed at various points in Fig. 5a-c after enzyme treatment, which confirmed the structural changes due to enzymatic degradation. The alterations of bonds like C-O, C-H, C=O, and C=C and the introduction of hydroxyl groups at 3300  $\text{cm}^{-1}$  in PE and at 3386  $\text{cm}^{-1}$  in PS samples can be noticed. The development of hydrolyzing bonds (alkoxy, alkene, carbonyl, and hydroxyl) in polymeric structures was thought to be a critical phase in biodegradation procedures, which eased the biodegradation procedure by allowing fungal enzymes to target these chemical bonds and functional groups. There would not be any action between the fungal enzyme and the polymer samples if these functional groups were not formed.

## 3.6. SEM

SEM (scanning electron microscope) is a valuable technology that produces a detailed and vivid appearance of materials with excellent clarity and high accuracy. SEM is commonly used for the characterization of materials and to examine surface phenomena in materials. A Hitachi S2380N scanning electron microscope was used for the examination of all samples. Fig. 6 displays the micrographs of polymeric samples both before (Fig. 6a-c) and after (Fig. 6d-f) their treatment with enzyme. After deterioration, the original morphologies of polymeric films were altered. The surfaces of the polymeric films were smooth when not subjected to enzymatic treatment, but deformities, including various holes, cavities, cracks, and surface irregularities, appeared on the surfaces of the polymers after their treatment with lipase. This showed that the lipase had attacked the polymeric surfaces, thus confirming their degradation. The maximum surface deformities were shown by polystyrene with several pits and cavities on the surface. Polyethylene also showed surface cracks and holes, while polyethylene terephthalate showed the least surface changes.



**Fig. 4.** Lipase-mediated degradative pathways. (a) Explained pathway for PE degradation. The enzyme attacked the C-C backbone along with dehydrogenation and oxidation. The large polymeric chains were converted into smaller units. An asterisk mark showed the location of additional functional groups being added to polymers. (b) Explained pathway for PET degradation. PET was hydrolyzed into ethylene glycol (EG) and terephthalic acid (TPA) after the action of the enzyme. The hydrolytic action of the enzyme produced the PET intermediate, including MHET [mono-(2-hydroxyethyl) terephthalate] and BHET [bis-(2-hydroxyethyl) terephthalate], which were further hydrolyzed into EG and TPA monomers. An asterisk mark showed the location of additional functional groups being added to polymers. (c) Explained pathway for PS degradation. The degradative process showed multiple steps, including (I) the breakdown of the main chain and (II) the breakdown of the side chains. A potential cleavage of the main and side chains caused the breakdown of PS.

#### Table 2

Comparative analysis of PE (polyethylene), PET (polyethylene terephthalate), and PS (polystyrene) weights before and after incubation.

Plastic samples	Percentage weight loss mean $\pm$ standard deviation
PE samples	
Control	$0 \pm 0^{c}$
A. niger MG654699.1 lipase	$3.8\pm0.15^{\rm b}$
PET samples	
Control	$0 \pm 0^{c}$
A. niger MG654699.1 lipase	$3.6\pm0.17^{\rm b}$
PS samples	
Control	$0\pm0^{ m c}$
A. niger MG654699.1 lipase	$5.0\pm0.26^a$

Note: The mean values shown by differing letters represent the statistical difference at p < 0.05 after performing all experiments in triplicate.

## 4. Discussion

Overall, the results of the earlier investigation, which focused on the lipase from *A. niger*, were in line with the results of the present study. Solid-state fermentation has significant potential for the synthesis of enzymes. The selection of an appropriate substrate in SSF involves several factors, primarily related to the cost and availability of substrate; therefore, agricultural byproducts are seen as the most favorable option (Dwivedi et al., 2022). The nitrogenous source has a considerable impact on lipase synthesis. Wheat bran is comprised of  $13.1 \pm 1.3\%$  of protein,

and various publications have described its importance for the synthesis of fungal lipases (de Azevedo et al., 2020). One of the substrates for filamentous fungi producing lipases is olive oil, which serves as a carbon source and inducer of lipase synthesis (Putri et al., 2020). Indicators, along with substrates added to agar plates, can be used to identify lipolytic microbes. It is a quick and effective screening method for determining organisms that produce lipase. Surfactants known as tweens are commonly utilized as the substrate of screening tests as they facilitate optimal substrate-enzyme interaction and are easy to include in culture media (Geoffry and Achur, 2018). Suyanto et al. (2019) showed that the lipase produced by the SSF using A. niger had 10.83 U/mL of activity (Suyanto et al., 2019). Two fungi, including A. niger (13 F) and F. solani (7 F), produced crude lipase with an activity of 5.95 U/mL (Patel and Shah, 2020). A study by (Romero et al., 2012) found that 37°C was the best temperature for the lipase activity derived from A. niger ATCC MYA-135. A. terreus (AH-F2) isolated from oily samples and soil showed the production of lipase with 5.0 U/ml activity (Shabbir and Mukhtar, 2018). Two fungi, Sordida sp. and Stemphylium lycopersici, isolated from Tocoyena bullata and Humiria balsamifera leaves, were capable of producing lipase with activities of 286 and 397 U/mL, respectively (Rocha et al., 2020). Our findings for the determination of lipase molecular weight are in agreement with the lipase produced by A. niger PTCC5010 which showed a band around 30 kDa after electrophoresis (ghamari, 2015). A 31 kDa lipase was extracted from A. niger, along with two other lipases of 43 and 65 kDa (Fernández-Lorente et al., 2005). There have been numerous reports of A. niger lipases with



Fig. 5. FTIR analysis of (a) PE (polyethylene), (b) PET (polyethylene terephthalate), and (c) PS (polystyrene) plastic samples incubated with lipase from *A. niger* MG654699.1. Several functional groups were introduced in the plastic films after incubation in comparison to controls.

molecular weights between 11 and 67 kDa. The lipase of *A. niger* (NCIM 1207) showed 32.2 kDa of size on SDS-PAGE (Mhetras et al., 2009).

Many extracellular enzymes from fungi have been identified to degrade various types of plastics (Urbanek et al., 2020). Lipase, a multifunctional biocatalyst that is mostly utilized for the esterification and hydrolysis of oil and fat. As a potential substitute for conventional chemical catalysts, lipase can catalyze additional reactions, including acidolysis, alcoholysis, ammonolysis, and transesterification, with the benefits of significant energy efficacy and environmentally friendly (Facin et al., 2019). Lipases are widely used in biotransformation due to their commercial availability, vast substrate specificity, independence from coenzymes or cofactors, activity under minimal reaction conditions, and generally good chemical selectivity and stereomeric specificity. They exhibit significant catalytic activities in both aqueous and non-aqueous conditions (Vanleeuw et al., 2019). The action of A. niger MG654699.1 extracted lipase on PE, PET, and PS has been shown in Fig. 4, converting the PE long chain into smaller units (Lenz, 1993), PET into EG and TPA, MHET, and BHET, for conversion into EG and TPA monomers (Yoshida et al., 2016), (Swiderek et al., 2023), and cleaving

the main and side chains of PS (Hou and Majumder, 2021). Various fungi, including Aspergillus flavus, Aspergillus niger, Pullularia pullulans, Curvularia sp., Trichoderma sp., and Penicillium sp., have demonstrated the ability to degrade PS using FTIR, weight loss, and microscopic analyses (Zhang et al., 2022). The enzymes displaying lipophilic activity (LiP) were discovered in Streptomyces sp. and were able to break down lignocellulose. Pometto et al. (1992) demonstrated the ability of these enzymes to break down PE (Pometto et al., 1992). The backbones of PET polymers usually have hydrolysable connections, making them vulnerable to lipase digestion. The lipase from T. lanuginosus has been shown to hydrolyze PET by interfacial activation (Eberl et al., 2009). As with PE and PET degradation, the researchers have found that PS degrading mechanisms also involve lipases, oxidoreductases, and laccases (Zhang et al., 2022). According to a study by (Hou and Majumder, 2021), alkane hydroxylases and P450 monooxygenases are most likely responsible for breaking C-C bonds present in the main chain of PS, while ring hydroxylating dioxygenases may cleave the side-chains. Although the whole biodegradation process and mechanisms are yet unknown, the lipase isolated from A. niger MG654699.1 provides a solid research basis



Fig. 6. Scanning electron micrographs of untreated plastic samples, including (a) PE, (b) PET, (c) PS, and A. niger MG654699.1 lipase-treated plastic sample, including (d) PE, (e) PET, and (f) PS. All the samples were completely dried before their analysis under SEM.

for future enzyme application and mechanism studies. The most widely used indicator to explain the rate of plastic degradation with several treatments is weight loss (Huang et al., 2021). The action of *A. niger* MG654699.1 lipase showed the degradation rate of 3.8%, 3.6%, and 5% for PE, PET, and PS, respectively (Supplementary, Fig. S2). The degradation of polyethylene for 28 days using *Aspergillus flavus* (PEDX3) resulted in a weight loss of 3.90% (Zhang et al., 2020). The lipase from *C. antarctica* hydrolyzed the PET and exhibited a weight loss of 0.4% after three weeks of treatment (Carniel et al., 2017). A study by Taghavi et al. (2021) stated that polyethylene and polystyrene showed 7.8% and 5.13% degradation, respectively, after 45 days of incubation.

The surface roughness of all plastic films indicated that selected strains played a beneficial role in biodegradation (Taghavi et al., 2021). The alterations at the molecular level cause a diminution of mechanical characteristics, which favors macroscopic degradation (Saliu et al., 2021). Oxidation products produced at various frequencies demonstrated the breakdown of the polymers (Sekhar et al., 2016). Previous FTIR studies showed that modifications to side chains and additions or deletions of functional groups are responsible for plastic degradation (Harshvardhan and Jha, 2013). The identified displacement of peaks and the production of hydrolyzing bonds and oxidation products in treated samples, such as hydroxyls, carbonyls, alcohols, and esters, represented the change in the chemical structure of plastics (Wilkes and Aristilde, 2017). A study by Singh et al. (2020) showed that the breakdown of polyethylene and polystyrene created more alkanes, whereas the degradation of polyethylene terephthalate produced only a small amount (Singh et al., 2020). SEM is an effective instrument for detecting surface defects, roughness, and the creation of grooves and cracks on plastic samples. Khandare et al. (2021) found that the surface roughness of treated polymers was caused by the action of lipase when observed with a scanning electron microscope (Khandare et al., 2021). The results

obtained from the current work showed that lipase can be produced from *A. niger* MG654699.1 under SSF. The produced lipase showed the degradation of selected polymers and, thus, can be used for the biodegradation of synthetic plastics.

#### 5. Conclusion

The collected results indicated that *A. niger* MG654699.1 has the ability to produce extracellular lipase during SSF, and the application of wheat bran made the procedure economical. The obtained enzyme was observed to degrade the PE, PET, and PS samples within a 30-day incubation period. The molecular size of lipase was found to be 30 kDa after SDS-PAGE analysis. Among all the lipase-treated samples, PS showed the maximum weight loss (5%). Surface disintegration, biocatalytic degradation, and physical and chemical modification of treated polymers suggested that the application of lipase by *A. niger* should be considered to disintegrate the bulk amount of plastic waste at municipal levels.

#### Statements & Declarations

#### Funding

This work did not receive any specific grant from funding agencies in the public, commercial, or not-for-profit sectors.

## **Ethical approval**

This article does not include any studies of human participants or animals by the authors of this investigation.

#### Consent to publish

All authors have agreed to publish this article for the use of scientific communities and the general public at large.

## Declaration of generative Artificial Intelligence

There is no use of Artificial Intelligence tools to analyze and draw insights from data as part of the research process.

## CRediT authorship contribution statement

Ayesha Safdar: Writing – original draft, Investigation, Formal analysis. Fatima Ismail: Writing – review & editing, Supervision, Methodology. Muhammad Imran: Validation, Conceptualization.

#### Declaration of competing interest

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the reported work.

## Data availability

No data was used for the research described in the article.

#### Acknowledgements

The authors are thankful to the Department of Biochemistry, The Islamia University of Bahawalpur, Pakistan, for providing necessary facilities.

#### Supplementary materials

Supplementary material associated with this article can be found, in the online version, at doi:10.1016/j.envadv.2024.100563.

#### References

- A'yuni, H., Ilmi, M., 2021. Lipase production from Aspergillus aculeatus Ms.11 in broth medium with variation of agitation speed. AIP Conf. Proc. 2353, 30081. https://doi. org/10.1063/5.0052540.
- Bradford, M.M., 1976. A rapid and sensitive method for the quantitation of microgram quantities of protein utilizing the principle of protein-dye binding. Anal. Biochem. 72, 248–254. https://doi.org/10.1016/0003-2697(76)90527-3.
- Carniel, A., Valoni, É., Nicomedes, J., Gomes, A.da C., Castro, A.M.de, 2017. Lipase from Candida antarctica (CALB) and cutinase from Humicola insolens act synergistically for PET hydrolysis to terephthalic acid. Process Biochem 59, 84–90. https://doi.org/ 10.1016/j.procbio.2016.07.023.
- de Azevedo, W.M., de Oliveira, L.F.R., Alcântara, M.A., Cordeiro, A.M.T.de M., Damasceno, K.S.F.da S.C., Assis, C.F.de, Sousa Junior, F.C.de, 2020. Turning cacay butter and wheat bran into substrate for lipase production by Aspergillus terreus NRRL-255. Prep. Biochem. Biotechnol. 50, 689–696. https://doi.org/10.1080/ 10826068.2020.1728698.
- Demir, H., Tari, C., 2016. Effect of physicochemical parameters on the polygalacturonase of an Aspergillus sojae mutant using wheat bran, an agro-industrial waste, via solidstate fermentation. J. Sci. Food Agric. 96, 3575–3582. https://doi.org/10.1002/ jsfa.7543.
- Dominik, D., Jennifer, C., R, S.W., 2019. Plastics: environmental and biotechnological perspectives on microbial degradation. Appl. Environ. Microbiol. 85 https://doi.org/ 10.1128/AEM.01095-19 e01095-19.
- Dwivedi, S., Tanveer, A., Yadav, S., Anand, G., Yadav, D., 2022. Agro-wastes for cost effective production of industrially important microbial enzymes. Microb. Biotechnol. 435–460. https://doi.org/10.1002/9781119834489.ch23.
- Eberl, A., Heumann, S., Brückner, T., Araujo, R., Cavaco-Paulo, A., Kaufmann, F., Kroutil, W., Guebitz, G.M., 2009. Enzymatic surface hydrolysis of poly(ethylene terephthalate) and bis(benzoyloxyethyl) terephthalate by lipase and cutinase in the presence of surface active molecules. J. Biotechnol. 143, 207–212. https://doi.org/ 10.1016/j.jbiotec.2009.07.008.
- Facin, B.R., Melchiors, M.S., Valério, A., Oliveira, J.V., Oliveira, D.de, 2019. Driving immobilized lipases as biocatalysts: 10 years state of the art and future prospects. Ind. Eng. Chem. Res. 58, 5358–5378. https://doi.org/10.1021/acs.iecr.9b00448.

- Fan, C., Huang, Y.-Z., Lin, J.-N., Li, J., 2021. Microplastic constituent identification from admixtures by Fourier-transform infrared (FTIR) spectroscopy: The use of polyethylene terephthalate (PET), polyethylene (PE), polypropylene (PP), polyvinyl chloride (PVC) and nylon (NY) as the model constituent. Environ. Technol. Innov. 23, 101798 https://doi.org/10.1016/j.eti.2021.101798.
- Fernández-Lorente, G., Ortiz, C., Segura, R.L., Fernández-Lafuente, R., Guisán, J.M., Palomo, J.M., 2005. Purification of different lipases from Aspergillus niger by using a highly selective adsorption on hydrophobic supports. Biotechnol. Bioeng. 92, 773–779. https://doi.org/10.1002/bit.20656.
- Gao, R., Sun, C., 2021. A marine bacterial community capable of degrading poly (ethylene terephthalate) and polyethylene. J. Hazard. Mater. 416, 125928 https:// doi.org/10.1016/j.jhazmat.2021.125928.
- Geoffry, K., Achur, R.N., 2018. Screening and production of lipase from fungal organisms. Biocatal. Agric. Biotechnol. 14, 241–253. https://doi.org/10.1016/j. bcab.2018.03.009.
- ghamari, mahdieh, 2015. Purification and Zymography of lipase from Aspergillus niger PTCC5010. Int. J. Eng. 28, 1117–1123.
- Ha, J., Park, J.-Y., Choi, Y., Chang, P.-S., Park, K.-M., 2021. Comparative analysis of universal protein extraction methodologies for screening of lipase activity from agricultural products. Catalysts. https://doi.org/10.3390/catal11070816.
- Harshvardhan, K., Jha, B., 2013. Biodegradation of low-density polyethylene by marine bacteria from pelagic waters, Arabian Sea, India. Mar. Pollut. Bull. 77, 100–106. https://doi.org/10.1016/j.marpolbul.2013.10.025.
- Hou, L., Majumder, E.L.-W., 2021. Potential for and distribution of enzymatic biodegradation of polystyrene by environmental microorganisms. Materials. https:// doi.org/10.3390/ma14030503.
- Huang, D., Xu, Y., Lei, F., Yu, X., Ouyang, Z., Chen, Y., Jia, H., Guo, X., 2021. Degradation of polyethylene plastic in soil and effects on microbial community composition. J. Hazard. Mater. 416, 126173 https://doi.org/10.1016/j. jhazmat.2021.126173.
- Ismail, A.R., Baek, K.-H., 2020. Lipase immobilization with support materials, preparation techniques, and applications: present and future aspects. Int. J. Biol. Macromol. 163, 1624–1639. https://doi.org/10.1016/j.ijbiomac.2020.09.021.
- Ismail, F., Ghani, A., Akbar, S., 2021. Emergence of Antifungal Azole Resistance in the Fungal Strains of Tinea corporis, Tinea capitis, Tinea cruris and Tinea pedis from the Locality of Southern Punjab, Pakistan. RADS J. Biol. Res. Appl. Sci. 12, 24–38. https://doi.org/10.37962/jbas.v12i1.348.
- Jin, J., Arciszewski, J., Auclair, K., Jia, Z., 2023. Enzymatic polyethylene biorecycling: Confronting challenges and shaping the future. J. Hazard. Mater. 460, 132449 https://doi.org/10.1016/j.jhazmat.2023.132449.
- Kaushal, J., Khatri, M., Arya, S.K., 2021. Recent insight into enzymatic degradation of plastics prevalent in the environment: a mini - review. Clean. Eng. Technol. 2, 100083 https://doi.org/10.1016/j.clet.2021.100083.
- Khandare, S.D., Chaudhary, D.R., Jha, B., 2021. Marine bacterial biodegradation of lowdensity polyethylene (LDPE) plastic. Biodegradation 32, 127–143. https://doi.org/ 10.1007/s10532-021-09927-0.
- Kumar, A., Park, G.D., Patel, S.K.S., Kondaveeti, S., Otari, S., Anwar, M.Z., Kalia, V.C., Singh, Y., Kim, S.C., Cho, B.-K., Sohn, J.-H., Kim, D.R., Kang, Y.C., Lee, J.-K., 2019. SiO2 microparticles with carbon nanotube-derived mesopores as an efficient support for enzyme immobilization. Chem. Eng. J. 359, 1252–1264. https://doi.org/ 10.1016/j.cej.2018.11.052.
- Kumar, A., Verma, V., Dubey, V.K., Srivastava, A., Garg, S.K., Singh, V.P., Arora, P.K., 2023. Industrial applications of fungal lipases: a review. Front. Microbiol. 14 https://doi.org/10.3389/fmicb.2023.1142536.
- LAEMMLI, U.K., 1970. Cleavage of structural proteins during the assembly of the head of Bacteriophage T4. Nature 227, 680–685. https://doi.org/10.1038/227680a0.
- Lenz, R.W., 1993. Biodegradable polymers Biopolymers I, in: Langer, R.S., Peppas, N.A. (Eds.), Springer Berlin Heidelberg, Berlin, Heidelberg, pp. 1–40. 10.1007/B Fb0027550.
- Li, H., Kognou, A.L.M., Jiang, Z.-H., Qin, W., Xu, C.C., 2022. Production of biopolyurethane (BPU) foams from greenhouse/agricultural wastes, and their biodegradability. Biofuels Bioprod. Biorefin. 16, 826–837. https://doi.org/10.1002/ bbb.2344.
- Matjašič, T., Simčič, T., Medvešček, N., Bajt, O., Dreo, T., Mori, N., 2021. Critical evaluation of biodegradation studies on synthetic plastics through a systematic literature review. Sci. Total Environ. 752, 141959 https://doi.org/10.1016/j. scitotenv.2020.141959.
- Mehmood, T., Saman, T., Asgher, M., Irfan, M., Anwar, Z., Nadeem, F., Siddiqa, A., 2019. Optimization of cultural parameters for pectin methylestrase and polygalacturonase production from Schizophyllum commune in solid state fermentation. Bangladesh J. Bot. 48, 65–74.
- Melani, N.B., Tambourgi, E.B., Silveira, E., 2020. Lipases: from production to applications. Sep. Purif. Rev. 49, 143–158. https://doi.org/10.1080/ 15422119.2018.1564328.
- Mhetras, N.C., Bastawde, K.B., Gokhale, D.V, 2009. Purification and characterization of acidic lipase from Aspergillus niger NCIM 1207. Bioresour. Technol. 100, 1486–1490. https://doi.org/10.1016/j.biortech.2008.08.016.
- Otari, S.V, Patel, S.K.S., Kalia, V.C., Lee, J.-K., 2020. One-step hydrothermal synthesis of magnetic rice straw for effective lipase immobilization and its application in esterification reaction. Bioresour. Technol. 302, 122887 https://doi.org/10.1016/j. biortech.2020.122887.
- Paluzar, H., Tuncay, D., Aydogdu, H., 2021. Production and characterization of lipase from Penicillium aurantiogriseum under solid-state fermentation using sunflower pulp. Biocatal. Biotransform. 39, 333–342. https://doi.org/10.1080/ 10242422.2021.1901888.

- Patel, G.B., Shah, K.R., 2020. Isolation, screening and identification of Lipase producing fungi from cotton seed soapstock. Indian J. Sci. Technol. 13, 3762–3771. https://doi. org/10.17485/IJST/v13i36.1099.
- Patel, S.K.S., Lee, J.-K., 2022. Plastic eating enzymes: a step towards sustainability. Indian J. Microbiol. 62, 658–661. https://doi.org/10.1007/s12088-022-01041-w.
- Pometto, A.L., Lee, B.T., Johnson, K.E., 1992. Production of an extracellular polyethylene-degrading enzyme(s) by Streptomyces species. Appl. Environ. Microbiol. 58, 731–733. https://doi.org/10.1128/aem.58.2.731-733.1992.
- Putri, D.N., Khootama, A., Perdani, M.S., Utami, T.S., Hermansyah, H., 2020. Optimization of Aspergillus niger lipase production by solid state fermentation of agro-industrial waste. Energy Rep. 6, 331–335. https://doi.org/10.1016/j. egyr.2019.08.064.
- Restrepo-Flórez, J.-M., Bassi, A., Thompson, M.R., 2014. Microbial degradation and deterioration of polyethylene – a review. Int. Biodeterior. Biodegradation 88, 83–90. https://doi.org/10.1016/j.ibiod.2013.12.014.
- Reyes-Reyes, A.L., Valero Barranco, F., Sandoval, G., 2022. Recent advances in lipases and their applications in the food and nutraceutical industry. Catalysts. https://doi. org/10.3390/catal12090960.
- Rhodes, C.J., 2018. Plastic pollution and potential solutions. Sci. Prog. 101, 207–260. https://doi.org/10.3184/003685018X15294876706211.
- Rocha, K.S.C., Queiroz, M.S.R., Gomes, B.S., Dallago, R., de Souza, R.O.M.A., Guimarães, D.O., Itabaiana, I., Leal, I.C.R., 2020. Lipases of Endophytic Fungi Stemphylium lycopersici and Sordaria sp.: Application in the synthesis of solketal derived Monoacylglycerols. Enzyme Microb. Technol. 142, 109664 https://doi.org/ 10.1016/j.enzmictec.2020.109664.
- Romero, C.M., Pera, L.M., Loto, F., Vallejos, C., Castro, G., Baigori, M.D., 2012. Purification of an organic solvent-tolerant lipase from Aspergillus niger MYA 135 and its application in ester synthesis. Biocatal. Agric. Biotechnol. 1, 25–31. https:// doi.org/10.1016/j.bcab.2011.08.013.
- Safdar, A., Ismail, F., Imran, M., 2023. Characterization of detergent-compatible lipases from candida albicans and acremonium sclerotigenum under solid-state fermentation. ACS Omega. https://doi.org/10.1021/acsomega.3c03644.
- Safdar, A., Ismail, F., Safdar, M., Imran, M., 2024. Eco-friendly approaches for mitigating plastic pollution: advancements and implications for a greener future. Biodegradation. https://doi.org/10.1007/s10532-023-10062-1.
- Saliu, F., Veronelli, M., Raguso, C., Barana, D., Galli, P., Lasagni, M., 2021. The release process of microfibers: from surgical face masks into the marine environment. Environ. Adv. 4, 100042 https://doi.org/10.1016/j.envadv.2021.100042.
- Samad, M.Y.A., Razak, C.N.A., Salleh, A.B., Zin Wan Yunus, W.M., Ampon, K., Basri, M., 1989. A plate assay for primary screening of lipase activity. J. Microbiol. Methods 9, 51–56. https://doi.org/10.1016/0167-7012(89)90030-4.
- Sekhar, V.C., Nampoothiri, K.M., Mohan, A.J., Nair, N.R., Bhaskar, T., Pandey, A., 2016. Microbial degradation of high impact polystyrene (HIPS), an e-plastic with decabromodiphenyl oxide and antimony trioxide. J. Hazard. Mater. 318, 347–354. https://doi.org/10.1016/j.jhazmat.2016.07.008.

- Shabbir, A., Mukhtar, H., 2018. Optimization process for enhanced extracellular lipases production from a new isolate of Aspergillus terreus ah-F2. Pak. J. Bot 50, 1571–1578.
- Singh, R.K., Ruj, B., Sadhukhan, A.K., Gupta, P., 2020. A TG-FTIR investigation on the copyrolysis of the waste HDPE, PP, PS and PET under high heating conditions. J. Energy Inst. 93, 1020–1035. https://doi.org/10.1016/j.joei.2019.09.003.
- Suyanto, E., Soetarto, E.S., Cahyanto, M.N., 2019. Production and optimization of lipase by Aspergillus niger using coconut pulp waste in solid state fermentation. In: Journal of Physics: Conference Series. IOP Publishing, p. 12005. https://doi.org/10.1088/ 1742-6596/1374/1/012005.
- Świderek, K., Velasco-Lozano, S., Galmés, M.À., Olazabal, I., Sardon, H., López-Gallego, F., Moliner, V., 2023. Mechanistic studies of a lipase unveil effect of pH on hydrolysis products of small PET modules. Nat. Commun. 14, 3556. https://doi.org/ 10.1038/s41467-023-39201-1.
- Taghavi, N., Singhal, N., Zhuang, W.-Q., Baroutian, S., 2021. Degradation of plastic waste using stimulated and naturally occurring microbial strains. Chemosphere 263, 127975. https://doi.org/10.1016/j.chemosphere.2020.127975.
- Temporiti, M.E., Nicola, L., Nielsen, E., Tosi, S., 2022. Fungal Enzymes Involved in Plastics Biodegradation. Microorganisms. https://doi.org/10.3390/ microorganisms10061180.
- Umamaheswari, S., Murali, M., 2013. FTIR spectroscopic study of fungal degradation of poly (ethylene terephthalate) and polystyrene foam. Chem. Eng. 64, 159.
- Urbanek, A.K., Mirończuk, A.M., García-Martín, A., Saborido, A., de la Mata, I., Arroyo, M., 2020. Biochemical properties and biotechnological applications of microbial enzymes involved in the degradation of polyester-type plastics. Biochim. Biophys. Acta 1868, 140315. https://doi.org/10.1016/j.bbapap.2019.140315.
- Vanleeuw, E., Winderickx, S., Thevissen, K., Lagrain, B., Dusselier, M., Cammue, B.P.A., Sels, B.F., 2019. Substrate-specificity of Candida rugosa lipase and its industrial application. ACS Sustain. Chem. Eng. 7, 15828–15844. https://doi.org/10.1021/ acssuschemeng.9b03257.
- Wilkes, R.A., Aristilde, L., 2017. Degradation and metabolism of synthetic plastics and associated products by Pseudomonas sp.: capabilities and challenges. J. Appl. Microbiol. 123, 582–593. https://doi.org/10.1111/jam.13472.
- Yoshida, S., Hiraga, K., Takehana, T., Taniguchi, I., Yamaji, H., Maeda, Y., Toyohara, K., Miyamoto, K., Kimura, Y., Oda, K., 2016. A bacterium that degrades and assimilates poly(ethylene terephthalate). Science 351, 1196–1199. https://doi.org/10.1126/ science.aad6359.
- Zhang, J., Gao, D., Li, Q., Zhao, Yixuan, Li, L., Lin, H., Bi, Q., Zhao, Yucheng, 2020. Biodegradation of polyethylene microplastic particles by the fungus Aspergillus flavus from the guts of wax moth Galleria mellonella. Sci. Total Environ. 704, 135931 https://doi.org/10.1016/j.scitotenv.2019.135931.
- Zhang, Y., Pedersen, J.N., Eser, B.E., Guo, Z., 2022. Biodegradation of polyethylene and polystyrene: from microbial deterioration to enzyme discovery. Biotechnol. Adv. 60, 107991 https://doi.org/10.1016/j.biotechadv.2022.107991.